

Material Specification Sheet

Material Number: 18440

Description: Double Coated High Strength Acrylic Tape Low Surface Energy (LSE) - Tissue

Carrier

Applications: 18440 is double coated version of FFT 18400, designed for those bonding applications requiring high levels of initial tack and excellent adhesion to a wide variety of materials. The tissue carrier offers excellent conformability to curved or irregular surfaces and improved dimensional stability over transfer tapes.

Product Construction:

Property	Thickness	
Adhesive/ Carrier	0.0063" (160 μm)	Acrylic Adhesive on Nonwoven Carrier
Liner	0.0036" (91 µm)	Densified Kraft

Typical Physical Properties:

Property	Material		Test Method	Value
Adhesion- 180° Peel* Stainless Sta ABS PP Talc PP HDPE TPO Painted Meta	Stainless Steel	Unwind Side	PSTC-101	106 oz/in (1156 N/m)
		Liner Side	1 010 101	133 oz/in (1453 N/m)
	ABS	Unwind Side		98 oz/in (1068 N/m)
		Liner Side		131 oz/in (1436 N/m)
	PP	Unwind Side		102 oz/in (1121 N/m)
		Liner Side		128 oz/in (1401 N/m)
	Talc PP	Unwind Side		99 oz/in (1086 N/m)
		Liner Side		125 oz/in (1366 N/m)
	HDDE	Unwind Side		88 oz/in (963 N/m)
		Liner Side		112 oz/in (1226 N/m)
	TDO	Unwind Side		123 oz/in (1348 N/m)
	TPU	Liner Side		131 oz/in (1436 N/m)
	Painted Metal	Unwind Side		82 oz/in (893 N/m)
	Fairited Metai	Liner Side		83 oz/in (911 N/m)
Loop Tack	Stainless Steel	Unwind Side	PSTC-16	126 oz/in (1383 N/m)
		Liner Side		139 oz/in (1523 N/m)
Static Shear	1 in ² , 2.2# load 1 in ² , 2.2# load	Unwind Side	PSTC-107	>3000 minutes
		Liner Side		>750 minutes
Service Temperature		Continuous	I N/A	200°F (93°C)
(max)		Intermittent		250°F (121°C)
Min. Application Temp.			N/A	50°F (10°C)

^{*2} mil PET support, 1 minute dwell, 12 in/min

The data, including flammability ratings, presented in this Material Specification Sheet is for reference only and reflects typical properties and characteristics obtained under controlled test conditions. FFT excludes any expressed or implied warranties of fitness for a particular application or purpose. The user has the responsibility to determine fitness for use and assumes all risk and liability for that particular application. The data reflected in this bulletin is subject to change. Please contact FFT to verify current status.

