



Material Specification Sheet

Description: 1.8# 35 IFD Medium Reticulated Foam

Product Summary: Reticulated foam is a fast-drying open-cell foam with breathability for water and air to easily pass through the material, making it an ideal solution for outdoor cushioning applications and other uses.

Typical Physical Properties:

Property	Value
Color	Natural or Black
Density	1.7 – 1.9 lbs. / ft. ³
Indentation Force Deflection	32.5 – 37.5 lbs. / ft. ²
Cell Count	30 ppi
CFD (50%)	.5 psi
Tensile Strength	20 psi min.
Elongation	>225%
Tear Resistance	5.5 lbs. min.
Hysteresis Loss	35% max
Flammability	Cal 117-2013

The data, including flammability ratings, presented in this Material Specification Sheet is for reference only and reflects typical properties and characteristics obtained under controlled test conditions. FFT excludes any expressed or implied warranties of fitness for a particular application or purpose. The user has the responsibility to determine fitness for use and assumes all risk and liability for that particular application. The data reflected in this bulletin is subject to change. Please contact FFT to verify current status.