



Science.
Applied to Life.™

Designing the future today.

3M Converter Markets


Selection Guide | July 2023

Creative Precision

3M's legacy of innovation drives the continual improvement of our adhesive technologies. Pair that with the tools and technical support we provide, and you're on your way to quickly finding the products that meet your precise requirements.

3M's industry-leading adhesive technologies, added to your own expertise, will help increase production efficiency and improve product performance, appearance, and identification. Partner with 3M to create converted parts that are perfect for your customer's designs.

Trust 3M Converter Markets as your source for tapes, films, release liners, reclosable fasteners, labeling materials, flexographic mounting systems, graphic solutions and more.



Expect performance. Spec 3M.



Persistent Innovation

It's all about helping customers around the globe increase their production efficiency and improve product performance, appearance and identification.

3M Converter Solution Tools — just a click away.

Compare bonding products based on your specifications using our online Bonding Product Comparison Tool. 3M design specialists can provide additional insight into these options, plus make recommendations tailored to your specific needs.

Let's work together. 3M products are constantly evolving to better meet customer needs. If you need help finding the right product for your solutions, get in touch with us.

Make a winning combination with the 3M TSR Program.

When you're digging into a new project, reach out to your 3M Specialist who will work with you on initial testing of an adhesive design solution.

Information access — 24/7.

From product information and educational materials to our selector tools, you'll find our online resources invaluable.

3M.com/Converter

3M.com/Doublesidedtape

3M.com/ThinBondingSelector

Thin Bonding App



iOS



Android



Give 3M a Call

1-800-831-0658
Monday–Friday
8 a.m. to 5 p.m. Central Time



Chat with us


Monday–Friday
8 a.m. to 5 p.m. Central Time



Send us a Message

Find "Support Link" at
3M.com/Converter.
We will respond to your email
request in 24–48 hours.

The Science of Adhesion



Bonding and Assembly eLearning Academy

Our website offers courses that will expand your knowledge of bonding solutions: how they work, what might go wrong and products to consider for various applications.

Adhesion Science consists of three equally essential parts which combine to form the basis of adhesive selection and adhesive engineering: Surface Science, Adhesive Chemistry, and Joint Geometry.

Learn more about how adhesives work and how you can help them perform better. Go to 3M.com/bonding-and-assembly and click on “The Science of Adhesion” link.

Surface energy ranges.

**Metal Surfaces
(High Surface Energy)**

mJ/m ²	Surfaces
1103	Copper
840	Aluminum
753	Zinc
526	Tin
458	Lead
700–1100	Stainless Steel
250–500	Glass Porcelain

**High Surface Energy
Plastics (HSE)**

mJ/m ²	Surfaces
50	Polyimide Industrial Film
47	Phenolic
46	Nylon
45	Alkyd Enamel
43	Polyester
43	Epoxy Paint

**Low Surface Energy
Plastics (LSE)**

mJ/m ²	Surfaces
37	PVA
36	Polystyrene
36	Acetal
33	EVA
31	Polyethylene
29	Polypropylene
28	Polyvinyl Fluoride Film
18	PTFE
Broad Range	Powder Coated Paints


As a rule of thumb, the higher the surface energy, the greater the strength of adhesion.
Note: These values are provided as a guide. Formulation modifications can substantially alter surface energies.

Secure bonding. It's all about adhesive surface contact.

Applying firm pressure to the bond increases adhesive flow and contact for more secure bonding. Time and temperature will typically further increase contact and adhesion values.


1

**Initial Contact
(Minimal Contact)**



2

**After Rubdown
(More Contact)**



3

**After Dwell Time
(Excellent Contact)**




Table of Contents

Science of Adhesion.....	2
Pressure Sensitive Adhesive Constructions.....	4

Double Sided Tapes

Considerations for Selecting 3M™ Double Sided Tapes....	6–7
3M Go-To Adhesives.....	8–9
Adhesive Families.....	10–11
Selection Guide.....	12
Adhesive Properties.....	13
Liner Reference Chart.....	14
3M™ Secondary Release Liners.....	15
3M™ Adhesive Transfer Tapes.....	16–19
3M™ Double Lined Adhesive Transfer Tapes.....	20–21
3M™ Double Coated Tapes.....	21–24
3M™ Differential Double Coated Tapes.....	25
3M™ Removable/Repositionable Tapes.....	26
3M™ Membrane Switch Spacers.....	27–28
3M™ Extended Liner Tapes.....	29
3M™ Screen Printable Adhesives.....	30
Scotch® ATG Adhesive Transfer Tapes.....	30
3M™ Foam Lamination Tapes.....	31
3M™ Bonding Films.....	32
3M™ Double Coated Foam Tapes.....	32
3M™ VHB™ Tapes.....	33–34

Durable Label Materials

Overview.....	36–37
3M™ Versatile Print Label Materials.....	38–39
3M™ Water-based Inkjet label Materials.....	40
Facestock Properties.....	41–43
Liner Selection.....	43
Adhesive Families.....	44–45
Adhesive Selection Guide.....	46
Adhesive Properties.....	47
3M™ Durable Label Materials.....	48–58
3M™ Removable Label Materials.....	59
3M™ Tamper Evident Label Materials.....	60
3M™ Overlamine Label Materials.....	61–62
3M™ Specialty Label Materials.....	62–64

Single Coated Tapes

Selection Guides and Reference Charts.....	66–67
3M™ Single Coated Tapes.....	68–74
3M™ Single Coated Foam Tapes.....	74
3M™ Single Coated Foil/Foam Sheets.....	75
3M™ Extreme Sealing Tapes.....	75
3M™ Splicing Tapes.....	75
3M™ Polyurethane Protective Tapes (PPT).....	75
3M™ Repulpable Tapes.....	76

Reclosable Fasteners

Overview.....	78
3M™ Dual Lock™ Reclosable Fasteners.....	79
3M™ Hook and Loop Reclosable Fasteners.....	80

Specialty Products

3M™ Premium Polyurethane Foam Tapes.....	82
Construction Availability.....	82

Flexographic Mounting Systems


Overview.....	84
3M™ Flexographic Mounting Systems.....	85–86
E-Series Tapes with Easy Mount Adhesive.....	87
EH-Series Tapes.....	87
3M™ Thin Tapes.....	87–88
3M™ Flexographic Mounting Aids.....	88
3M™ Non-Repulpable Splicing Tapes.....	88

Numerical Index.....	89–91
----------------------	-------


Expect performance. Spec 3M.

Pressure Sensitive Adhesive Constructions


3M™ Adhesive Transfer Tapes




3M™ Double-lined Adhesive Transfer Tapes — Sheets




3M™ Double Coated Tapes




3M™ Double Coated Spacers — Sheets




3M™ VHB™ Tape and Double Coated Foam Tapes




3M™ Single Coated Foam Tapes




3M™ Durable Label Materials



3M™ Single Coated Tapes



3M™ Dual Lock™ Reclosable Fasteners



3M™ Reclosable Fasteners — Hook and Loop



Double Sided Tapes

Make your design a reality.

Whether you're bonding similar or different substrates, our double sided tapes provide the strength, conformability, adhesion and aesthetic requirements you need to make your project successful.

Learn more at:
3M.com/DoubleSidedTape



Bond glass to plastic.

Help make sales soar with anti-lifting, drop-resistant 3M™ Double Coated Tape 93015LE.



Tapes created for performance.

A double sided tape has pressure-sensitive adhesive exposed on both sides, allowing two parts to be bonded together by the tape between them. A carrier that holds adhesive can range from a film as thin as a fraction of a millimeter up to a thick foam that helps damp vibrations. Pressure sensitive adhesives can meet specific needs from low-tack, which allows for repositioning, all the way up to permanent bonding solutions. A double sided tape that has a carrier can be produced with the same adhesive on both sides, or with different adhesives to meet the bonding requirements of different substrates.

Benefits of a 3M™ Double Sided Tape.

While the characteristics of adhesive families and individual tapes vary, double sided tapes generally offer these benefits to your production.



Faster Assembly Time

Tape is easy to apply by hand or with automation. No waiting for adhesive to cure or mechanical fastening to be completed.



Design Flexibility

Conformability, gap filling, invisible bond lines—the flexible design options you need.



Immediate Handling Strength

Immediate handling strength with no cure time. Assembled parts move faster to the next step.



LSE and Dissimilar Materials Bonding

Versatile for lightweight designs and hard-to-stick-to surfaces.



Clean Aesthetics and Reduced Product Bulk

Virtually invisible bond lines without protruding fasteners. Replaces mechanical fasteners with thinner, lighter materials.



Moisture Intrusion Prevention

Provides adhesion to both substrates, helping prevent moisture from penetrating the bond.

Making the best choice for the needed performance.

What materials are you bonding? How will the assembly be used?

- Type of substrate or hard-to-bond materials
- Bonding dissimilar materials
- Configuration of your part (design/shape)
- Appearance and aesthetic considerations
- Need for disassembly for maintenance or service

How will the product be processed?

- Need high-speed bonding
- Need to be able to reposition
- Will be subjected to vibration
- Requires heat and/or pressure for bonding
- Desire to cut costs, increase production, or simplify operation


How do you need the adhesive to perform?

- Match strength to stresses/ combination of stresses: tensile, shear, cleavage and peel
- Flexibility
- Maintain surface integrity
- Bond and seal
- Resist harsh environmental conditions


Learn more at: [3M.com/DoubleSidedTape](https://www.3M.com/DoubleSidedTape)

Design for challenges.


Regardless of the joint type used, it's important to understand the different stresses that are imparted onto a bonded assembly.




Tensile is pull exerted equally over the entire joint. Pull direction is straight and away from the adhesive bond.



Shear is pull directed across the adhesive, forcing the substrates to slide over each other.



Cleavage is pull concentrated at one edge of the joint, exerting a prying force on the bond. The other edge of the joint is theoretically under zero stress.



Peel is concentrated along a thin line at the edge of the bond where one substrate is flexible. Once peeling has begun, the stress line stays out in front of the advancing bond separation.

Thin, clean designs made easy.


Pressure Sensitive Adhesives (PSA)

A quick peel and stick that offers consistent bondline thickness.

PSAs easily distribute loading over the entire bondline. They are low odor so no ventilation is needed. Plus, there's no curing required.

Production flexibility: Hand apply, ATG, die cuts, automation, or roll-to-roll processing.

Learn more at:
[3M.com/Bonding](https://www.3m.com/Bonding)



3M Go-To Adhesives

The bond between concept and reality.

Acrylic adhesives open the door to solving the challenges of speed, strength and product shelf life. Now it's time to dream bigger. 3M Go-To Adhesives are flagged throughout this catalog with the red circle next to product numbers.



100MP

3M™ High-Performance Acrylic Adhesive 100MP

Higher peel strength than most acrylic formulations. Exceptional shear strength, even at high temperatures.



200MP

3M™ High-Strength Acrylic Adhesive 200MP

Shear strength with versatility for bonding a variety of commonly used substrates. Great for outdoor applications and repeat use.



300LSE

3M™ Low Surface Energy Acrylic Adhesive 300LSE

For hard-to-bond surfaces. Great solution for dissimilar material bonding. Holds securely and performs reliably — giving you more freedom to imagine. To design. To build.



300MP+

3M™ High-tack Acrylic Adhesive 300MP+

For hard-to-bond and textured materials such as foams and textiles.

Giving you more freedom to imagine.

Attach. Seal. Reduce noise. Expand your materials—and your design possibilities. Advanced adhesives keep it together under the harshest of conditions, while you feel the thrill of defying creative limitations.

100MP

Built for extremes. Indoor and out.

Adhesives that deliver in high temperatures and other challenging environments. Exceptional shear strength even at elevated temperatures; outstanding solvent resistance.



Bond metal to metal.

200MP

Brought together by design.

Best for bonding metals and high surface energy substrates. Anti-lifting for precision and staying-power performance on curved surfaces.



Bond printed polycarbonate to polyester.

300LSE

Thin can do what you can imagine.

Make your design a reality. Bond plastic to metals. Rubber to plastic. Even foam to chrome. Open your mind to new design possibilities.



Bond metal speaker mesh to plastic.

300MP+

It's a textured world. Design for it.

Attach, seal, reduce noise. This adhesive is for bonding foam and fabric.



Attach fabric to metal.

Adhesive Transfer Tapes

Double Coated Tapes

Product Page

16

—

16, 20

22

18, 20

22

18

22–23

Expect performance. Spec 3M.

Adhesive Families

Color coded to make cross referencing between charts easier.

100

100 High Temperature Acrylic

- Up to 450°F (232°C) short-term heat resistance and excellent solvent resistance
- High peel strength compared to other acrylic formulations
- Exceptional shear strength even at elevated temperatures
- Exhibits low outgassing characteristics

★ 100MP

100MP High Performance Acrylic

- Up to 500°F (260°C) short-term heat resistance and outstanding solvent resistance
- Higher peel strength than most other acrylic formulations
- Exceptional shear strength even at elevated temperatures

100HT

100HT Ultra High Temperature Acrylic

- Up to 550°F (288°C) short-term heat resistance and outstanding solvent resistance
- Higher peel strength than most other acrylic formulations
- Exceptional shear strength even at elevated temperatures

★ 200MP

200MP High Performance Acrylic

- Up to 400°F (204°C) short-term heat resistance and excellent solvent resistance
- Outstanding adhesion to metal and high surface energy plastics
- Excellent shear strength to resist slippage and edge lifting
- Short-term repositionability for placement accuracy

220

220 Industrial Acrylic

- Up to 350°F (177°C) short-term heat resistance and good chemical resistance
- Good shear strength and chemical resistance for general purpose industrial applications
- Good adhesion to most metal and high surface energy plastics

290

290 Low Outgassing Acrylic

- Up to 450°F (232°C) short-term heat resistance
- Exceeds most OEM specifications for outgassing and long-term performance
- High peel strength compared to other acrylic formulations
- Exceptional shear strength even at elevated temperatures

300

300 High Strength Acrylic

- Up to 250°F (121°C) short-term heat resistance
- High initial adhesion especially to low surface energy plastics
- Quick flowing to speed lamination of textured plastics, foams, fabrics and coated papers

300FR

300FR Flame Retardant

- Meets various flame retardancy standards such as UL94 V-2, F.A.R. 25.853, and FMVSS 302
- Similar adhesive properties to adhesive 300 family
- Good adhesion to a wide variety of surfaces including LSE plastics, foams and fabrics

★ 300LSE

300LSE Low Surface Energy Acrylic

- Up to 300°F (149°C) short-term heat resistance
- Outstanding adhesion to low surface energy plastics, powder coated paints and lightly oiled metals
- Good chemical and humidity resistance

★ 300MP+

300MP+ High-tack Acrylic

- Designed especially to bond most plastics, fabrics and foams

300SF

300SF Solventless

- Excellent initial adhesion
- Ideal for use on coated papers and other smooth surface materials
- Manufactured using a solventless adhesive coating process

320AF

320AF Acid Free

- Provides a consistently strong bond across a range of temperatures up to 180°F (82°C)
- PH balance between 7.0 and 8.5 so it will not discolor and damage papers, photographs and other acid sensitive materials

340

340 High-tack Acrylic

- Up to 180°F (82°C) short-term heat resistance
- Good bonding to foam and other substrates
- High-tack adhesive
- Medium shear strength

350

350 High Performance Acrylic

- Up to 450°F (232°C) short-term heat resistance
- Excellent solvent resistance and adhesion to LSE materials

★ Go-To Product

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

360

360 Acrylic Adhesive

- Up to 250°F (121°C) short-term heat resistance
- Outstanding adhesion to polypropylene and LSE plastics as well as HSE materials
- Very quick bonding dwell time to achieve full adhesion level

375

375 High Performance Double Coated

- Up to 300°F (149°C) short-term heat resistance
- Good adhesion to both high and low surface energy substrates
- Excellent initial tack

400

400 Acrylic Adhesive

- Up to 250°F (121°C) short-term heat resistance
- Good low temperature performance and peel strength on many surfaces
- Excellent adhesion to uncoated papers
- Clarity and UV resistance for window label applications

700 Series

700 Series Synthetic Rubber

- Up to 200°F (93°C) short-term heat resistance
- Good adhesion to low surface energy substrates
- For indoor and room temperature applications

800 Series

800 Series Natural Rubber

- Up to 200°F (93°C) short-term heat resistance
- Offers good adhesion to a variety of surfaces
- For indoor and room temperature applications

900R

900R Miscellaneous Rubber Adhesive Group

- Excellent initial adhesion and high bond to a variety of foams
- Utility rubber-based adhesive ideal for the foam fabricating industry

1000 Series

1000 Series Repositionable Acrylic

- Good holding to many surfaces
- Clean removal

2000MP

2000MP Optically Clear Acrylic

- Visual accuracy — light transmission > 99%, free of birefringence, refractive index of 1.47
- High cohesive and peel strengths
- High temperature, humidity and UV light resistance
- Long-term durability without yellowing, delaminating or degrading

Electric

Electrically Conductive

- Good initial tack, non-corrosive adhesive
- Built-in conductive tape
- Helps reinforce tape
- Low electrical resistance with good conductivity

Low VOC

Low VOC Acrylic

- Low emission adhesives that meet indoor air quality standards for automotive and construction markets
- Low odor

Vinyl

Plasticizer Resistant

- Bonds to many flexible vinyls
- Outstanding resistance to effects of plasticizer migration

Screen Print

Screen Printable Adhesive

- For selective placement of pressure sensitive adhesive using screen print technology
- Available as UV curable or water based

Silicone

Silicone Adhesive

- Up to 500°F (260°C) short-term heat resistance
- Outstanding solvent resistance
- Adheres to silicone without priming

Thermal

Thermally Conductive

- High-performance acrylic adhesive with highly conductive ceramic particles
- For an extremely reliable thermal interface
- Highly conformable

Other

Other Adhesive Family

- Newly developed or specialty adhesives that do not fit in the current adhesive family definitions

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Double Sided Tapes Selection Guide Based on Surface Energy


These charts are based on relative adhesion within each given surface energy category.

Metals	Surface Energy (Dynes/cm)
Copper	1103
Aluminum	840
Zinc	753
Tin	526
Lead	543


High Surface Energy (HSE) Plastics	Surface Energy (Dynes/cm)
Polyimide	50
Phenolic	47
Nylon®	46
Alkyd Enamel	45
Polyester	43
Epoxy Paint	43
Polyurethane	43
ABS	42
Polycarbonate	42
PVC	39
Modified PPE Resin	38
Acrylic	38

Low Surface Energy (LSE) Plastics	Surface Energy (Dynes/cm)
PVA	37
Polystyrene	36
Acetal	36
EVA	33
Polyethylene	31
Polypropylene	29
PVF	28
PTFE	18
Powder Coatings	Broad Range


Adhesive Performance on Metals



Adhesive Performance on High Surface Energy (HSE) Plastics



Adhesive Performance on Low Surface Energy (LSE) Plastics







Rankings are a general guide. Adhesives should be tested with actual components to ensure acceptable performance.

★ Go-To Product

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

Adhesive Properties

Adhesive Family	Adhesive Properties				Adhesion to:			Environmental Performance				Temperature °F (°C)		
	Peel		Shear					Chemical	Ultra Violet	Plasticizers	Humidity	Minimum Application	Service Low'	Service High'
	Initial	Ultimate	Room Temp.	150°F	Metal	HSE Plastic	LSE Plastic							
Acrylic Adhesives														
100	3	9	10	10	9	8	1	9	10	5	10	50 (10)	-40 (-40)	450 (232)
100MP 	4	10	10	10	10	7	1	10	10	5	10	50 (10)	-40 (-40)	500 (260)
100HT	4	10	10	10	10	7	1	10	10	5	10	50 (10)	-40 (-40)	550 (288)
200MP 	4	10	10	10	10	9	1	9	10	5	10	50 (10)	-40 (-40)	400 (204)
220	4	8	10	9	8	7	1	8	10	4	8	50 (10)	-40 (-40)	350 (177)
290	3	9	10	10	9	8	1	9	10	5	10	50 (10)	-40 (-40)	350 (177)
300	6	7	4	1	7	8	9	6	7	3	8	50 (10)	-40 (-40)	250 (121)
300FR	6	7	4	1	8	9	9	6	7	3	8	50 (10)	-40 (-40)	250 (121)
300LSE 	7	9	8	8	9	9	10	8	7	4	9	50 (10)	-40 (-40)	300 (149)
300MP+ 	6	7	5	5	7	7	4	—	—	—	9	50 (10)	-40 (-40)	—
300SF	6	7	4	1	7	8	9	6	7	3	8	50 (10)	-40 (-40)	350 (177)
320AF	7	7	4	1	7	7	7	6	6	3	8	50 (10)	-40 (-40)	250 (121)
340	6	7	6	5	6	6	5	7	7	4	9	50 (10)	-40 (-40)	180 (82)
350	7	9	8	8	9	10	10	8	7	4	9	50 (10)	-40 (-40)	450 (232)
360	10	10	8	5	10	10	10	8	7	4	8	50 (10)	-40 (-40)	250 (121)
375	6	8	8	8	8	8	6	7	7	5	8	50 (10)	-10 (-23)	300 (149)*
400	4	5	5	4	5	5	5	5	10	4	8	50 (10)	-60 (-51)	250 (121)
Rubber Adhesives														
700 Series	7	9	10	2	8	9	9	2	4	1	9	50 (10)	-40 (-40)	200 (93)
800 Series	9	10	6	2	8	8	8	1	1	1	1	50 (10)	-40 (-40)	180 (82)
900R	10	10	5	4	10	9	9	4	4	3	1	50 (10)	-40 (-40)	200 (93)
Other Adhesives														
1000 Series	2	3	3	3	3	1	1	2	7	3	4	50 (10)	-20 (-29)	250 (121)
2000MP Series	4	6	6	5	9	5	4	7	10	5	10	50 (10)	-40 (-40)	350 (177)
Electric	3	5	5	4	5	5	4	7	7	5	10	50 (10)	-20 (-29)	160 (71)
Low VOC (Acrylic)	7	10	8	7	9	8	8	8	8	5	10	50 (10)	-40 (-40)	350 (177)
Vinyls	4	6	5	5	10	10	7	5	7	10	10	50 (10)	-40 (-40)	250 (121)
Screen Printable	5	6	6	5	7	7	7	5	6	4	5	50 (10)	-40 (-40)	300 (149)
Silicone	4	5	10	8	9	8	7	10	10	3	10	40 (4)	-60 (-51)	500 (260)
Thermally Conductive	3	5	5	4	8	6	4	7	7	5	10	50 (10)	20 (-6.7)	185 (85)

*Reflects lowest service temperature that bond holds and highest temperature for short periods (minutes, hours).

*Service temperature dependent on carrier. See technical data page for further information.

Values: 1 = Lowest Performance; 10 = Highest Performance

Rankings are a general guide. Adhesives should be tested with actual components to ensure acceptable performance.

Go-To Product

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

Liner Reference Chart

3M offers paper and film release liners in a number of different constructions and weights to meet various process requirements.

Paper liners include densified kraft (DK) to reduce the edge burr on metal plates and for rotary processing, Extended DK liners (XL) and polycoated kraft (PCK) for moisture stability to resist wrinkling and curling are also available on selected tapes.


Film liners add strength in high-speed processing and dispensing and are available for clean room processing. They also offer high clarity for graphic inspection.

Product Group	Basis Weight	Caliper mils	Liner Type	Description	High Tensile Strength	Humidity Resistance	Rotary Processing	Kiss Cutting	Steel Rule
Paper Liners	43#	2.5	Densified Kraft (DK)	Silicone treated on one side for use as a second liner to protect adhesive during selective die-cutting. Printable.			■		
	55#	3.2	Densified Kraft (DK)	Caliper-controlled hard liner for consistent base in rotary printing and die-cutting of labels.			■	■	■
	60#	3.5	Densified Kraft (DK)	Hard dense liner reduces edge burr in hand tool processing of metal plates.			■	■	■
	62#	3.7	Densified Kraft (DK)	Heavier version of 60#.			■	■	■
	58#	3.0	Glassine	Hard dense liner that is resistant to water and oils.	■	■	■	■	■
	60#	3.2	Glassine	Hard dense liner that is resistant to water and oils.	■	■	■	■	■
	58#	4.2	Polycoated Kraft (PCK)	Moisture stable. Flat-bed die-cutting.		■			■
	58#	4.2	Polycoated Kraft (PCK) Lay-flat	Excellent moisture stability for lay-flat processing.		■	■		■
	78#	5.7	Polycoated Kraft (PCK)	Extra tough liner for tear resistance. Conformable for EMI/RFI shielding applications. Moisture stable. Flat-bed die-cutting.	■	■		■	■
	78#	6.0	Extensible Polycoated Kraft (EK)	Extra tough liner for tear resistance. Conformable for EMI/RFI shielding applications.	■	■		■	■
	83#	6.2	Polycoated Kraft (PCK)	Excellent moisture stability for lay-flat processing. Thicker caliper for kiss-cutting and steel rule die-cutting.		■		■	■
Film Liners	—	2.0	Clear Polyester (PET)	High strength reduces breakage during die-cutting and dispensing.	■	■	■	■	■
	—	3.0	Clear Polyester (PET)	High strength reduces breakage during die-cutting and dispensing.	■	■	■	■	■
	—	3.0	Clear High Density Polyethylene (HDPE)	Silicone treated for easy release. Clarity for see-through applications.	■	■			■

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Secondary Release Liners

Product Group	Product	Description/Application Ideas	Construction		Master Size	Printable
			Caliper (mils)	Liner		
Silicone Liners	4988	Neutral-colored, polycoated liner. Release coat one side.	6.4	83# Polycoated Kraft, Neutral Color	48" width – length can vary	Yes
	4994	Caliper-controlled liner for rotary die-cutting. Release coated two sides.	3.2	55# Densified Kraft, White	54" width – length can vary	No
	4996	Clear film is ideal for graphics inspection of backlit panels. Release coat one side.	1.4	Polyester Film, Clear	54" width – length can vary	Yes
	4997	Heavy liner ideal for kiss-cutting and lay-flat applications. Release coat one side.	4.0	70# Flatstock, Clear	48" width – length can vary	No
	4998	Release coat two sides (matte).	4.2	58# Polycoated Kraft, Tan	60" width – length can vary	No
	4999	Caliper controlled liner for rotary die-cutting. Release coat one side.	3.2	55# Densified Kraft, White	54" width – length can vary	Yes
	5002	Clear polyester film for rotary cutting. Release coat one side.	2.0	Polyester Film, Clear	60" width – length can vary	No
	5002D	Clear polyester film for rotary cutting. Release coat two sides.	2.0	Polyester Film, Clear	54" x 360 yd	No
	5051	Special PCK liner for double lining. Release coat one side.	4.2	58# Polycoated Kraft	48" width – length can vary	Yes



Preventing premature adhering.
3M™ Release Liners deliver a flexible solution for a wide range of applications and adhesive products.

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Adhesive Transfer Tapes

Adhesive Family ¹	Product	Description/Application Ideas	Adhesive Caliper (mils)	Liner ²		Master Size*	Specs	Adhesion				Chemical Resistance	Temperature	
				Type	Caliper (mils)			Metal	HSE Plastic	LSE Plastic	Foam		Low °F (°C)	High °F (°C)
100 High Temperature Acrylic	941	Graphic attachment for low odor appliance applications.	2	58# PCK	4.2	48" x 180 yd	UL	9	8	1	2	9	-40 (-40)	450 (232)
	965	Fuel and hydraulic line labels. Excellent chemical resistance. Aerospace.	2	55# DK	3.2	48" x 180 yd	—	9	8	1	2	9	-40 (-40)	450 (232)
	966	Meets NASA guidelines for low outgassing material for spacecraft. Flex circuit attachment. High temp.	2	62# DK	3.5	48" x 180 yd	UL MH	9	8	1	2	9	-40 (-40)	450 (232)
	966FL	Meets NASA guidelines for low outgassing material for spacecraft. Flex circuit attachment. Static dissipative PET liner.	2	PET	3.0	48" x 180 yd	UL MH	9	8	1	2	9	-40 (-40)	450 (232)
	9461P	Thinner version of laminating adhesive 9462P.	1	55# DK	3.2	48" x 360 yd	—	9	8	1	2	9	-40 (-40)	450 (232)
	9462P	Laminating adhesive 966 on a caliper-controlled liner for rotary die-cutting.	2	55# DK	3.2	48" x 360 yd	UL	9	8	1	2	9	-40 (-40)	450 (232)
100MP High Performance Acrylic³	F9460PC	High-performance industrial joining and metal fabrication.	2	58# PCK	4.2	60" x 180 yd	UL MH	10	7	1	2	10	-40 (-40)	500 (260)
	F9469PC	High-performance industrial joining and metal fabrication.	5	58# PCK	4.2	60" x 180 yd	UL MH	10	7	1	2	10	-40 (-40)	500 (260)
	F9473PC	High-performance industrial joining and metal fabrication.	10	58# PCK	4.2	60" x 180 yd	UL MH	10	7	1	2	10	-40 (-40)	500 (260)
100HT Ultra High Temperature Acrylic	9082	Excellent heat resistance in high temp environments. For applications that require both higher processing and operating temperatures.	2	White DK Liner	3.2	48" x 180 yd	UL	10	7	1	2	10	-40 (-40)	550 (288)
	9085	Thicker version of 9082.	5	White DK Liner	3.2	48" x 180 yd	—	10	7	1	2	10	-40 (-40)	550 (288)
	9085UV	Same as 9085 but with UV light detectable adhesive.	5	58# PCK	4.2	48" x 360 yd	—	10	7	1	2	10	-40 (-40)	550 (288)
200MP High Performance Acrylic	467MC	Same as 467MP with a paper MicroChannel liner to aid in bubble- and wrinkle-free graphic attachment.	2	58# PCK	4.2	54" x 180 yd	UL	10	9	1	3	9	-40 (-40)	400 (204)
	467MP	Graphic attachment and general industrial joining. Industry standard.	2	58# PCK	4.2	60" x 600 yd	UL MH	10	9	1	3	9	-40 (-40)	400 (204)
	467MPF	Polyester liner for rotary processing of graphic and die cut parts.	2	PET	2.0	54" x 180 yd	UL	10	9	1	3	9	-40 (-40)	400 (204)
	468MC	Same as 468MP with a paper MicroChannel liner to aid in bubble- and wrinkle-free graphic attachment.	5	58# PCK	4.0	54" x 180 yd	—	10	9	1	3	9	-40 (-40)	400 (204)
	468MP	Industry standard for graphic attachment and die cut parts.	5	58# PCK	4.2	60" x 600 yd	UL MH	10	9	1	3	9	-40 (-40)	400 (204)
	468MPF	Thicker version of 467MPF.	5	PET	2.0	54" x 180 yd	UL	10	9	1	3	9	-40 (-40)	400 (204)
	9667MP	Same as 467MP on heavy, lay-flat liner for kiss-cutting.	2	78# PCK	5.7	54" x 180 yd	UL	10	9	1	3	9	-40 (-40)	400 (204)
	9668MP	Same as 468MP on heavy, lay-flat liner.	5	78# PCK	5.7	54" x 360 yd	UL MH	10	9	1	3	9	-40 (-40)	400 (204)

1. More information on pages 10–13. 2. More information on page 14. 3. Products in this platform are 3M™ VHB™ Tapes offering our highest strength.

M^H meets Mil-P-19834B Type I.

*Select products have multiple master sizes.

Values: 1 = Lowest Performance; 10 = Highest Performance

Rankings are a general guide. Adhesives should be tested with actual components to ensure acceptable performance.

★ Go-To Product

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Adhesive Transfer Tapes (cont.)

Adhesive Family ¹	Product	Description/Application Ideas	Adhesive Caliper (mils)	Liner ²		Master Size*	Specs	Adhesion				Chemical Resistance	Temperature	
				Type	Caliper (mils)			Metal	HSE Plastic	LSE Plastic	Foam		Low °F (°C)	High °F (°C)
220 Industrial Acrylic	9502	Economical attachment of graphics and industrial joining.	2	58# PCK	4.2	60" x 360 yd	UL	8	7	1	2	8	-40 (-40)	350 (177)
	9505	Thicker version of 9502 for textured surfaces.	5	58# PCK	4.2	60" x 360 yd	UL	8	7	1	2	8	-40 (-40)	350 (177)
290 Low Outgassing Acrylic	501FL	Ultra-clean adhesive for low outgassing applications.	1	PET	2.0	23.5" x 180 yd	—	9	7	1	2	9	-40 (-40)	450 (232)
	502FL	Ultra-clean adhesive for low outgassing applications.	2	PET	2.0	23.5" x 180 yd	—	9	7	1	2	9	-40 (-40)	450 (232)
300 High Strength Acrylic	927	Attach gaskets and a variety of industrial foam and LSE materials.	2	60# DK	3.5	48" x 180 yd	—	7	9	9	9	6	-40 (-40)	250 (121)
	950	Thicker version of 927.	5	58# Glassine	3.2	48" x 180 yd	UL	7	9	9	9	6	-40 (-40)	250 (121)
	950EK	950 with Extensible Kraft liner.	5	78# EK	5.7	48" x 180 yd	—	7	9	9	9	6	-40 (-40)	250 (121)
	9458	Thin, high-tack adhesive for rotary processing HSE and LSE parts.	1	55# DK	3.2	54" x 360 yd	UL	7	9	9	9	6	-40 (-40)	250 (121)
	9459W	White adhesive version of laminating adhesive.	1.5	55# DK	3.2	48" x 360 yd	UL	7	9	9	9	6	-40 (-40)	250 (121)
	9471	For smooth LSE plastics.	2	60# DK	3.5	48" x 180 yd	UL MH	7	9	9	9	6	-40 (-40)	250 (121)
	9472	5.0 mil version of 9471. For textured surfaces.	5	60# DK	3.5	48" x 180 yd	UL MH	7	9	9	9	6	-40 (-40)	250 (121)
	9671	Heavier lined version of 9471 for easy handling, lay-flat properties.	2	83# PCK	6.2	48" x 180 yd	UL MH	7	9	9	9	6	-40 (-40)	250 (121)
	9672	Heavier lined version of 9472 for easy handling, lay-flat properties.	5	83# PCK	6.2	48" x 180 yd	UL	7	9	9	9	6	-40 (-40)	250 (121)
	300FR Flame Retardant	9372W	Flame retardant transfer tape with moisture stable liner.	2	83# PCK	6.2	48" x 360 yd	—	8	9	9	9	6	-40 (-40)
9372DKW		Flame retardant transfer tape with rotary die-cuttable liner.	2	55# DK	3.2	48" x 180 yd	—	8	9	9	9	6	-40 (-40)	250 (121)
9375W		Flame retardant transfer tape with moisture stable liner.	5	83# PCK	6.2	48" x 180 yd	UL	8	9	9	9	6	-40 (-40)	250 (121)
300SF Solvent Free	XT2105	Attach coated papers and plastics in printing and graphic applications.	2	55# DK	3.2	48" x 60 yd	—	6	9	9	4	5	-40 (-40)	200 (93)
	XT2112	Perfect for plastics assembly and for attaching heavy paperboards and corrugated in P.O.P. and packaging applications.	5	55# DK	3.2	48" x 60 yd	—	6	9	9	4	5	-40 (-40)	200 (93)


1. More information on pages 10–13. 2. More information on page 14.

M^H meets Mil-P-19834B Type I.

*Select products have multiple master sizes.

Values: 1 = Lowest Performance; 10 = Highest Performance



Rankings are a general guide. Adhesives should be tested with actual components to ensure acceptable performance.



Made for easy handling. Adhesive Transfer Tape (ATT or unsupported tape) is composed of a thin film of adhesive with a liner over the top so it can be easily handled.

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Adhesive Transfer Tapes (cont.)

Adhesive Family ¹	Product	Description/Application Ideas	Adhesive Caliper (mils)	Liner ²		Master Size*	Specs	Adhesion				Chemical Resistance	Temperature	
				Type	Caliper (mils)			Metal	HSE Plastic	LSE Plastic	Foam		Low °F (°C)	High °F (°C)
 300LSE Low Surface Energy Acrylic	9453FL	Film lined version of 9453LE for rotary processing.	3.5	PET	2.0	54" x 180 yd	UL	9	9	10	8	8	-40 (-40)	300 (149)
	9453LE	A 3.5 mil version of 9471LE for application to rough surfaces.	3.5	58# PCK	4.2	54" x 180 yd	UL	9	9	10	8	8	-40 (-40)	300 (149)
	9471FL	Film lined version of 9471LE for rotary processing.	2	PET	2.0	54" x 180 yd	UL	9	9	10	8	8	-40 (-40)	300 (149)
	9471LE	Bonds graphics to powder coatings, LSE plastics and oily materials.	2	58# PCK	4.2	54" x 180 yd	UL	9	9	10	8	8	-40 (-40)	300 (149)
	9472FL	A 5 mil version of 9471LE with film liner for textured surfaces.	5	PET	2.0	54" x 180 yd	UL	9	9	10	8	8	-40 (-40)	300 (149)
	9472LE	Thicker adhesive for textured LSE plastics and powder coatings.	5	58# PCK	4.2	54" x 180 yd	UL	9	9	10	8	8	-40 (-40)	300 (149)
	9653LE	Heavy lined 9453LE for easy handling and lay-flat properties.	3.5	83# PCK	6.2	54" x 180 yd	UL	9	9	10	8	8	-40 (-40)	300 (149)
	9671LE	Heavy lined 9471LE for easy handling and lay-flat properties.	2	83# PCK	6.2	54" x 180 yd	UL	9	9	10	8	8	-40 (-40)	300 (149)
	9672LE	Heavy lined 9472LE for easy handling and lay-flat properties.	5	83# PCK	6.2	54" x 360 yd	UL	9	9	10	8	8	-40 (-40)	300 (149)
 300MP+ High-tack Acrylic	9772WL+	Provides excellent bond to various fabricated foams, fabrics and substrates.	2	96# PCK	7.0	60" x 360 yd	—	7	7	4	9	—	-40 (-40)	—
	9773WL+	Provides excellent bond to various fabricated foams, fabrics and substrates.	3	96# PCK	7.0	60" x 360 yd	—	7	7	4	9	—	-40 (-40)	—
	9774WL+	Provides excellent bond to various fabricated foams, fabrics and substrates.	4	96# PCK	7.0	60" x 360 yd	—	7	7	4	9	—	-40 (-40)	—
	9775WL+	Provides excellent bond to various fabricated foams, fabrics and substrates.	5	96# PCK	7.0	60" x 360 yd	—	7	7	4	9	—	-40 (-40)	—
350 High Performance Acrylic	9442	Excellent temperature and solvent resistance. High bond to low surface energy substrates.	2	55# DK	3.2	48" x 180 yd	UL	9	10	10	9	8	-40 (-40)	450 (232)
	9445	Thicker version of 9442.	5	55# DK	3.2	48" x 180 yd	UL	9	10	10	9	8	-40 (-40)	450 (232)
	9482PC	High-tack and shear strength. Excellent adhesion to plastics and foams.	2	58# PCK	4.2	48" x 180 yd	UL	9	10	10	9	8	-40 (-40)	450 (232)
	9485EK	Thicker version of 9482PC with an Extensible Kraft liner.	5	78# EK	5.7	48" x 180 yd	UL	9	10	10	9	8	-40 (-40)	450 (232)
	9485PC	A 5 mil version of 9482PC.	5	58# PCK	4.2	48" x 180 yd	UL	9	10	10	9	8	-40 (-40)	450 (232)
	9675	Heavy lined version of 9485PC for easy handling, lay-flat properties.	5	83# PCK	6.2	48" x 180 yd	UL	9	10	10	9	8	-40 (-40)	450 (232)

1. More information on pages 10–13. 2. More information on page 14.

*Select products have multiple master sizes.

Values: 1 = Lowest Performance; 10 = Highest Performance

Rankings are a general guide. Adhesives should be tested with actual components to ensure acceptable performance.

Go-To Product

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Adhesive Transfer Tapes (cont.)

Adhesive Family ¹	Product	Description/Application Ideas	Adhesive Caliper (mils)	Liner ²		Master Size*	Specs	Adhesion				Chemical Resistance	Temperature	
				Type	Caliper (mils)			Metal	HSE Plastic	LSE Plastic	Foam		Low °F (°C)	High °F (°C)
360 Acrylic Adhesive	9626	Quick stick with high bond strength. Designed for use with 3M™ Label Component Systems.	2	Glassine	3.2	54" x 540 yd	—	10	10	10	9	8	-40 (-40)	250 (121)
	9627	Quick stick with high bond strength. Designed for use with 3M™ Label Component Systems.	5	Glassine	3.2	54" x 180 yd	—	10	10	10	9	8	-40 (-40)	250 (121)
400 Acrylic Adhesive	463	High-tack and excellent adhesion to most paper stocks. For automatic dispensing.	2	58# Glassine	3.5	48" x 180 yd	—	5	5	5	4	5	-60 (-51)	250 (121)
	465	Same as 463, but with easy liner release for manual or hand application.	2	60# DK	3.5	48" x 180 yd	—	5	5	5	4	5	-60 (-51)	250 (121)
	9457	Adhesive with long-term stability, excellent outdoor performance and UV resistance. Adhesive 400 is best if necessary to apply at cooler temperatures.	1	55# DK	3.2	54" x 360 yd	UL	5	5	5	4	5	-60 (-51)	250 (121)
Vinyl	F9465PC	Vinyl plasticizer resistant adhesive.	5	58# PCK	4.2	54" x 360 yd	—	10	10	7	5	5	-40 (-40)	200 (93)
	F9467U	Vinyl plasticizer resistant adhesive.	3.5	58# PCK	4.2	54" x 180 yd	—	10	10	7	5	5	-40 (-40)	200 (93)
Other	97053	Micro scrim reinforced adhesive transfer tape has excellent quick stick for permanent bond applications on plastics, metals, non-wovens, felts and foams.	2.5	50# DK	3.0	60" x 720 yd	—	6	6	5	5	5	-40 (-40)	175 (79)

1. More information on pages 10–13. 2. More information on page 14.

M^H meets Mil-P-19834B Type I.

*Select products have multiple master sizes.

Values: 1 = Lowest Performance; 10 = Highest Performance

Rankings are a general guide. Adhesives should be tested with actual components to ensure acceptable performance.



Attach upholstery material to high-density foam.

Keep materials together under the hardest conditions with 3M™ Double Coated Tape 99786+ with Adhesive 300MP+.





Attach glass to metal.

Hold securely for a clean finish with 3M™ Adhesive Transfer Tape 468MP with Adhesive 200MP.

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Double Lined Adhesive Transfer Tapes

Adhesive Family ¹	Product	Description/Application Ideas	Adhesive Caliper (mils)	Liner ²		Master Size	Specs	Adhesion				Chemical Resistance	Temperature	
				Type	Caliper (mils)			Metal	HSE Plastic	LSE Plastic	Foam		Low °F (°C)	High °F (°C)
 200MP High Performance Acrylic	7952MP	Double lined laminating adhesive 467MP.	2	58# PCK	4.2	48" x 360 yd	UL	10	9	1	3	9	-40 (-40)	400 (204)
				58# PCK	4.2	48" x 36"	UL	10	9	1	3	9	-40 (-40)	400 (204)
	7955MP	Double lined laminating adhesive 468MP. For selective die-cutting.	5	58# PCK	4.2	48" x 360 yd	UL	10	9	1	3	9	-40 (-40)	400 (204)
				58# PCK	4.2	48" x 36"	UL	10	9	1	3	9	-40 (-40)	400 (204)
	7962MP	Laminating adhesive 7952MP on a lay-flat liner for kiss-cutting and selective die-cutting.	2	78# PCK	5.7	48" x 360 yd	UL	10	9	1	3	9	-40 (-40)	400 (204)
				58# PCK	4.2	48" x 36"	UL	10	9	1	3	9	-40 (-40)	400 (204)
7965MP	Laminating adhesive 7955MP on a lay-flat liner for kiss-cutting and selective die-cutting.	5	78# PCK	5.7	48" x 360 yd	UL	10	9	1	3	9	-40 (-40)	400 (204)	
			58# PCK	4.2	48" x 36"	UL	10	9	1	3	9	-40 (-40)	400 (204)	
220 Industrial Acrylic	9552	Economical attachment of graphics and industrial joining. Double lined version of 9502.	2.3	58# PCK	4.2	48" x 360 yd	UL	8	7	1	2	8	-40 (-40)	350 (177)
	9555	Thicker version of 9552 for textured surfaces. Double lined version of 9505.	4.9	58# PCK	4.2	48" x 360 yd	UL	8	7	1	2	8	-40 (-40)	350 (177)
 300LSE Low Surface Energy Acrylic	8132LE	Double lined laminating adhesive 9471LE. For selective die-cutting. Application to smooth surfaces.	2	58# PCK	4.2	48" x 360 yd	UL	9	10	10	8	8	-40 (-40)	300 (149)
				83# PCK	6.2	48" x 36"	UL	9	10	10	8	8	-40 (-40)	300 (149)
	8153LE	Double lined laminating adhesive 9453LE. For selective die-cutting. Application to rough surfaces.	3.5	58# PCK	4.2	48" x 360 yd	UL	9	10	10	8	8	-40 (-40)	300 (149)
				83# PCK	6.2	48" x 36"	UL	9	10	10	8	8	-40 (-40)	300 (149)

1. More information on pages 10–13. 2. More information on page 14.

Values: 1 = Lowest Performance; 10 = Highest Performance

Rankings are a general guide. Adhesives should be tested with actual components to ensure acceptable performance.



Double lined adhesive transfer tapes are excellent for selective die-cutting applications.

Go-To Product

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Double Lined Adhesive Transfer Tapes (cont.)

Adhesive Family ¹	Product	Description/Application Ideas	Adhesive Caliper (mils)	Liner ²		Master Size	Specs	Adhesion				Chemical Resistance	Temperature	
				Type	Caliper (mils)			Metal	HSE Plastic	LSE Plastic	Foam		Low °F (°C)	High °F (°C)
2000MP Optically Clear Acrylic ³	8211	General purpose, high adhesion optically clear adhesive.	1	PET/PET	2.0/2.0	60" x 180 yd	—	7	9	—	—	9	-40 (-40)	350 (177)
	8212	General purpose, high adhesion optically clear adhesive.	2	PET/PET	2.0/2.0	60" x 180 yd	—	7	9	—	—	9	-40 (-40)	350 (177)
	8213	General purpose, high adhesion optically clear adhesive.	3	PET/PET	2.0/2.0	60" x 180 yd	—	7	9	—	—	9	-40 (-40)	350 (177)
	8214	General purpose, high adhesion optically clear adhesive.	4	PET/PET	2.0/2.0	60" x 180 yd	—	7	9	—	—	9	-40 (-40)	350 (177)
	8215	General purpose, high adhesion optically clear adhesive.	5	PET/PET	2.0/2.0	60" x 180 yd	—	7	9	—	—	9	-40 (-40)	350 (177)
	8142KCL	Very soft, optically clear adhesive.	2	PET/PET	3.0/3.0	60" x 180 yd	—	—	5	—	—	6	-40 (-40)	185 (85)
	8171PCL	UV blocking, optically clear adhesive.	1	PET/PET	2.0/2.0	60" x 180 yd	—	—	4	—	—	6	-40 (-40)	185 (85)
	9483	Optically clear adhesive.	5	PET/PP	3.0/3.0	48" x 180 yd	—	9	9	—	—	9	-40 (-40)	350 (177)

1. More information on pages 10–13. 2. More information on page 14.

3. All optically clear adhesives can be manufactured in a single coated or double coated tape format upon special request.

Values: 1 = Lowest Performance; 10 = Highest Performance

Rankings are a general guide. Adhesives should be tested with actual components to ensure acceptable performance.

3M™ Double Coated Tape


The ideal general purpose industrial thin bond tape for use in many markets including consumer appliances, industrial machinery, transportation, signage, general industrial and consumer electronics. Bonds to many high surface energy substrates and some low surface energy substrates, including: stainless steel, HDPE, ABS, acrylic, PP, polycarbonate, aluminum and glass.

Product	Adhesive Type	Carrier Type (Thickness)	Liner Type (Thickness)	Total Tape Thickness w/o Liner	Short-Term Temperature Performance	Long-Term Temperature Performance	Color
GPT-020	Solventless Acrylic	PET 0.5 mils (12 micron)	White PCK 4 mils (100 micron)	8 mils (200 micron)	375°F (190°C)	195°F (90°C)	Transparent
GPT-020F	Solventless Acrylic	PET 0.5 mils (12 micron)	White PP 4 mils (100 micron)	8 mils (200 micron)	375°F (190°C)	195°F (90°C)	Transparent



Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Double Coated Tapes



Bond foam to plastic.

Bond curved plastic pieces to foam or plastic with 3M™ Double Coated Tape 93015LE with Adhesive 300LSE.

Adhesive Family ¹	Product	Description/Application Ideas	Tape Cal. (mils)	Carrier Type	Liner ²			Specs	Adhesion				Chemical Resistance	Temperature	
					Type	Caliper (mils)	Master Size*		Metal	HSE Plastic	LSE Plastic	Foam		Low °F (°C)	High °F (°C)
★ 200MP High Performance Acrylic	92015	Double coat with thin polyester film carrier for dimensional stability and improved handling.	5.9	PET	58# PCK	4.2	54" x 180 yd	UL	10	9	1	2	9	-40 (-40)	300 (149)
	9495B	Black version of 9495MP.	5.7	Black PET	58# PCK	4.2	54" x 180 yd	UL	10	9	1	2	9	-40 (-40)	300 (149)
	9495MP	Double coated film tapes feature a thin polyester film for dimensional stability and improved handling with ease of die cutting and laminating.	5.7	PET	58# PCK	4.2	54" x 180 yd	UL	10	9	1	2	9	-40 (-40)	300 (149)
★ 300LSE Low Surface Energy Acrylic	93005LE	Very thin double coated polyester tape with good anti-lifting properties.	2.0	PET	58# PCK/78# PCK	4.2/6.2	54" x 360 yd	UL	9	9	10	8	8	-40 (-40)	300 (149)
	93010LE	Double coated tape with a polyester film carrier for dimensional stability, improved handling and die cuttability.	3.9	PET	58# PCK	4.2	54" x 180 yd	UL	9	9	10	8	8	-40 (-40)	300 (149)
	93015LE	Double coated tape with a polyester film carrier for dimensional stability, improved handling and die cuttability.	5.9	PET	58# PCK	4.2	54" x 180 yd	UL	9	9	10	8	8	-40 (-40)	300 (149)
	93020LE	Double coated tape with a polyester film carrier for dimensional stability, improved handling and die cuttability.	7.9	PET	58# PCK	4.2	54" x 180 yd	UL	9	9	10	8	8	-40 (-40)	300 (149)
	9495LE	Double coated tape with a polyester film carrier for dimensional stability, improved handling and die cuttability.	6.7	PET	58# PCK	4.2	54" x 180 yd	UL	9	9	10	8	8	-40 (-40)	300 (149)
★ 300 High Strength Acrylic	444	Foam lamination. Gasket attachment.	3.9	PET	55# DK	3.2	48" x 108 yd	—	7	9	9	9	6	-40 (-40)	250 (121)
	444PC	Foam lamination. Gasket attachment.	3.9	PET	58# PCK	4.2	48" x 648 yd	—	7	9	9	9	6	-40 (-40)	250 (121)
	9009	Thin double coat for applications where thickness is critical.	2.1	PET	55# DK	3.2	54" x 180 yd	—	7	9	9	9	6	-40 (-40)	250 (121)
	9019	Ultra-thin double coat for applications where thickness is critical.	1.1	PET	55# DK	3.2	54" x 180 yd	—	7	9	9	9	6	-40 (-40)	250 (121)

1. More information on pages 10–13. 2. More information on page 14.

*Select products have multiple master sizes.

Values: 1 = Lowest Performance; 10 = Highest Performance

Rankings are a general guide. Adhesives should be tested with actual components to ensure acceptable performance.

★ Go-To Product

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Double Coated Tapes (cont.)

Adhesive Family ¹	Product	Description/Application Ideas	Tape Cal. (mils)	Carrier Type	Liner ²			Specs	Adhesion				Chemical Resistance	Temperature	
					Type	Caliper (mils)	Master Size*		Metal	HSE Plastic	LSE Plastic	Foam		Low °F (°C)	High °F (°C)
	9832+	General purpose tape with improved temperature resistance.	4.8	PET	58# PCK	4.2	54" x 250 yd	—	7	7	4	9	—	-40 (-40)	—
	9832HL+	Same as 9832+ except with a heavier liner.	4.8	PET	83# PCK	6.2	54" x 250 yd	—	7	7	4	9	—	-40 (-40)	—
	99786+	Thin non-woven carrier for dimensional stability and improved handling.	5.5	Non-Woven	58# PCK Printed	4.2	48" x 180 yd	—	7	7	4	9	—	-40 (-40)	—
	99786NP+	Same as 99786+ except on an unprinted liner.	5.5	Non-Woven	58# PCK Unprinted	4.2	54" x 180 yd	—	7	7	4	9	—	-40 (-40)	—
	9456	High-tack acrylic adhesive with good adhesion to many plastics.	5.0	Tissue	55# DK	3.2	54" x 180 yd	—	6	6	5	4	8	-40 (-40)	180 (82)
	9824	Foam lamination. Gasket attachment.	3.1	PET	55# DK	3.2	54" x 250 yd	—	6	6	5	4	8	-40 (-40)	180 (82)
	9828	Foam lamination. Gasket attachment.	4.0	PET	55# DK	3.2	54" x 250 yd	—	6	6	5	4	8	-40 (-40)	180 (82)
	9828PC	High-tack acrylic adhesive with good adhesion to many foams.	4.0	PET	74# PCK	5.6	54" x 250 yd	—	6	6	5	4	8	-40 (-40)	180 (82)
	9500PC	High performance with good chemical resistance.	5.6	PET	58# PCK	4.5	48" x 108 yd	—	9	10	10	9	8	-40 (-40)	350 (177)
	3028EK	Same as 9500PC with an Extensible Kraft liner which facilitates narrow slitting.	5.6	PET	77# EK	5.5	48" x 108 yd	—	9	10	10	9	8	-40 (-40)	350 (177)
	9628B	Outstanding quick stick and adhesion to polypropylene.	2.0	PET Black	60# Glassine	3.2	54" x 180 yd	—	10	10	10	6	8	-40 (-40)	250 (121)
	9628FL	Outstanding quick stick and adhesion to polypropylene.	2.0	PET Clear	PET Clear	2.0	54" x 180 yd	—	10	10	10	6	8	-40 (-40)	250 (121)
	9629B	Outstanding quick stick and adhesion to polypropylene.	4.0	PET Black	60# Glassine	3.2	54" x 180 yd	—	10	10	10	6	8	-40 (-40)	250 (121)
	9629FL	Outstanding quick stick and adhesion to polypropylene.	4.0	PET	PET Clear	2.0	54" x 540 yd	—	10	10	10	6	8	-40 (-40)	250 (121)
	9629PC	Outstanding quick stick and adhesion to polypropylene.	4.0	PET	58# PCK	4.2	54" x 540 yd	—	10	10	10	6	8	-40 (-40)	250 (121)
	9086	Easy tearing, easy handling.	7.5	Tissue	Glassine Black Logo	3.0	54" x 750 yd	—	8	8	6	3	7	-10 (-23)	250 (121)
	9087	Thick adhesive to bond rough surfaces.	10.2	PVC	Glassine Green Logo	3.0	54" x 750 yd	—	8	8	6	3	7	-10 (-23)	185 (85)
	415	Splice papers, films and foils.	4.0	PET	60# DK	4.0	48" x 504 yd	—	5	5	5	5	5	-60 (-51)	250 (121)

1. More information on pages 10–13. 2. More information on page 14.

*Select products have multiple master sizes.

Values: 1 = Lowest Performance; 10 = Highest Performance

Rankings are a general guide. Adhesives should be tested with actual components to ensure acceptable performance.

Go-To Product

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.


3M™ Double Coated Tapes (cont.)

Adhesive Family ¹	Product	Description/Application Ideas	Tape Cal. (mils)	Carrier Type	Liner ²		Master Size	Specs	Adhesion				Chemical Resistance	Temperature	
					Type	Caliper (mils)			Metal	HSE Plastic	LSE Plastic	Foam		Low °F (°C)	High °F (°C)
700 Synthetic Rubber	476	High-tack. Permanent	6.0	Film	62# DK	3.7	27" x 120 yd	—	8	9	9	3	2	-40 (-40)	150 (65)
	9443NP	High-tack rubber adhesive with good adhesion to most plastics.	6.0	HDPE	60# DK	3.7	27" x 120 yd	—	8	9	9	2	2	-40 (-40)	200 (93)
	9579	Core starting on metal cores.	9.0	HDPE	62# DK	3.7	27" x 144 yd	—	8	9	9	2	2	-40 (-40)	200 (93)
860 Natural Rubber	401M	Used for mounting rubber or photopolymer printing plates.	9.0	Paper	54# DK	3.0	23.5" x 72 yd	—	8	8	8	5	1	-40 (-40)	180 (82)
	410M	Core starting/end tabbing of papers, films and foils.	6.0	Paper	54# DK	3.0	23.5" x 108 yd	—	8	8	8	5	1	-40 (-40)	200 (93)
900R Synthetic Rubber	9816L	General purpose, high-tack, rubber-based adhesive.	3.5	PET	60# Kraft	3.5	54" x 250 yd	—	8	8	7	7	3	-40 (-40)	150 (65)
	9816M	General purpose, high-tack, rubber-based adhesive.	3.5	PET	74# Kraft	3.5	60" x 250 yd	—	8	8	7	7	3	-40 (-40)	150 (65)
Low VOC	9599	Acrylic adhesive for high adhesion to a variety of materials including metals and HSE plastics. Low-VOC properties suitable for interior automotive applications.	5.0	Non-Woven Tissue	PCK White	4.5	51" x 55 yd	—	9	8	8	4	7	-40 (-40)	275 (135)
	DCX 1018	Acrylic adhesive for high adhesion to a variety of materials including metals and HSE plastics. Low-VOC properties suitable for interior automotive applications.	5.0	Tissue	PCK White	4.2	51" x 55 yd	—	9	9	8	8	8	-40 (-40)	350 (177)

1. More information on pages 10–13. 2. More information on page 14.

Values: 1 = Lowest Performance; 10 = Highest Performance

Rankings are a general guide. Adhesives should be tested with actual components to ensure acceptable performance.



Attach closed-cell foam to galvanized steel.
3M™ Double Coated Tape 9832HL+.



Attach rubber to plastic.
3M™ Double Coated Tape 93015LE with Adhesive 300LSE.



Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Differential Double Coated Tapes³

Adhesive Family ¹	Product	Description/Application Ideas	Tape Cal. (mils)	Carrier Type	Liner ²		Master Size	Specs	Adhesion				Chemical Resistance	Temperature	
					Type	Caliper (mils)			Metal	HSE Plastic	LSE Plastic	Foam		Low °F (°C)	High °F (°C)
350/ Silicone Differential Adhesive	9731	Differential adhesive-silicone adhesive on back side. Silicone keypad attachment, printer toner cartridge refurbishing.	5.5	PET	58#PCK/ 3 mil PET	2.9/4.2	48" x 108 yd*	—	9	10	10	9	8	-40 (-40)	250 (121)
	9731-50	Differential adhesive-silicone adhesive on back side which provides adhesion to many difficult to bond to substrates including silicone rubbers and low surface energy plastics.	2.0	PET	58# PCK/ 2.9 mil PET	2.9/4.2	48" x 36 yd	—	9	10	10	9	8	-40 (-40)	250 (121)
	9731-100	Differential adhesive-silicone adhesive on back side which provides adhesion to many difficult to bond to substrates including silicone rubbers and low surface energy plastics.	4.0	PET	58# PCK/ 2.9 mil PET	2.9/4.2	48" x 36 yd	—	9	10	10	9	8	-40 (-40)	250 (121)
200MP/ 300LSE Differential Adhesive	9496LE	Adhesive 200MP provides excellent bond strength to a variety of high surface energy substrates. 300LSE bonds to powder coated metals, oily metals and LSE plastic.	6.7	PET	58#/58#	4.2/4.2	24" x 36"	—	10	9	1	3	9	-40 (-40)	250 (121)
		Adhesive 200MP provides excellent bond strength to a variety of high surface energy substrates. 300LSE bonds to powder coated metals, oily metals and LSE plastic.	6.7	PET	58#/58#	4.2/4.2	24" x 36"	—	9	10	10	1	7	-40 (-40)	250 (121)
Acrylic/ Rubber Differential Adhesive	9817M	Exposed side is acrylic, liner side is rubber-based. Excellent quick stick and adhesion to high and low energy surfaces.	3.3	PET	74# Kraft	3.5	60" x 250 yd*	—	8	8	7	6	3	-40 (-40)	175 (79)

1. More information on pages 10–13. 2. More information on page 14. 3. Second number reflects removable adhesive side.
*Select products have multiple master sizes.

Values: 1 = Lowest Performance; 10 = Highest Performance

Rankings are a general guide. Adhesives should be tested with actual components to ensure acceptable performance.

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.


3M™ Removable/Repositionable Tapes

Adhesive Family ¹	Product	Description/Application Ideas	Tape Cal. (mils)	Carrier Type	Liner ²		Master Size*	Specs	Adhesion				Chemical Resistance	Temperature	
					Type	Caliper (mils)			Metal	HSE Plastic	LSE Plastic	Foam		Low °F (°C)	High °F (°C)
400/1000 Differential Adhesive³	9415PC	High-tack/low tack differential adhesive. Polyester film carrier.	2	PET	77# EK	6.0	48" x 216 yd	—	5	5	5	4	5	-20 (-29)	150 (65)
	9416	High-tack/low tack differential adhesive. Tissue carrier.	2	Tissue	78# EK	5.6	47" x 432 yd	—	3	1	1	—	2	-20 (-29)	150 (65)
420/1050 Differential Adhesive³	9425	High-tack/medium tack for repositionable parts. Hot wire cuttable.	5.5	UPVC	58# PCK	4.2	48" x 144 yd	—	8/3	7/1	1	4/1	2	-20 (-29)	125 (52)
	9425HT	High-tack/medium tack acrylic adhesive offers permanent adhesion to one substrate with removability to the other.	5	PET	58# PCK	4.2	48" x 360 yd	—	8/3	7/1	1	4/1	2	-20 (-29)	250 (121)
400/1070 Repositionable Acrylic³	665	Medium tack/medium tack differential adhesive. Hot wire cuttable. Linerless.	3.5	UPVC	None	—	48" x 216 yd	—	5	5	5	4	5	-60 (-51)	125 (52)
	666	Linered version of 665.	3.5	UPVC	LDPE	4.0	48" x 108 yd	—	5	5	5	4	5	-60 (-51)	125 (52)
100 High Temp. Acrylic	4658F	Clear, closed foam acrylic foam tape. Initially repositionable, but will create permanent bond.	31.0	None	PET	2.0	48" x 162 yd	—	9	8	1	—	9	-40 (-40)	450 (232)
1000 Repositionable Acrylic	9449S	Low tack adhesive transfer tape laminates to various substrates to make them repositionable.	0.4	None	55# DK	2.5	48" x 360 yd	—	3	1	1	—	2	-20 (-29)	250 (121)

1. More information on pages 10–13. 2. More information on page 14. 3. Second number reflects removable adhesive side.
*Select products have multiple master sizes.

Values: 1 = Lowest Performance; 10 = Highest Performance

Rankings are a general guide. Adhesives should be tested with actual components to ensure acceptable performance.



Making changes easier.

3M™ Repositionable Tapes are double coated. Ideal for applications where one or both parts need to be repositioned or removed easily.

9415PC

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Membrane Switch Spacers — Double Coated Spacers



Accuracy with one touch.

Piece together the power of precision, then seal it in. Design machines that respond to your commands with the lightest touch — so we can live better, work smarter and surpass the limits of yesterday. Because that’s how progress is made — and how success is felt. Membrane switches engineered with 3M™ Acrylic Adhesives measure up to the most demanding standards. With exceptionally high shear strength, great durability and features that streamline the creative process, you can trust that your design delivers accuracy with style—and stands up to the test of time.

Adhesive Family ¹	Product	Description/Application Ideas	Construction			Sheet Size* Master Roll	Specs
			Total Thickness (mils)	Top Liner Adhesive Type Carrier Adhesive Type Bottom Liner	Caliper (mils)		
200MP High Performance Acrylic	7945MP	Excellent temperature, chemical and UV resistance. High shear strength withstands repeated stresses of switch actuation. Designed to separate switch circuitry until actuation. Both liners are printed.	5	58# PCK	—	48" x 36" 48" x 360 yd	UL
				200MP	2		
				Polyester	1		
	7953MP	Same characteristics as 7945MP. Primary liner is printed. Also used for graphic attachment.	3.5	58# PCK	—	48" x 36" 48" x 360 yd	UL
				200MP	1.5		
				Polyester	0.5		
	7956MP	Same characteristics as 7945MP. Both liners are printed.	6	58# PCK	—	24" x 36" 48" x 360 yd	UL
				200MP	2		
				Polyester	2		
	7956MWS	For use in graphic and non-graphic applications. Metalized vapor coat and white color provide strong opacity for facilitating backlighting and eliminating floodcoats. Single liner.	6	58# PCK	—	48" x 360 yd	UL
200MP				2			
Polyester (white, vapor coated)				2			
7956WDL	Same characteristics as 7956MWS except in sheets.	6	58# PCK	—	24" x 36" 48" x 360 yd	UL	
			200MP	2			
			Polyester (white, vapor coated)	2			
7957MP	Same characteristics as 7945MP, except thicker polyester. Both liners are printed.	7	58# PCK	—	48" x 36" 48" x 360 yd	UL	
			200MP	2			
			Polyester	3			
7959MP	Same characteristics as 7945MP, except thicker polyester. Both liners are printed.	9	58# PCK	—	48" x 36" 48" x 360 yd	UL	
			200MP	2			
			Polyester	5			
			200MP	2			
				58# PCK	—		


1. More information on pages 10–13.

*Select products have multiple master sizes.

Go-To Product


Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Membrane Switch Spacers — Double Coated Spacers (cont.)

Adhesive Family ¹	Product	Description/Application Ideas	Construction			Sheet Size Master Roll	Specs
			Total Thickness (mils)	Top Liner Adhesive Type Carrier Adhesive Type Bottom Liner	Caliper (mils)		
 200MP High Performance Acrylic (cont.)	7961MP	Same characteristics as 7945MP, except thicker polyester. Both liners are printed.	11	58# PCK	—	48" x 36"* 48" x 360 yd	UL
				200MP	2		
				Polyester	7		
				200MP	2		
	7966MWS	For use in graphic and non-graphic applications. Metalized vapor coat and white color provide strong opacity for facilitating backlighting and eliminating floodcoats.	9	58# PCK	—	48" x 360 yd	UL
				200MP	2		
				Polyester (white, vapor coated)	2		
				200MP	5		
	7966WDL	Same characteristics as 7966MWS except in sheets.	9	58# PCK	—	24" x 36" 48" x 360 yd	UL
				200MP	2		
				Polyester (white, vapor coated)	2		
				200MP	5		
9045MP	Excellent high temperature, chemical and UV resistance. High cohesive strength withstands repeated stresses of switch actuation. Heavy liner for improved handling and lay-flat properties. Both liners are printed.	5	94# PCK	—	48" x 36"* 48" x 360 yd	UL	
			200MP	2			
			Polyester	1			
			200MP	2			
9057MP	Excellent high temperature, chemical and UV resistance. High cohesive strength withstands repeated stresses of switch actuation. Heavy liner for improved handling and lay-flat properties. Both liners are printed.	7	94# PCK	—	24" x 36" 48" x 360 yd	UL	
			200MP	2			
			Polyester	3			
			200MP	2			
9059MP	Excellent high temperature, chemical and UV resistance. High cohesive strength withstands repeated stresses of switch actuation. Heavy liner for improved handling and lay-flat properties. Both liners are printed.	9	94# PCK	—	48" x 36"* 48" x 360 yd	UL	
			200MP	2			
			Polyester	5			
			200MP	2			
9061MP	Excellent high temperature, chemical and UV resistance. High cohesive strength withstands repeated stresses of switch actuation. Heavy liner for improved handling and lay-flat properties. Both liners are printed.	11	94# PCK	—	24" x 36" 48" x 360 yd	UL	
			200MP	2			
			Polyester	7			
			200MP	2			
				94# PCK	—		

1. More information on pages 10–13.

3M™ Membrane Switch Spacers — Single Coated Spacers

Adhesive Family ¹	Product	Description/Application Ideas	Construction			Sheet Size* Master Roll	Specs
			Total Thickness (mils)	Carrier Adhesive Type Bottom Liner	Caliper (mils)		
 200MP High Performance Acrylic	7992MP	Adhesive 200MP on one side of a clear polyester carrier.	4	Polyester Film	2	24" x 36" 48" x 360 yd	—
				200MP	2		
				94# PCK	—		
	7993MP	Excellent temperature, chemical and UV resistance. Used for lead protection, dome retainer sheets, and for printing conductive circuitry.	3	Polyester Film	1	48" x 36" 48" x 360 yd	UL
				200MP	2		
				94# PCK	—		
	7995MP	Same characteristics as 7993MP, except with thicker polyester.	5	Polyester	3	24" x 36" 48" x 360 yd	UL
				200MP	2		
94# PCK				—			
7997MP	Same characteristics as 7993MP, except with thicker polyester.	7	Polyester	5	24" x 36" 48" x 360 yd	UL	
			200MP	2			
			94# PCK	—			

1. More information on pages 10–13.

*Select products have multiple master sizes.

Go-To Product

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Extended Liner Tapes

Adhesive Family ¹	Product	Application Ideas	Tape Thickness w/o Liner mils (mm)	Liner Type ²	Description	Temperature Resistance °F (°C)		Solvent Resistance	Relative Adhesion	
						Short-Term	Long-Term		HSE	LSE
400 Acrylic Adhesive	465XL	Seal flaps on overnight envelopes. Pressure sensitive edging on business forms. General commercial joining applications. For attaching materials that require more adhesive thickness. Larger outsert attachments.	2.0 (0.05)	60# DK Tan with Green Print	General purpose.	250 (121)	180 (82)	5	5	5
	450EK	Pharmaceutical outsert attachment. For applications requiring a more tear resistant liner.	1.0 (0.025)	78# Extensible Kraft White (No Print)	General purpose.	250 (121)	180 (82)	5	5	5
	450XL	Pharmaceutical outsert attachment. General paper attachment.	1.0 (0.025)	60# DK Tan with Green Print	General purpose.	250 (121)	180 (82)	5	5	5
	920XL	Seal flaps on poly-bags and envelopes. Pressure sensitive edging on business forms, literature, photos, posters and labels.	1.0 (0.025)	40# DK White with Red Print	General purpose.	250 (121)	180 (82)	5	5	5
600	9934XL	P.O.P. displays. Difficult splicing applications, shelf talkers, price tags, polyethylene foam bonding. High-tack to LSE materials. Indirect food-contact applications. ³	4.0 (0.10)	60# DK Tan (No Print)	High-tack to LSE materials.	150 (65)	120 (49)	5	9	9
760 Synthetic Rubber	476XL	Heavy-duty sealing. Mounting of promotional items. Core starting. Closure of overnight boxes, tubes and envelopes. Indirect food-contact applications. ³	6.0 (0.16)	62# DK White with Red Print	High-tack, double coated film.	150 (65)	120 (49)	5	9	9
770 Synthetic Rubber	9925XL⁴	General mounting. P.O.P. items. Attaching tags and labels. Core starting. Permanent bonding paper-to-paper, business forms, traffic tickets, novelty items and literature. Indirect food-contact applications. ³	2.5 (0.065)	43# DK White with Black Print	Tissue reinforced. High initial adhesion to a wide variety of materials.	150 (65)	100 (41)	4	9	9
Other	3693FLE	Commonly used as a self-adhesive closure system on the longitudinal lap of jacketed pipe insulation (SSL – self seal lap) or a temporary closure system for PVC jacketing.	4.0 (0.10)	50# Paper	Aggressive, cold weather acrylic pressure sensitive adhesive (PSA) tape with a finger lift edge (FLE), meaning that on one edge the removable liner extends beyond the adhesive, making it easier to manually remove the liner.	—	250 (121)	—	7	6

1. More information on pages 10–13. 2. More information on page 14. 3. FDA acceptable dry ingredients listed as indirect food-contact additives when used in food packing with minimal opportunity for exposure. 4. Non-liner side is adhesive coated full width.

Easy liner starting and removal.

3M™ Extended Liner Tapes are constructed with liners that extends beyond the width of the adhesive to provide easy liner starting. The dry edge or finger lift edge on each side of the tape makes liner removal easy.




★ Go-To Product

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Screen Printable Adhesives

Product Group	Product	Description/Application Ideas	Adhesion Specs	Size
Screen Printable Adhesives	SP7202	Screen printable, cures in seconds to create a pressure sensitive adhesive. Until exposed to UV, adhesive stays fluid to help reduce screen refills and cleaning. Solvent free 100% solids.	Process dependent	1 liter (6/case)
	SP7533	Water-dispersed, pressure sensitive. Excellent balance of peel and shear strength. High heat resistance.	Process dependent	1 liter (6/case) 5 liters (2/case) 1 gallon (4/case)
	SP7555	UV curable. Pressure sensitive. Excellent LSE adhesion and water resistance.	Process dependent	1 liter (6/case)



Scotch® ATG Adhesive Transfer Tapes

Adhesive Family ¹	Product	Tape Thickness w/o Liner mils (mm)	Description	Temperature Resistance °F (°C)		Solvent Resistance	Relative Adhesion		Application Ideas	Adhesive Transfer Tape Equivalent
				Short-Term	Long-Term		HSE	LSE		
300 High-tack Acrylic	976	2.0 (0.05)	High-tack. Excellent adhesion to most plastics.	250 (121)	150 (65)	6	8	9	Attach fabric swatches in sample books.	927
	969	5.0 (0.13)	High-tack. Excellent adhesion to most plastics.	250 (121)	150 (65)	6	8	9	Assemble P.O.P. displays. Bond trim strips to furniture or luggage. Bond labels to plastic toys. Attach gaskets or foams.	950
350 High Performance Acrylic	926	5.0 (0.13)	High performance. Excellent solvent and temperature resistance.	450 (232)	300 (149)	8	10	10	Bond fabric or trim to window blinds. Splice aluminum coils. Bond foam insulation. Mount nameplates on award plaques.	9485PC
400 General Purpose Adhesive	924	2.0 (0.05)	General purpose. Excellent adhesion to most paper stocks.	250 (121)	180 (82)	5	5	5	Seal pocket in folders. Bond mat board in picture frames. Splice paper, films and foils. General purpose bindery attaching.	465
	987*	1.7 (0.040)	General purpose. Excellent adhesion to most paper stocks.	250 (121)	180 (82)	5	5	5	Seal pocket in folders. Bond mat board in picture frames. Splice paper, films and foils. General purpose bindery attaching.	465
400/1000 Repositionable Adhesive ²	928	2.0 (0.05)	Differential tack. Repositionable.	180 (82)	150 (65)	5	5/1	5/1	Attach credit card in mailer. Core start/end tab paper, films and foils. Attach temporary labels.	9416

1. More information on pages 10–13. 2. Second number reflects removable adhesive side. *3M Brand.



Scotch® ATG Applicator 714
Used for 1/4" wide tape



Scotch® ATG Applicator 3662
Used for 2" wide tape

Scotch® ATG Applicator 752C
3/4", 1/2" and 1/4" wide tape
(1/4" adapter purchased separately)



Scotch® ATG Applicator 700
Used for 1/2" and 3/4" wide tape

No mess, no cleanup.

A touch of the finger triggers a quick, controlled application of Scotch® ATG Adhesive Transfer Tape at the same time as the liner rewinds into the applicator.

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.




3M™ Foam Lamination Tapes — L-Series


The perfect seal. Just the right amount of acoustic insulation. Ideal impact damping. Whatever your design challenge, there's a 3M™ Foam Lamination Tape that can make your vision a reality. Our L1/L3 series adhesive platforms allow you to pair your design with the right foam and adhesive for your application.

Product Family	Product	Adhesive Caliper mils (mm)	Liner Type	Liner Caliper mils (mm)	Temperature Resistance °F (°C)	Roll size Width in. (mm) Length yds. (m)	Application Ideas
L1 Platform Modified acrylic adhesive with good initial tack and peel adhesion.	Double Coated Tape L1+DCP	3.5 (0.088)	74# white, unprinted DK	4.1 (0.104)	200°F (93°C)	Widths: 39 (1000), 54 (1372), 60 (1524) Length: 251 (230)	Foams, including cross-linked PE, EVA and microcellular urethane.
	Scrim Reinforced Adhesive Transfer Tape L1+RT	3.2 (0.081)	74# white, unprinted DK	4.1 (0.104)	200°F (93°C)	Widths: 39 (1000), 54 (1372), 60 (1524) Length: 251 (230)	Foams, including cross-linked PE, EVA and microcellular urethane.
L3 Platform Specialty acrylic adhesive with good adhesion to many elastomeric substrates.	Adhesive Transfer Tape L3+T3	3.0 (0.076)	83# tan, unprinted PCK	6.2 (0.157)	275°F (135°C)	Width: 54 (1372) Length: 54 (229)	Elastomers, including TPV, neoprene rubber, butyl rubber and many versions of EPDM rubber.
	Adhesive Transfer Tape L3+T5	5.0 (0.127)	83# tan, unprinted PCK	6.2 (0.157)	275°F (135°C)	Width: 54 (1372) Length: 54 (229)	Elastomers, including TPV, neoprene rubber, butyl rubber and many versions of EPDM rubber.


Scrim Reinforced Tape



Double Coated Tape



Adhesive Transfer Tape



Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Bonding Films

Product	Caliper (mils)	Base Resin	Color	Bond/Cure Time	Bondline Temp. (°F)	Description	Spec	Size
406	3.0	EAA	Clear	2–5 sec.	320	Flexible, light colored, thermoplastic bonding film exhibits good adhesion to a variety of substrates, especially metals.	—	48" x 180 yd
583	2.0	Nitrile Phenolic	Brown	2–5 sec.	250	Heat or solvent-activated dry film adhesive.	UL	48" x 180 yd
588	6.0	Nitrile Phenolic	Yellow	2–5 sec.	250	Heat or solvent-activated dry film adhesive.	—	21" x 180 yd
615	2.5 or 4.0	Polyester	Tan	2–5 sec.	280	Flexible, light colored, thermoplastic bonding films exhibit good adhesion to a variety of substrates. 615 contains a non-woven scrim.	—	0.6m x 155m
615S	6.0 or 9.0	Polyester	Tan	2–5 sec.	280	Flexible, light colored, thermoplastic bonding films exhibit good adhesion to a variety of substrates. 615S contains a non-woven scrim.	—	6 mil: 0.6m x 155m 9 mil: 0.6m x 80m
668	2.5 or 4.0	Polyamide	Tan	2–5 sec.	320	Flexible, light colored, thermoplastic bonding film is tacky at room temperature and has good adhesion to a variety of substrates at elevated temperatures.	—	0.6m x 155m
690	8.0	Polyester	Tan	2–5 sec.	280	Flexible, light colored, thermoplastic bonding film is tacky at room temperature and has good adhesion to a variety of substrates at elevated temperatures.	—	0.6m x 80m*

*MOQ is 2 rolls.

3M™ Double Coated Foam Tapes

Carrier	Product	Liner Type	Tape Thickness mils (mm)	Description	Adhesive Type	Temperature Resistance °F (°C)		Solvent Resistance	Relative Adhesion		Application Ideas
						Minutes Hours	Days Weeks		HSE	LSE	
Urethane	4004	A	250 (6.4)	Off-white, open-cell urethane foam carrier. High shear adhesive with high temperature resistance.	100	380 (193)	220 (104)	Med	High	Low	Bond acoustic panels to walls. Mount air fresheners, soap dispensers, interior signs and nameplates. Attach wire clips to various surfaces. Mount electrical channel to wall.
	4008	A	125 (3.2)		100	380 (193)	220 (104)	Med	High	Low	
	4016	A	62 (1.6)		100	380 (193)	220 (104)	Med	High	Low	
	4026	A	62 (1.6)		100	380 (193)	220 (104)	Med	High	Low	
	4052	A	31 (0.8)	Black version of 4032.	100	380 (193)	220 (104)	Med	High	Low	Bond acoustic panels to walls. Mount air fresheners, soap dispensers, interior signs and nameplates. Attach wire clips to various surfaces. Mount electrical channel to wall.
	4056	A	62 (1.6)	Black version of 4016 and 4026.	100	380 (193)	220 (104)	Med	High	Low	
	4085	E	45 (1.1)	Off-white, open-cell urethane foam carrier. High-tack adhesive.	740	200 (93)	125 (52)	Med	High	Low	
Polyethylene	4462	B	31 (0.8)	White or black, closed-cell polyethylene foam carrier. High-tack adhesive.	745	158 (70)	120 (49)	Med	High	Low	Attach hooks, wire clips and racks. Mount retail shelf price channels. Mount pen holders.
	4466	B	62 (1.6)		745	158 (70)	120 (49)	Med	High	Low	
	4492	C	31 (0.8)	White or black, closed-cell polyethylene foam carrier.	430	180 (82)	158 (70)	Med	High	Low	Mount nameplates on awards and novelties. P.O.P. displays and signs.
	4496	C	62 (1.6)	High shear adhesive with high temperature resistance.	430	180 (82)	158 (70)	Med	High	Low	
Acrylic	4658F	D	31 (0.8)	Clear, closed-cell acrylic foam tape. Clean removability from many substrates.	100	212 (100)	175 (80)	High	High	Low	Removable P.O.P. displays, signs, exhibits and trade shows, nameplates.

Liner Types: A. 3 mil 62# Densified Kraft-Green Plaid; B. 3 mil Densified Kraft-White; C. 4 mil 58# Polycoated Kraft-Tan; D. 2 mil Polyester Film-clear; E. 3 mil Densified Kraft-Tan.





3M™ Double Coated Urethane Foam Tape 4026

An excellent choice for interior mounting applications where the tape will be protected from the environment.

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.





 Long-term bonding
 in a wide range
 of temperatures.



3M™ VHB™ Tapes



With 3M™ VHB™ Tapes, you can maintain consistency from sketch to construction, eliminating distracting, visible fasteners, like screws and bolts. These high-strength, double-sided acrylic foam tapes let you quickly and easily create a long-lasting bond that actually builds strength over time. With the ability to join a variety of materials including aluminum, steel, glass, plastics and painted and powder-coated surfaces. They provide resilient bonding solutions in just about anything you can dream up. Visit [3M.com/VHB](https://www.3m.com/VHB) to open a world of new possibilities.

Product	Tape Thickness w/o Liner mils (mm)	Liner Type	Description	Temperature Resistance °F (°C)		Solvent Resistance	Relative Adhesion		Spec	Application Ideas
				Minutes Hours	Days Weeks		HSE	LSE		
4941 Tape Family										
4926	15 (0.4)	A	Gray, closed-cell acrylic foam carrier. Conformable. For most critical applications where a customer needs the strongest possible solution. Tested to resist high windloads, vibration, etc. where holding strength is critical.	300 (149)	200 (93)	High	High	Med	UL	Bond architectural signs to frames. Attach trim and extrusions. Hat channels and stiffeners.
4936	25 (0.64)	A		300 (149)	200 (93)	High	High	Med	UL	
4936F	25 (0.64)	F		300 (149)	200 (93)	High	High	Med	UL	
4941	45 (1.1)	A		300 (149)	200 (93)	High	High	Med	UL	
4941F	45 (1.1)	D		300 (149)	200 (93)	High	High	Med	UL	
4956	62 (1.6)	A		300 (149)	200 (93)	High	High	Med	UL	
4956F	62 (1.6)	F		300 (149)	200 (93)	High	High	Med	UL	
4991	90 (2.3)	F		250 (121)	200 (93)	High	High	Med	UL	
4991B	90 (2.3)	F	Black version of 4991.	250 (121)	200 (93)	High	High	Med	—	Bond architectural signs to frames. Attach trim and extrusions. Hat channels and stiffeners.
4919F	25 (0.64)	F	Black version of 4936F.	300 (149)	200 (93)	High	High	Med	UL	
4947F	45 (1.1)	F	Black version of 4941F.	300 (149)	200 (93)	High	High	Med	UL	
4979F	62 (1.6)	F	Black version of 4956F.	300 (149)	200 (93)	High	High	Med	UL	
5952 Tape Family										
5906	6 (0.15)	G	Black, closed cell acrylic foam carrier. A highly conformable tape that excels at bonding a variety of paint systems, medium surface energy plastics and irregular surfaces.	300 (149)	250 (121)	High	High	Med	—	Automotive Displays. Bond and seal polycarbonate lens over LCD. Bond and seal plastic windows to pre-painted control panels/switch gear. Mount vinyl wiring ducts and conduit channels. Seam vinyl banners.
5907	8 (0.20)	G		300 (149)	250 (121)	High	High	Med	—	
5908	10 (0.25)	G		300 (149)	250 (121)	High	High	Med	—	
5909	12 (0.30)	G		300 (149)	250 (121)	High	High	Med	—	
5913	14 (0.35)	G		300 (149)	250 (121)	High	High	Med	—	
5915	16 (0.40)	F		300 (149)	250 (121)	High	High	Med	UL	
5915P	16 (0.40)	E		300 (149)	250 (121)	High	High	Med	UL	
5925	25 (0.60)	F		300 (149)	250 (121)	High	High	Med	UL	
5925P	25 (0.60)	E		300 (149)	250 (121)	High	High	Med	UL	
5930	32 (0.80)	F		300 (149)	250 (121)	High	High	Med	UL	

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ VHB™ Tapes (cont.)

Product	Tape Thickness w/o Liner mils (mm)	Liner Type	Description	Temperature Resistance °F (°C)		Solvent Resistance	Relative Adhesion		Spec	Application Ideas
				Minutes Hours	Days Weeks		HSE	LSE		
5952 Tape Family (cont.)										
5930P	32 (0.80)	E	Black, closed cell acrylic foam carrier. A highly conformable tape that excels at bonding a variety of paint systems, medium surface energy plastics and irregular surfaces.	300 (149)	250 (121)	High	High	Med	UL	Automotive Displays. Bond and seal polycarbonate lens over LCD. Bond and seal plastic windows to pre-painted control panels/switch gear. Mount vinyl wiring ducts and conduit channels. Seam vinyl banners.
5952	45 (1.1)	F		300 (149)	250 (121)	High	High	Med	UL	
5952P	45 (1.1)	E		300 (149)	250 (121)	High	High	Med	UL	
5962	62 (1.6)	F		300 (149)	250 (121)	High	High	Med	UL	
5962P	62 (1.6)	E		300 (149)	250 (121)	High	High	Med	UL	
5958FR	40 (1.0)	F	Meets FAR 25.853 (a) 12 sec vertical burn Appendix F, Part 1 (a) (ii).	300 (149)	200 (93)	High	High	Med	—	Overhead stow bins, signage, kick plates, galley modules, plastic and metal decorative trim, ceiling tile stiffeners, mirror mounting, air duct spuds, floor and wall panel attachment, clip attachment.
RP+ Tape Family										
RP+040GP	16 (0.4)	A	Gray, closed-cell acrylic foam carrier. A general purpose adhesive with 3M™ VHB™ Tape performance, designed for a wide range of general bonding needs.	450 (230)	250 (121)	High	High	Med	UL	Panel bonding, stiffener attachment and trim attachment.
RP+040GF	16 (0.4)	F		450 (230)	250 (121)	High	High	Med	UL	
RP+060GP	25 (0.6)	A		450 (230)	250 (121)	High	High	Med	UL	
RP+060GF	25 (0.6)	F		450 (230)	250 (121)	High	High	Med	UL	
RP+080GP	32 (0.8)	A		450 (230)	250 (121)	High	High	Med	UL	
RP+080GF	32 (0.8)	F		450 (230)	250 (121)	High	High	Med	UL	
RP+110GP	45 (1.1)	A		450 (230)	250 (121)	High	High	Med	UL	
RP+110GF	45 (1.1)	F		450 (230)	250 (121)	High	High	Med	UL	
RP+160GP	62 (1.6)	A		450 (230)	250 (121)	High	High	Med	UL	
RP+160GF	62 (1.6)	F		450 (230)	250 (121)	High	High	Med	UL	
RP+230GP	90 (2.3)	A		450 (230)	250 (121)	High	High	Med	UL	
RP+230GF	90 (2.3)	F	450 (230)	250 (121)	High	High	Med	UL		
GPH Tape Family										
GPH-060GF	25 (0.6)	F	Superior high-temp performance for powder coat or liquid paint processes and multi material bonding.	450 (230)	300 (150)	High	High	Med	UL	GPH's high temperature resistance allows it to reduce the number of "touches," leading to a more streamlined manufacturing process.
GPH-110GF	45 (1.1)	F		450 (230)	300 (150)	High	High	Med	UL	
GPH-160GF	62 (1.6)	F		450 (230)	300 (150)	High	High	Med	UL	
LSE Tape Family										
LSE-060WF	25 (0.6)	F	White, closed cell acrylic foam carrier. Designed to bond composites, TPE, TPO, PP and low surface energy (LSE) plastics without primer. UL 746C.	300 (150)	200 (93)	High	High	High	UL	Made to live outdoors. Resists hot, cold and cycling temperature, UV light, moisture and solvents. Seals against environmental conditions. Low-temperature bonding with high initial tack at low temperatures on frost-free surfaces down to 0°C.
LSE-110WF	45 (1.10)	F		300 (150)	200 (93)	High	High	High	UL	
LSE-160WF	62 (1.6)	F		300 (150)	200 (93)	High	High	High	UL	
4950 Tape Family										
4914-015	6 (0.15)	A	Closed-cell acrylicfoam tape.	300 (150)	200 (93)	High	High	Med	—	This family has general purpose adhesive on both sides of firm type foam. Typically used on metal, glass and high surface energy plastic substrates. Available in white and black.
4914-020	8 (0.20)	A	Closed-cell acrylicfoam tape.	300 (150)	200 (93)	High	High	Med	—	
4914	10 (0.25)	A	Closed-cell acrylicfoam tape. UL 746C.	300 (150)	200 (93)	High	High	Med	UL	
4920	15 (0.4)	A	Closed-cell acrylicfoam tape. UL 746C.	300 (150)	200 (93)	High	High	Med	UL	
4930	25 (0.6)	A	Closed-cell acrylicfoam tape. UL 746C.	300 (150)	200 (93)	High	High	Med	UL	
4950	45 (1.1)	A	Closed-cell acrylicfoam tape. UL 746C.	300 (150)	200 (93)	High	High	Med	UL	
4955	80 (2.0)	A	Closed-cell acrylicfoam tape. UL 746C.	400 (204)	300 (150)	High	High	Med	UL	
4959	120 (3.0)	A	Closed-cell acrylicfoam tape. UL 746C.	400 (204)	300 (150)	High	High	Med	UL	
4910 Tape Family										
4905	20 (0.5)	F	Clear, acrylic construction for joining transparent material.	300 (150)	200 (93)	High	High	Low	UL	Excellent for applications where clear or colorless is desired. The general purpose adhesive on both sides is suitable for high surface energy substrates.
4910	40 (1.0)	F	Clear, acrylic construction for joining transparent material.	300 (150)	200 (93)	High	High	Low	UL	

Liner Types: A. 3 mil 54# Densified Kraft Paper; B. 5 mil Clear Polyethylene Film; C. 2 mil Polyester Film D. 5 mil Red Polyethylene Film; E. 4 mil 58# Polycoated Kraft Paper; F. 5 mil Red Printed Polyethylene Film; G. 3 mil Clear PET. **Relative Adhesion:** HSE: High Surface Energy; LSE: Low Surface Energy. **Multi-purpose Acrylic:** Bonds to a wide range of materials including metals, glass, and high and medium surface energy plastics and paints. Resists migration of plasticizers in vinyl substrates. **Modified Acrylic:** Bonds to medium low surface energy paints and plastics, including many powder coated paints in addition to the substrates listed with the multi-purpose acrylic adhesive (except plasticized vinyl).


Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

Durable Label Materials

Vital messaging. Securely accomplished.

Labels need to last a long time to keep providing end users with vital messaging through scorching sun, bitter cold, harsh chemical environments and more. 3M's innovative solutions perform with different print methods, substrates and ink systems. Plus, our programs offer the speed, flexibility and service that will help everyone succeed.

Learn more at:
3M.com/DurableLabels



Communicate critical messages.

Discover how to help make sales soar with 3M™ Versatile Print Durable Label Materials.

Delivering vital information. In the toughest environments.

3M is the premier durable label solution provider globally in the label industry today. 3M materials and services will enable you and your customers to present the best images, products, and quality as we solve marketplace solutions from design to production. We do this by partnering with industry leaders to deliver the best possible technology for innovative solutions regardless of your print method, substrates and ink systems.


Performance you can trust. From the top...down.

3M™ Durable Label Materials combine performance-based adhesives, topcoats, liners and more — a winning combination that helps keep messaging vibrant and legible for years, even in harsh conditions. When you're facing a challenging situation, you can talk to a 3M Technical Services Specialist about your exact needs and we'll help you find a solution.



Printing Performance

State-of-the-art topcoat technology keeps you on the cutting edge of printing trends.



Adhesives & Liners

World-class adhesive and liner performance with unmatched durability.



Full-Service Value

Availability is key. 3M provides the support needed to ensure products arrive on time and perform for the tasks at hand.


Fast Track Service Programs — The speed, flexibility and service you need.

To best meet your customers needs for short runs or specialized materials, use the Fast Track Service Programs. These cost-effective options meet your requirements and your tight deadlines. Program advantages include: less inventory, less waste, faster turnaround, first run assurance, and faster delivery.



2-Day Pre-Slit Program

- Pre-slit stocked 4.5" or 6" rolls
- Shipped within 48 hours
- Minimum order of 4.5" or 6" pre-slit rolls
- No upcharge



2-Day Precision Roll Program

- Custom-slit widths
- No upcharge
- Roll length of 1,668 ft.
- Minimum order of 2" x 1,668 ft.



Mini-Master Program

- Custom-slit, full web width master rolls
- No upcharge
- Roll length short as 150 ft.
- Minimum order starts at 750 ft. rolls

Printing Methods Overview



	Why Customers Choose	Advantages	Disadvantages
<p>Thermal Transfer</p> <p>A digital printing method in which material is applied to the label material by melting a coating of ribbon so that it stays glued to the material on which the print is applied. It contrasts with direct thermal printing, where no ribbon is present in the process.</p>	<ul style="list-style-type: none"> • Variable information on demand • Barcoding, track and trace • Extreme durability • End-user print on demand 	<ul style="list-style-type: none"> • Many substrates can be printed with inks • Variety of ribbons available to meet application needs • Cost effective use for serialization 	<ul style="list-style-type: none"> • Single color printing based on ribbon used • Images are often required to be pre-printed with other print methods
<p>Flexographic</p> <p>Uses quick-drying, semi-liquid inks and flexible photopolymer printing plates wrapped around rotating cylinders on a web press. The inked plates have a slightly raised image and rotate at high speeds to transfer the image to the substrate.</p>	<ul style="list-style-type: none"> • The most economical for high volume printing • The most common print method for labels • Wide choice of inks (water-based, UV) 	<ul style="list-style-type: none"> • Lower cost process for high volume jobs • Large number of label material options • Low maintenance equipment 	<ul style="list-style-type: none"> • Cannot print variable data • Newer water-based inks require more durable top coatings to anchor to the media (i.e., Versatile Print)
<p>UV Inkjet</p> <p>A form of digital printing that uses ultra-violet lights to almost instantly dry or cure ink as it is printed. In addition, UV cured inks are weather-resistant and offer increased resistance to fading.</p>	<ul style="list-style-type: none"> • Printing on demand • Variable data • Design freedom • Reduced need for constant cleaning 	<ul style="list-style-type: none"> • Printing and die-cutting in one step • Cost effective for short print runs (no print plate required like in flexo) • Less setup material waste (vs. flexo) • VOC free 	<ul style="list-style-type: none"> • Inks must be cured to dry (UV) • Less efficient for longer static image runs
<p>Laser/Toner-Based</p> <p>An electrostatic digital printing process where a laser is used to apply a negative charge to a drum. Pigmented toner is then collected by the charge and transferred to the substrate where it is fused by heat and pressure.</p>	<ul style="list-style-type: none"> • Cost effective print method • Designed for small to medium runs 	<ul style="list-style-type: none"> • Cost effective for short print runs (no print plate required like in flexo) • Less set up material waste (vs. Flexo) 	<ul style="list-style-type: none"> • Limited to matte substrates • Metalized films may damage equipment • Durability is moderate
<p>Screen Print</p> <p>A printing technique whereby a mesh is used to transfer ink onto a substrate, except in areas made impermeable to the ink by a blocking stencil. Cured with UV exposure.</p>	<ul style="list-style-type: none"> • Extremely durable inks, fade resistant • Outdoor durability • Less expensive on large runs vs. digital 	<ul style="list-style-type: none"> • Able to print a large variety of materials • Heavier ink laydowns (versatility) • Vibrant, high quality inks 	<ul style="list-style-type: none"> • Amount of time to set up jobs • Not practical for smaller runs • Not environmentally friendly
<p>Solvent Inkjet</p> <p>A digital form of printing that utilizes pigmented inks carried in a Volatile Organic Compound. Printed materials are usually cured through heating of inks and substrates.</p>	<ul style="list-style-type: none"> • Extremely durable inks, fade resistant • Outdoor durability • Digital short run capability 	<ul style="list-style-type: none"> • Wide web format for large graphics and banners • High resolution graphics • Fast print speeds 	<ul style="list-style-type: none"> • Mainly limited to vinyl substrates • VOC vapors
<p>Water-Based Inkjet</p> <p>An inkjet printing system which utilizes electronic pulses to activate jets of ink to deposit the ink in precise locations. Water is the carrier for pigmented and dye base inks.</p>	<ul style="list-style-type: none"> • Color variable information on demand • Can be utilized for small to medium digital runs • Durability has greatly improved in recent years 	<ul style="list-style-type: none"> • Small footprint that allows end user to print high quality labels in their specialized processes • Media is converted often in blanks processed by converters 	<ul style="list-style-type: none"> • Limited run volume • Not well suited for longer print runs

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

One topcoat. More possibilities.

3M™ Versatile Print Label Material

The future of labels is here. 3M™ Versatile Print Material works with more inks on more printing presses. Plus, you have the flexibility to use a single product for multiple print jobs. Stay on the forefront of the industry with a topcoat that creates vibrant labels that last longer, plus saves you time and money.

Versatile across these printing methods:

- Water-based Flexographic
- UV Flexographic
- UV Digital Inkjet
- Thermal Transfer
- Screen Printing
- Toner-Based
- Hybrid Presses



Versatile — let the creativity flow.

- Proprietary 3M topcoat offers exceptional performance across multiple print methods
- Estimating is streamlined with one go-to label material

Verified — trusted results on more presses.

- UL Component Recognition to UL969 with many ink systems and print technologies*
- Print press manufacturer tested
- Topcoat has both high gloss and high surface energy compared to competitive offerings, giving strong print performance

*See UL file MH16411 and MH18072 in UL Product iQ™ (Certifications Search) at ul.com for specific details.


— 3M 7871V	- - - Competitor A
— 3M 7908V	- - - Competitor B

Vibrant — stunning results.

- Streak free and crystal clear with crisp edges
- Near zero edge bleed and high image sharpness
- Create highly durable, glossy labels on digital and flexo

Print performance.

3M™ Versatile Print Label Material outperforms traditional gloss PET products in key measures of print performance.



Ink anchorage tested via ASTM 3359 for cross hatch adhesion using 3M™ Scotch® Cellophane Film Tape 610. Scratch and smear resistance tested via industry recognized qualitative tests using thumbnail scratch and thumb pressure smear. For more information, please contact a 3M expert at 3M.com/durablelabels.

Stay Tuned! We are continuing to expand our portfolio of 3M Versatile Print products. Please contact your 3M Converter Markets representative for more information regarding Versatile Print series product availability.

3M™ Versatile Print Label Materials

Facestock	Product	Typical Performance Characteristics	Construction		Print Method*							
			Caliper (mils)	Facestock Adhesive Type Liner	Thermal Transfer	Flexographic	UV Inkjet	Laser/Toner-Based	Screen	Solvent Inkjet	Water Inkjet	
3M™ Versatile Print Polyester Gloss White	7871V	Excellent high temperature resistance and adhesion to LSE plastics and smooth powder coats. Broad applications in automotive, electronics, healthcare, heavy machinery, general industrial. Specialty applications in automotive EV battery, GHS drum labeling. BS5609 certified durable label.	2.0 1.8 3.2	PET, Versatile Print TC 350 55# Densified Kraft	■	■	■	■	■			
	7868V	High abrasion and solvent resistance. Excellent high temperature resistance. Excellent adhesion to LSE plastics and smooth powder coats. BS5609 certified durable label.	2.0 1.1 3.2	PET, Versatile Print TC 350 55# Densified Kraft	■	■	■	■	■			
	7908V	Heavy adhesive coat weight for textured surfaces. Excellent high temperature resistance. Excellent adhesion to LSE plastics and powder coats. 90# liner with layflat properties ideal for sheet and screen printing applications.	2.0 1.8 6.8	PET, Versatile Print TC 350 90# Polycoated Kraft	■	■	■	■	Ⓢ			
	7331V	Good for general purpose indoor and outdoor use. Excellent bond to LSE plastics. Applications include medical device and equipment, lawn and garden, and appliance.	2.0 0.8 3.2	PET, Versatile Print TC 300 55# Densified Kraft	■	■	■	■	■			
	7816V	High abrasion and solvent resistance. Economical durable label material with firm adhesive to resist oozing.	2.0 0.8 3.2	PET, Versatile Print TC 310 55# Densified Kraft	■	■	■	■	■			
3M™ Versatile Print Polyester Gloss Platinum	7872V	Excellent high temperature resistance and adhesion to LSE plastics and smooth powder coats. Broad applications in automotive, electronics, healthcare, heavy machinery, general industrial. Differentiate your labels with a unique platinum metallic appearance.	2.0 1.8 3.2	PET, Versatile Print TC 350 55# Densified Kraft	■	■	■	■	■			
	7875V	Durable label material with firm adhesive to resist oozing. Differentiate your labels with a unique platinum metallic appearance.	2.0 0.8 3.2	PET, Versatile Print TC 310 55# Densified Kraft	■	■	■	■	■			
3M™ Versatile Print Polyester Gloss Bright Silver	7323V	Good for indoor and outdoor use. Excellent bond to LSE plastics. Match a metallic look with gloss bright silver.	2.0 0.8 3.2	PET, Versatile Print TC 300 55# Densified Kraft	■	■	■	■	■			
	7903V	Good for indoor and outdoor use. Excellent bond to LSE plastics. 90# liner with layflat properties ideal for sheet and screen printing applications. Match a metallic look with gloss bright silver.	2.0 1.8 6.8	PET, Versatile Print TC 350 90# Polycoated Kraft	■	■	■	■	Ⓢ			
3M™ Versatile Print Polyester Gloss Brushed Silver	7909V	High abrasion and solvent resistance. 90# liner with layflat properties ideal for sheet and screen printing applications. Applications include heavy machinery, name plate, and safety labeling.	2.0 1.8 6.8	PET, Versatile Print TC 350 Polyester Film	■	■	■	■	■			
3M™ Versatile Print Polyester Gloss Clear	7876V	High abrasion and solvent resistance. Heavy adhesive coat weight for textured surfaces. Excellent high temperature resistance. Excellent adhesion to LSE plastics and powder coats. Use where you need a printable, clear label with high performance adhesive.	2.0 1.8 3.2	PET, Versatile Print TC 350 55# Densified Kraft	■	■	■	■	■			
	7350V	Good for indoor and outdoor use. Excellent bond to LSE plastics. Use where you need a printable, clear label with high performance adhesive.	2.0 0.8 3.2	PET, Versatile Print TC 300 55# Densified Kraft	■	■	■	■	■			
	7905V	Excellent high temperature resistance. Excellent adhesion to LSE plastics and powder coats. 90# liner with layflat properties ideal for sheet and screen printing applications. Use where you need a printable, clear label with high performance adhesive.	2.0 1.8 6.8	PET, Versatile Print TC 350 90# Polycoated Kraft	■	■	■	■	Ⓢ			

*3M™ Durable Label Materials have been tested with various print systems with positive results. Print systems vary, so please request a sample and test in your specific application.

Ⓢ 90# polycoated kraft liner is specifically designed for screen printing.

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

**Water-based.
Fast paced.
Inkjet printable.**

3M™ Water-based Inkjet Label Materials

Optimize your water-based inkjet printing with this breakthrough durable label material. 3M™ Water-based Inkjet Labels let you print with great resolution at a low cost per area. It's the durable label stock you can count on to enhance your digital messaging.

High value. Low cost per area.

- Unique topcoat designed for water-based inkjet print systems
- Durable facestock and adhesive stand up to harsh environments
- UL recognized with several different water-based inkjet systems
- BS5609, Section 3 compliant material



More story at
3M.com/DurableLabels
Request a sample

Facestock	Product	Typical Performance Characteristics	Construction		Print Method*							
			Caliper (mils)	Facestock Adhesive Type Liner	Thermal Transfer	Flexographic	UV Inkjet	Laser/Toner-Based	Screen	Solvent Inkjet	Water Inkjet	
3M™ Water-based Inkjet Polyester White	7850-IJ	Excellent high temperature resistance and adhesion to LSE plastics and smooth powder coats. Applications include medical device and equipment, heavy machinery.	3.0 1.1 3.2	PP, Waterbased Inkjet TC 350 55# Densified Kraft				■				■
	7882-IJ	Excellent cold temperature performance for a wide range of applications. Ideal for freezer or pharmaceutical applications.	3.0 0.8 3.2	PP, Waterbased Inkjet TC 400 55# Densified Kraft				■				■
3M™ Water-based Inkjet Polypropylene White	7790-IJ	Durable facestock and adhesive stand up to harsh environments. BS5609 certified durable label. Ideal for use in chemical drum labeling applications.	5.0 1.1 3.2	PP, Waterbased Inkjet TC 350 55# Densified Kraft				■				■
	FP033-IJ	Emulsion-based, high performance LSE adhesive with high-tack for demanding applications. Broad applications in general industrial.	5.0 1.4 3.2	PP, Waterbased Inkjet TC P1480 50# SC				■				■

*3M™ Durable Label Materials have been tested with various print systems with positive results. Print systems vary, so please request a sample and test in your specific application.



More durable than paper-based labels.

This premium graphic label material needs no additional topcoating or priming for print receptivity. This combines with world-class film and adhesive technology to ensure that your label performs, no matter what.

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

Facestock Properties

Facestock	Features	Film Properties	Processing Properties	Environmental Resistance to:			Print Method*						
		Service Temperatures	Conformability	Chemical	Moisture	Outdoor/UV	Thermal Transfer	Flexographic	UV Inkjet	Laser/Toner-Based	Screen	Solvent Inkjet	Water Inkjet
Acetate	Rigid film, tears easily, works well for security seals or overlamine.	-20 to 140°F	2	2	2	2							
Acrylate	Excellent clarity and UV resistance. 5 year outdoor performance.	-40 to 175°F	3	7	7	10	■						
Acrylate, Cast	Ultra-high temperature performance.	-40 to 392°F 530 for 30 sec. 500 for 7 min.	7	9	9	7	■						
Acrylate, Cast Modified	Ultra-high temperature performance. Can be imaged and kiss cut by a laser beam. Long-term readability, chemical and abrasion resistance.	-40 to 392°F 530 for 1 min. 482 for 5 min. 440 for 60 min.	7	10	8	10				■			
Acrylic	Good clarity and UV resistance.	-20 to 140°F	3	5	7	7		■					
Aluminum Foil	Vinyl top-coated for ink receptivity. Facestock can be embossed using dot matrix impact printers.	-40 to 350°F	4	7	10	10		■				■	
Polyimide	Ultra-high temperature performance. Easy readability of variable information and bar codes.	-40 to 500°F	6	10	10	10	■						
Thermoplastic Polycarbonate	Used to achieve the attractive appearance of subsurface screen printed polycarbonate.	-40 to 250°F	4	8	9	7							
Paper	Pharmaceutical and performance paper.	-40 to 350°F	3	3	2	6	■	■					
Polyart®	Non-glare surface, biaxially oriented, printable with some cold fusing and flash fusing laser printers. Accepts handwriting with a ballpoint pen or marker.	-40 to 160°F	7	6	8	7	■	■				■	
Polyester EDP, DMI and Laser TC	Polyester EDP available in white, silver and clear. Optimal clarity for overlamine applications. High quality rigid film with high tensile strength. Excellent dimensional stability. Not recommended for curved surfaces. High quality rigid film. High tear resistance, notch sensitive.	-40 to 302°F -20 to 257°F Clear only	2	9	9	8	■	■		■	■		
Polyester White and Clear Laser TC	Polyester available in white, silver and clear. Clear polyester provides optimal clarity for overlamine applications. High quality rigid film with high tensile strength. Excellent dimensional stability. Not recommended for curved surfaces. High quality rigid film. High tear resistance, notch sensitive.	-20 to 257°F	2	9	9	8	■	■		■	■		
Polyester MC		-40 to 302°F	2	9	9	8	■	■		■	■		
Polyester PT		-40 to 302°F -20 to 257°F Clear only	2	9	9	8	■	■			■		

*3M™ Durable Label Materials have been tested with various print systems with positive results. Print systems vary, so please request a sample and test in your specific application.

Values: 1 = Lowest Performance; 10 = Highest Performance

Rankings are a general guide. Adhesives should be tested with actual components to ensure acceptable performance.

For product recommendations or technical support, please call the Converter Markets Technical Support Line 1-800-223-7427.

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

Facestock Properties (cont.)

Facestock	Features	Film Properties	Processing Properties	Environmental Resistance to:			Print Method*						
		Service Temperatures	Conformability	Chemical	Moisture	Outdoor/UV	Thermal Transfer	Flexographic	UV Inkjet	Laser/Toner-Based	Screen	Solvent Inkjet	Water Inkjet
Versatile Print Topcoat	High abrasion and solvent resistance. Polyester films provide moisture barrier properties while able to withstand high temperatures making them ideal for durable label applications. They also demonstrate excellent dimensional stability and tensile strength.	-40° to 302°F	2	9	9	9	■	■	■	■	■		
Polyester Waterbased Inkjet Topcoat	Unique topcoat specifically designed for water-based inkjet printing provides outstanding print receptivity and abrasion resistance. Polyester films provide moisture barrier properties while able to withstand high temperatures making them ideal for durable label applications.	-40° to 302°F	2	8	8	8				■			■
Polyester TC	Polyester films provide moisture barrier properties while able to withstand high temperatures making them ideal for durable label applications. They also demonstrate excellent dimensional stability and tensile strength.	-40° to 302°F -20° to 257°F Clear only	2	9	9	8	■	■	■				
Polyester NTC	Optimal clarity for overlamine applications.	-20° to 257°F	2	9	9	8							
Polyethylene	High tear resistance and elongation, low tensile strength.	-20° to 140°F	10	3	7	4		■					
Polyolefin	Extremely pliable and conformable, moisture resistant. PVC-free vinyl alternative.	-40° to 140°F	9	7	7	3	■	■					
Polypropylene Waterbased Inkjet Topcoat	Unique topcoat specifically designed for water-based inkjet printing provides outstanding print receptivity and abrasion resistance. A conformable film that offers moisture resistance and durability even in outdoor conditions. Topcoat is water inkjet printable allowing for dynamic, durable, color on demand labels.	-40° to 140°F	8	7	8	7				■			■
Polypropylene, Label-Lyte® EDP	Outdoor UV durability up to one year. Excellent ink adhesion, good stiffness for auto application; excellent opacity.	-20° to 220°F	8	7	8	7	■	■					
Polypropylene, Label-Lyte® T2S	Outdoor UV durability up to one year. Excellent ink adhesion, good stiffness for auto application; excellent opacity.	-20° to 220°F	8	7	8	7	■	■					
Polypropylene T1S	Semi-hard film with high tear resistance and good dimensional stability.	-20° to 140°F	6	7	8	3		■					
Polypropylene EDP	Excellent opacity, moisture and tear resistance, excellent dimensional stability, resistant to cracking and abrasion, antistatic coating to eliminate double feeding when printing and folding.	-20° to 140°F	8	7	8	7	■	■		■			
Polypropylene TC, White, Clear or Metalized	High tensile strength, but notch sensitive.	-20° to 140°F	8	7	8	7		■					
Polystyrene, Matte and Gloss Clear	Economical, hard, rigid film. Tear and temperature sensitive. Not recommended for outdoor use.	-20° to 140°F	2	2	5	2		■					
Retro-Reflective Film	When bar code printed, the facestock extends the max. and min. scanning distance of long-range scanners.	-40° to 300°F	7	7	9	8	■						
Teslin®, Polyolefin	Durable alternative to paper labels, excellent abrasion properties.	-40° to 250°F	9	8	9	7		■		■			

*3M™ Durable Label Materials have been tested with various print systems with positive results. Print systems vary, so please request a sample and test in your specific application.

Values: 1 = Lowest Performance; 10 = Highest Performance

Rankings are a general guide. Adhesives should be tested with actual components to ensure acceptable performance.

For product recommendations or technical support, please call the Converter Markets Technical Support Line 1-800-223-7427.

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

Facestock Properties (cont.)

Facestock	Features	Film Properties	Processing Properties	Environmental Resistance to:			Print Method*						
		Service Temperatures	Conformability	Chemical	Moisture	Outdoor/UV	Thermal Transfer	Flexographic	UV Inkjet	Laser/Toner-Based	Screen	Solvent Inkjet	Water Inkjet
Vinyl (PVC) EDP, White	Conformability reduces as gauge increases. Multi-purpose film available in flexible, semi-rigid or rigid. Polymerically plasticized for dimensional stability. Handles outdoor conditions well. Will burn in flame, but should be self-extinguishing after removal. Low tear resistance. Available in medical grades.	-20° to 140°F	10	4	7	7	■	■		■			
Vinyl (PVC) NTC, White, Clear, Color or Translucent		-20° to 140°F	10	4	7	7							■
Vinyl (PVC) TC, White		-20° to 140°F	10	4	7	7	■	■					
Vinyl (PVC) TC2		-20° to 140°F	10	4	7	7		■					
Vinyl (PVC) TC3, White, Colors or Clear		-20° to 140°F	10	4	7	7		■					
Vinyl (PVC) TC6, White, Colors or Clear		-20° to 140°F	10	4	7	7	■	■					
Vinyl, Textured		-20° to 140°F	10	4	7	7	■	■		■	■		

Values: 1 = Lowest Performance; 10 = Highest Performance

Rankings are a general guide. Adhesives should be tested with actual components to ensure acceptable performance.

For product recommendations or technical support, please call the Converter Markets Technical Support Line 1-800-223-7427.

Liner Selection

Liner	Mil (nominal) Thickness	Description	Layflat	Semi Layflat	Back Side Printable	Fanfold	Roll-to-Roll
40# SC, 43# DK	2.4	Semi-bleached, super calendered/densified kraft sheet.			■		■
2.2 Glassine	2.2	Double sided glassine liner assures consistent die cutting. The backside release coating helps minimize label blocking.					■
3.0 Glassine	3.0	Double sided glassine liner assures consistent die cutting. The backside release coating helps minimize label blocking.				■	■
44# Polykraft	3.1	Polypropylene has been laminated to a 44# brown kraft sheet. Excellent caliper control and strength making it ideal for high-speed labeling applications.			■		■
50# SC, 55# DK	3.2	Semi-bleached, super calendered/densified kraft sheet designed for high-speed die-cutting and matrix stripping. Not recommended for sheet on press applications.			■		■
50# C2S	3.2	Back side has been lightly coated with silicone to reduce label pick. Recommended when using very soft adhesives or where heavy adhesive coat weights are required.					■
50# TL	3.4	Stabilized bleached kraft sheet with good caliper control. Ideal for most sheet-on-press applications. Back side is printable.		■	■	■	■
78# CCK, HL	4.6	Bleached, clay-coated kraft sheet. Excellent for sheet-on-press applications where additional strength and stiffness is required.		■	■	■	■
90# Polycoated	7.0	Bleached kraft sheet polyethylene-coated on two sides.	■				
1.5 Polyester	1.5	Clear polyester. Used when high strength and caliper control are important. Recommended for high-speed labeling applications or where clarity of the adhesive is critical.					■
4.0 Polyester	4.0	Clear polyester. Excellent for doming applications where ultimate lay flat is required.	■				

*3M™ Durable Label Materials have been tested with various print systems with positive results. Print systems vary, so please request a sample and test in your specific application.

The chart above is a general guide. Facestocks and adhesives should be tested with actual components to ensure acceptable performance.

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

Adhesive Families — Label Materials

100

100 High Temperature Acrylic

- Up to 450°F (232°C) short-term heat resistance and excellent solvent resistance
- High peel strength compared to other acrylic formulations
- Exceptional shear strength even at elevated temperatures
- Exhibits low outgassing characteristics

150

150 High Temperature Acrylic

- Up to 450°F (232°C) short-term heat resistance and excellent solvent resistance
- High internal strength ideal for applications on high surface energy plastics and metals

200MP

200MP High Performance Acrylic

- Up to 400°F (204°C) short-term heat resistance and excellent solvent resistance
- Outstanding adhesion to metal and high surface energy plastics
- Excellent shear strength to resist slippage and edge lifting
- Short-term repositionability for placement accuracy



300

300 High Strength Acrylic

- Up to 250°F (121°C) short-term heat resistance
- Greater initial adhesion especially to low surface energy plastics
- Quick flowing to speed lamination of textured plastics, foams, fabrics and coated papers



310

310 High Precision Acrylic

- Provides firmness and high precision strength on a variety of surfaces including HSE plastics and metals
- Compatible with a variety of print technologies including thermal transfer and laser printing

320

320 High Tenacity Acrylic

- Up to 250°F (11°C) short-term heat resistance
- High bond strength to a variety of surfaces
- Excellent flagging resistance on small diameter surfaces



350

350 High-Holding Acrylic

- Ideal for very high bond strength to many surfaces
- Most universal adhesive — ideal for powder coatings, LSE plastics and oily metals
- Up to 350°F (177°C) short-term heat resistance and excellent solvent resistance



400

400 Low Temperature Acrylic

- Good low temperature performance and peel strength on many surfaces
- Up to 250°F (121°C) short-term heat resistance
- Excellent adhesion to uncoated papers
- Clarity and UV resistance for window label applications

500

500 High Stability Acrylic

- Cleanly removes from most surfaces up to one year after application
- Excellent for die-cut masks needing outdoor performance and removability
- For vinyl label stocks only

1000 Series

1000 Series Repositionable Acrylic

- Good holding to many surfaces
- Clean removal or numerous reapplications
- Stain resistance on many surfaces

F2201

F2201 Freezer Acrylic

- Low 0°F (-18°C) application temperature, high initial tack
- Good moisture resistance
- Good long-term adhesion

Go-To Product

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

P1110

P1110 Permanent Rubber Based

- Excellent ultimate adhesion
- High initial tack
- Good choice for labeling LSE or waxy surfaces
- Good choice for toy labeling applications

P1212

P1212 General Purpose Acrylic

- Excellent clarity, good initial tack
- Excellent die-cutting properties
- Good UV resistance
- UL recognized for indoor use

P1400

P1400 High Performance Tackified Acrylic

- Excellent UV and moisture resistance
- Formulated for use in demanding environments
- Excellent adhesion to wide variety of substrates
- UL recognized for indoor/outdoor use

P1410

P1410 Tackified Acrylic

- High-tack
- Neutral pH
- Good adhesion to polyolefins

P1480

P1480 High Performance Tackified Acrylic

- High initial tack
- Good ultimate adhesion on a wide variety of surfaces
- Excellent choice for textured surfaces or powder coats
- Designed to meet difficult automotive underhood battery specifications

P1650

P1650 High Performance Acrylic

- Designed to meet difficult automotive underhood specifications
- Good chemical and moisture resistance
- Excellent thermal stability
- Resistance to many automotive and industrial fluids

P1655

P1655 White Opaque High Performance Acrylic

- Excellent opacity
- Designed to meet difficult automotive underhood specifications
- Excellent thermal stability

R3500

R3500 Ultra Removable Adhesive

- Good initial tack and long-term adhesion
- Multi-repositionable, static cling alternative
- Clean removability (no residue)

R3800

R3800 Ultra Removable Adhesive

- Good initial tack and long-term adhesion
- Clean removability (no residue)
- Lower tack version of Adhesive R3500

★ Go-To Product

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

Adhesive Selection Guide Based on Surface Energy


These charts are based on relative adhesion within each given surface energy category.

Metals	Surface Energy (Dynes/cm)
Copper	1103
Aluminum	840
Zinc	753
Tin	526
Lead	543


High Surface Energy (HSE) Plastics	Surface Energy (Dynes/cm)
Polyimide	50
Phenolic	47
Nylon®	46
Alkyd Enamel	45
Polyester	43
Epoxy Paint	43
Polyurethane	43
ABS	42
Polycarbonate	42
PVC	39
Modified PPE Resin	38
Acrylic	38
Polane® Paint	38

Low Surface Energy (LSE) Plastics	Surface Energy (Dynes/cm)
PVA	37
Polystyrene	36
Acetal	36
EVA	33
Polyethylene	31
Polypropylene	29
PVF	28
PTFE	18
Powder Coatings	Broad Range


Adhesive Performance on Metals



Adhesive Performance on High Surface Energy (HSE) Plastics



Adhesive Performance on Low Surface Energy (LSE) Plastics



Rankings are a general guide. Adhesives should be tested with actual components to ensure acceptable performance.

★ Go-To Product

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

Adhesive Properties

Adhesive Family	Temperature °F (°C)			Adhesive Properties			Adhesion to:			Environmental Properties Resistance to:		
	Minimum Application	Low Service	High Service	Initial Peel	Ultimate Peel	Convertibility	Metal	HSE Plastic	LSE Plastic	Chemical	Ultra Violet	Moisture
High Temperature Adhesives												
100	50 (10)	-40 (-40)	450 (232)	3	9	10	9	8	1	10	10	10
150	50 (10)	-40 (-40)	450 (232)	6	7	10	7	7	4	5	10	9
200MP	50 (10)	-40 (-40)	400 (204)	4	10	10	10	9	1	10	10	10
High Performance Adhesives												
300 ★	50 (10)	-40 (-40)	300 (149)	6	7	4	7	8	9	7	7	8
310 ★	50 (10)	-40 (-40)	300 (149)	5	6	6	7	7	5	7	7	8
350 ★	50 (10)	-40 (-40)	350 (177)	7	9	8	9	10	10	9	7	10
P1400	40 (4)	-20 (-29)	302 (150)	4	6	6	7	7	6	5	8	7
P1480 ★	40 (4)	-22 (-30)	300 (149)	6	8	4	8	8	9	7	5	7
P1650	40 (4)	-40 (-40)	302 (150)	6	7	4	8	7	8	7	5	7
General Purpose Adhesive												
P1212 ★	40 (4)	-20 (-29)	302 (150)	4	5	6	6	8	5	4	5	6
P1410	40 (4)	-20 (-29)	302 (150)	6	6	6	5	6	4	5	—	5
Specialty Adhesives												
320	50 (10)	-40 (-40)	250 (121)	7	7	6	7	7	7	6	6	8
400 ★	10 (-12)	-60 (-51)	250 (121)	5	5	6	5	5	5	5	10	8
F2201	0 (-18)	-40 (-40)	250 (121)	3	4	5	5	6	3	3	5	4
P1655	40 (4)	-40 (-40)	302 (150)	1	7	4	8	8	8	7	5	7
Rubber Based Adhesives												
P1110	55 (13)	-40 (-40)	155 (68)	6	7	4	8	9	9	3	3	3
Removable Adhesives												
500	50 (10)	-40 (-40)	175 (79)	4	5	3	5	7	4	5	10	10
1000 Series	50 (10)	-20 (-29)	250 (121)	2	3	7	3	1	1	2	5	3
R3500 ★	40 (4)	-20 (-29)	155 (68)	1	3	6	3	1	1	2	7	3
R3800	50 (10)	20 (-7)	155 (68)	1	3	6	3	1	1	2	7	2

Values: 1 = Lowest Performance; 10 = Highest Performance

Rankings are a general guide. Adhesives should be tested with actual components to ensure acceptable performance.

★ **Go-To Product**

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Durable Label Materials

3M™ Durable Label Materials — adhesives, topcoats, liners, and more — combine to keep messaging vibrant and legible for years, even in harsh conditions.

Facestock	Product	Typical Performance Characteristics	Construction		Print Method*							
			Caliper (mils)	Facestock Adhesive Type Liner	Thermal Transfer	Flexographic	UV Inkjet	Laser/Toner-Based	Screen	Solvent Inkjet	Water Inkjet	
Polyester Gloss White	V 7871V	High abrasion and solvent resistance. Excellent high temperature resistance and adhesion to LSE plastics and smooth powder coats. Broad applications in automotive, electronics, healthcare, heavy machinery, general industrial. Specialty applications in automotive EV battery, GHS drum labeling. BS5609 certified durable label.	2.0 1.8 3.2	PET, Versatile Print TC 350 55# Densified Kraft	■	■	■	■	■			
	7871VFL	Same product construction as 7871V label stock with film liner. Film liner provides smooth adhesive and resists tearing. Ideal for applications requiring automated dispensing.	2.0 1.8 1.5	PET, Versatile Print TC 350 Polyester Film	■	■	■	■	■			
	V 7868V	High abrasion and solvent resistance. Excellent high temperature resistance. Excellent adhesion to LSE plastics and smooth powder coats. BS5609 certified durable label.	2.0 1.1 3.2	PET, Versatile Print TC 350 55# Densified Kraft	■	■	■	■	■			
	V 7908V	High abrasion and solvent resistance. Heavy adhesive coat weight for textured surfaces. Excellent high temperature resistance. Excellent adhesion to LSE plastics and powder coats. 90# liner with layflat properties ideal for sheet and screen printing applications.	2.0 1.8 6.8	PET, Versatile Print TC 350 90# Polycoated Kraft	■	■	■	■	Ⓢ			
	7908FL	Same product construction as 7908V with thick polyester liner suitable for domed decals.	2.0 1.8 4.0	PET, Gloss White TC 350 Polyester Film	■	■	■		■			
	★ 7220SA	Adhesive allows releases trapped air to prevent bubbling for easy application of large format graphics. Ideal for applications where outgassing is a concern. High performance adhesive provides great adhesion to HSE and LSE surfaces, powder coated paint, and slightly oily metals. 90# liner with layflat properties ideal for sheet and screen printing applications.	2.0 1.1 6.8	PET, Gloss White TC 350 90# Polycoated Kraft	■	■	■			Ⓢ		
	7037	Same film as 7036 with aggressive adhesive for difficult substrates. 90# liner with layflat properties ideal for sheet and screen printing applications.	2.0 1.1 6.8	PET, White TC 350 90# Polycoated Kraft	■	■	■			Ⓢ		
	7907	350 adhesive for performance applications that require thermal transfer printing and demand adhesive performance on difficult to stick to surfaces (e.g. HSE plastics or powder coats). 90# liner with layflat properties ideal for sheet and screen printing applications.	2.3 1.8 6.8	PET, Matte White TC 350 90# Polycoated Kraft	■	■	■			Ⓢ		

*3M™ Durable Label Materials have been tested with various print systems with positive results. Print systems vary, so please request a sample and test in your specific application.

★ Go-To Product **V Versatile Print Label Materials** **Ⓢ 90# polycoated kraft liner is specifically designed for screen printing.**

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Durable Label Materials (cont.)

Facestock	Product	Typical Performance Characteristics	Construction		Print Method*							
			Caliper (mils)	Facestock Adhesive Type Liner	Thermal Transfer	Flexographic	UV Inkjet	Laser/Toner-Based	Screen	Solvent Inkjet	Water Inkjet	
Polyester Gloss White (cont.)	V 7331V	High abrasion and solvent resistance. Good for general purpose indoor and outdoor use. Excellent bond to LSE plastics. Applications include medical device and equipment, lawn and garden, and appliance.	2.0 0.8 3.2	PET, Versatile Print TC 300 55# Densified Kraft	■	■	■	■	■			
	7331FL	Same as 7331 label stock with film liner for automatic application equipment.	2.0 0.8 1.5	PET, White TC 300 Polyester Film	■	■	■					
	7931	High abrasion and solvent resistance. Good for indoor and outdoor use. Excellent bond to LSE plastics. 90# liner with layflat properties ideal for sheet and screen printing applications.	2.0 0.8 6.8	PET, Gloss White TC 300 90# Polycoated Kraft	■	■	■		Ⓢ			
	V 7816V	High abrasion and solvent resistance. Economical durable label material with firm adhesive to resist oozing.	2.0 0.8 3.2	PET, Versatile Print TC 310 55# Densified Kraft	■	■	■	■	■			
	7816FL	Offers excellent durability. Firm adhesive that resists oozing. Same as 7816 label stock with polyester liner.	2.0 0.8 1.5	PET, White TC 310 Polyester Film	■	■	■					
	7830/ 7864	Thin label profile provides good performance on small diameter packages. Excellent cold temperature performance. Good abrasion and chemical resistance.	1.0 0.8 3.2	PET, White TC 400 55# Densified Kraft	■	■	■					
	FM041902	Durable film facestock with aggressive, high-tack emulsion adhesive. Good adhesion to powder coats and heavily textured surfaces. Applications include automotive battery label and general industrial LSE labeling.	2.0 1.3 3.2	PET, White TC P1480 55# Densified Kraft	■	■	■					
	★ OFM03402	Glossy film label with excellent UV resistance and adhesion to a variety of substrates. Good choice for durable goods or lawn and garden applications.	2.0 0.9 3.2	PET, White TC P1400 50# Polycoated Kraft	■	■	■					
	7034	Glossy white film for use in general industrial applications. 90# liner with layflat properties ideal for sheet and screen printing applications.	2.0 0.9 6.8	PET, White TC P1400 90# Polycoated Kraft	■	■	■		Ⓢ			
8418	Ideal for fuel line identification. Intended for use with 8417 overlamine label material.	1.0 1.2 2.5	PET, White TC 100 43# Densified Kraft	■	■	■						

*3M™ Durable Label Materials have been tested with various print systems with positive results. Print systems vary, so please request a sample and test in your specific application.

Reliable tracking and identification.




Labeling needs vary. From durability to removability, indoor or outdoor use, 3M has a solution you can count on to go the distance and communicate important information.




★ Go-To Product **V Versatile Print Label Materials** **Ⓢ 90# polycoated kraft liner is specifically designed for screen printing.**

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Durable Label Materials (cont.)

Facestock	Product	Typical Performance Characteristics	Construction		Print Method*							
			Caliper (mils)	Facestock Adhesive Type Liner	Thermal Transfer	Flexographic	UV Inkjet	Laser/Toner-Based	Screen	Solvent Inkjet	Water Inkjet	
3M™ Water-based Inkjet Polyester	 7850-IJ	Topcoat uniquely designed for waterbased inkjet print systems. Durable facestock and adhesive stand up to harsh environments. Excellent high temperature resistance and adhesion to LSE plastics and smooth powder coats. Applications include medical device and equipment, heavy machinery.	3.0 1.1 3.2	PET, Waterbased Inkjet TC 350 55# Densified Kraft				■				■
	 7882-IJ	Topcoat uniquely designed for waterbased inkjet print systems. Durable facestock and adhesive stand up to harsh environments. Excellent cold temperature performance for a wide range of applications. Ideal for freezer or pharmaceutical applications.	3.0 0.8 3.2	PET, Waterbased Inkjet TC 400 55# Densified Kraft				■				
Polyester Matte White	 7246	Extreme durability topcoat. Eliminates the need for protective overlaminates in many applications. Excellent high temperature resistance and adhesion to LSE plastics and smooth powder coats.	2.2 1.8 2.2	PET TT3, Matte White 350 40# Densified Glassine	■	■						
	7874	Matte topcoated PET with high abrasion and solvent resistance for thermal transfer printed variable information. Excellent high temperature resistance and adhesion to LSE plastics and smooth powder coats. Broad applications in automotive, electronics, healthcare, heavy machinery and general industrial.	2.3 1.8 3.2	PET, White TT TC 350 50# SC	■	■						
	7850HL	Matte topcoat offers excellent ink anchorage for laser toner and dot-matrix printing. Excellent high temperature performance especially to LSE plastics and smooth powder coats. Clay-coated heavy liner ideal for laser printing applications.	2.3 1.1 4.6	PET, White Laser TC 350 78# CCK	■	■		■				
	7810	Features ultra smooth topcoat. Ideal for bar code applications. Good durability with a wide range of ribbons.	2.3 0.8 3.2	PET, White TT TC 300 55# DK	■	■						
	7880	Matte topcoat resists scuffing, chemicals and moisture. Excellent adhesion to LSE plastics.	2.3 0.8 3.2	PET, White DMI TC 300 55# Densified Kraft	■	■						
	7980	Matte topcoat resists scuffing, chemicals, and moisture. Excellent adhesion to smooth LSE plastics. 90# liner with layflat properties ideal for sheet and screen printing applications.	2.3 0.8 6.8	PET, Matte White TC 300 90# Polycoated Kraft	■	■				Ⓢ		

*3M™ Durable Label Materials have been tested with various print systems with positive results. Print systems vary, so please request a sample and test in your specific application.





Important messages need to be seen.

The right combination of adhesives, topcoats, liners and more — keeping messaging vibrant and legible for years, even in harsh conditions.

 **Go-To Product**  **Water-based Inkjet Label Materials**  **90# polycoated kraft liner is specifically designed for screen printing.**

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Durable Label Materials (cont.)




Facestock	Product	Typical Performance Characteristics	Construction		Print Method*							
			Caliper (mils)	Facestock Adhesive Type Liner	Thermal Transfer	Flexographic	UV Inkjet	Laser/Toner-Based	Screen	Solvent Inkjet	Water Inkjet	
Polyester Matte White (cont.)	7880HL	Heavy liner version of 7880 label stock for excellent liner stability in high humidity. Clay-coated heavy liner ideal for laser printing applications.	2.3 0.8 4.6	PET, White Laser TC 300 78# CCK	■	■		■				
	 7815	Features ultra smooth topcoat. Ideal for variable information applications. Good durability with a wide range of ribbons. Firm adhesive to resist oozing.	2.3 0.8 3.2	PET, White TT TC 310 50# SC	■	■						
	7815FL	Same product construction as 7815 label stock with polyester liner.	2.3 0.8 1.5	PET, White TT TC 310 Polyester Film	■	■						
	7840HL	Matte topcoat offers excellent ink anchorage for various digital printing technologies. Firm adhesive that resists oozing. Clay-coated heavy liner ideal for laser printing applications.	2.3 0.8 4.6	PET, White Laser TC 310 78# CCK	■	■		■				
	FM162	Dot-matrix imprintable film that also accepts thermal transfer print. General purpose adhesive bonds well to metals and HSE plastics.	2.0 0.9 3.2	PET, White EDP P1212 50# SC	■	■						
	FM034602	Micro-cavitated film with print receptive coating for use with most UV inkjet systems and thermal transfer printing. Designed for use in automotive applications. Excellent thermal stability.	2.0 1.3 3.2	PET, White MC P1650 50# SC	■	■	■					
	FM01961K	Specialized adhesive can be applied at temperatures as low as 0°F. Liner has special surface finish on the back side to enhance feed and reduce static problems. Excellent for drum labeling and laser printing applications.	2.0 0.8 4.6	PET, White MC F2201 78# CCK	■	■	■	■				
Polyester Gloss Clear	 7876V	High abrasion and solvent resistance. Heavy adhesive coat weight for textured surfaces. Excellent high temperature resistance. Excellent adhesion to LSE plastics and powder coats. Use where you need a printable, clear label with high performance adhesive.	2.0 1.8 3.2	PET, Versatile Print TC 350 55# Densified Kraft	■	■	■	■	■			
	7905	Heavy adhesive coat weight for textured surfaces. Excellent high temperature resistance. Excellent adhesion to LSE plastics and powder coats. 90# liner with layflat properties ideal for sheet and screen printing applications.	2.0 1.8 6.8	PET, Gloss Clear TC 350 90# Polycoated Kraft	■	■	■			Ⓢ		
	7350/ 7861	Offers high abrasion and solvent resistance. Excellent adhesion to LSE plastics. Ideal for indoor and outdoor applications.	2.0 0.8 3.2	PET, Clear TC 300 55# Densified Kraft	■	■	■					
	7350FL	Same as 7350 label stock with film liner for automatic application equipment.	2.0 0.8 1.5	PET, Clear TC 300 Polyester Film	■	■	■					
	7950	Offers high abrasion and solvent resistance. Excellent adhesion to smooth LSE plastics. Ideal for indoor and outdoor applications. 90# liner with layflat properties ideal for sheet and screen printing applications.	2.0 0.8 6.8	PET, Gloss Clear TC 300 90# Polycoated Kraft	■	■	■			Ⓢ		
	7831	Thin label profile provides good performance on small diameter packages. Excellent cold temperature performance.	1.0 0.8 3.2	PET, Clear TC 400 55# Densified Kraft	■	■	■					

*3M™ Durable Label Materials have been tested with various print systems with positive results. Print systems vary, so please request a sample and test in your specific application.

 **Go-To Product**  **Versatile Print Label Materials**  **90# polycoated kraft liner is specifically designed for screen printing.**

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Durable Label Materials (cont.)





Facestock	Product	Typical Performance Characteristics	Construction		Print Method*							
			Caliper (mils)	Facestock Adhesive Type Liner	Thermal Transfer	Flexographic	UV Inkjet	Laser/Toner-Based	Screen	Solvent Inkjet	Water Inkjet	
Polyester Gloss Clear (cont.)	 OFM3102	Durable film offers thermal stability and moisture resistance. Adheres to a variety of surfaces and offers excellent UV resistance.	2.0 0.9 3.2	PET, Clear TC P1400 50# SC	■	■	■					
	7029	Excellent UV resistance. Good adhesion to a variety of surfaces. 90# liner with layflat properties ideal for sheet and screen printing applications.	2.0 0.9 6.8	PET, Gloss Clear TC P1400 90# Polycoated Kraft	■	■	■		Ⓢ			
	FM042	High clarity emulsion adhesive with good initial tack and excellent die cutting properties. Adhesion to metals and HSE plastics.	2.0 0.9 3.2	PET, Clear TC P1212 50# SC	■	■	■					
Polyester Matte Clear	7881	Matte topcoat provides good chemical and abrasion resistance. Excellent adhesion to LSE plastics. Dot-matrix printable.	2.3 0.8 3.2	PET, Clear DMI TC 300 55# Densified Kraft	■	■						
	FM232	Matte film suitable for thin gauge label applications or as a printable overlaminated film. General purpose emulsion adhesive for HSE substrates.	1.0 0.8 3.2	PET, Clear TC P1212 50# SC	■	■	■					
Polyester Matte Silver	 7247	Extreme durability topcoat. Eliminates the need for protective overlaminates in many applications. Excellent high temperature resistance and adhesion to LSE plastics and smooth powder coats.	2.3 1.8 2.2	PET TT3, Matte Silver, 350 40# Densified Glassine	■	■						
	7879FL	Heavy adhesive coat weight for textured surfaces. Excellent adhesion to LSE plastics and powder coats.	3.3 1.8 1.5	PET, Silver TT TC 350 Polyester Film	■	■						
	7033	Aggressive adhesive for harsh environments. 90# liner with layflat properties ideal for sheet and screen printing applications.	2.0 1.1 6.8	PET, Matte Silver TC 350 90# Polycoated Kraft	■	■	■					
	7222/ 7865	Durable, moisture resistant film. Adhesive offers adhesion to a variety of surfaces, including LSE plastics. Applications include durable goods in an outdoor environment, instructional messaging and schematic panels.	2.0 0.8 3.2	PET, Matte Silver Gloss TC 300 55# Densified Kraft	■	■	■					
	7813	Ultra-smooth matte topcoat resists scuffing, chemicals and moisture. Excellent durability with a wide variety of ribbons. Excellent adhesion to LSE plastics.	3.3 0.8 3.2	PET, Silver Matte TT TC 300 55# Densified Kraft	■	■						
	7883	Matte topcoat ideal for dot matrix printing applications. Excellent adhesion to LSE plastics.	3.3 0.8 3.2	PET, Silver DMI TC 300 55# Densified Kraft	■	■						
	7883HL	Heavy liner version of 7883 label stock for excellent liner stability in high humidity.	3.3 0.8 4.6	PET, Silver DMI TC 300 78# CCK	■	■						
	 7818	Features ultra smooth matte topcoat, ideal for variable information applications. Good durability with a wide range of ribbons. Firm adhesive that resists oozing. Excellent durability.	3.3 0.8 3.2	PET, Silver TT TC 310 55# Densified Kraft	■	■						

*3M™ Durable Label Materials have been tested with various print systems with positive results. Print systems vary, so please request a sample and test in your specific application.

 **Go-To Product**  **90# polycoated kraft liner is specifically designed for screen printing.**

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Durable Label Materials (cont.)







Facestock	Product	Typical Performance Characteristics	Construction		Print Method*							
			Caliper (mils)	Facestock Adhesive Type Liner	Thermal Transfer	Flexographic	UV Inkjet	Laser/Toner-Based	Screen	Solvent Inkjet	Water Inkjet	
Polyester Matte Silver (cont.)	FM047202	Metalized film offers excellent thermal stability and moisture resistance. Quick tack high performance adhesive ideal for demanding applications, including powder coated paints.	2.0 1.2 3.2	PET, Matte Silver TC P1480 50# SC	■	■						
	 OFM2402	Durable, moisture resistant film. Adhesion to a variety of surfaces, including LSE plastics. Designed for use on durable goods in an outdoor environment.	2.0 0.9 3.2	PET, Matte Silver TC P1400 50# SC	■	■	■					
	FM092	Matte film with gloss topcoat. Adhesive offers good initial tack and excellent clarity and die cutting properties. Excellent choice for use in indoor nameplate applications.	2.0 0.9 3.2	PET, Matte Silver TC P1212 50# SC	■	■	■					
	FM043702	Thermal transfer printable topcoat. Designed for use in demanding environments including automotive underhood applications.	2.0 1.3 3.2	PET, Matte Silver TC P1650 50# SC	■	■	■					
Polyester Bright Silver	 7873V	High abrasion and solvent resistance. Heavy adhesive coat weight for textured surfaces. Excellent high temperature resistance. Excellent adhesion to LSE plastics and powder coats.	2.0 1.8 3.2	PET, Versatile Print TC 350 55# Densified Kraft	■	■	■	■	■			
	7340FL	Highly differentiated facestock uses proprietary 3M reflective film technology to produce a mirror-like finish without metalization. Luminous reflectivity >98%.	2.5 1.1 1.5	PET, Mirror Finish 350 Polyester Film	■	■						
	 7903V	High abrasion and solvent resistance. Good for indoor and outdoor use. Excellent bond to LSE plastics. 90# liner with layflat properties ideal for sheet and screen printing applications. Match a metallic look with gloss bright silver.	2.0 1.8 6.8	PET, Versatile Print PT 350 90# Polycoated Kraft	■	■	■	■		Ⓢ		
	7903FL	Print-treated bright silver polyester with film liner suitable for domed decals.	2.0 1.8 4.0	PET, Bright Silver PT 350 Polyester Film	■	■	■			■		
	7924	Excellent abrasion and chemical resistance. Excellent adhesion to smooth LSE plastics. Ideal for indoor and outdoor applications. 90# liner with layflat properties ideal for sheet and screen printing applications.	2.0 0.8 6.8	PET, Gloss Silver TC 300 90# Polycoated Kraft	■	■	■				Ⓢ	
	 7323V/ 7863V	High abrasion and solvent resistance. Good for indoor and outdoor use. Excellent bond to LSE plastics. Match a metallic look with gloss bright silver.	2.0 0.8 3.2	PET, Versatile Print TC 300 55# Densified Kraft	■	■	■	■	■			

*3M™ Durable Label Materials have been tested with various print systems with positive results. Print systems vary, so please request a sample and test in your specific application.

 Go-To Product  Versatile Print Label Materials  90# polycoated kraft liner is specifically designed for screen printing.

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Durable Label Materials (cont.)

Facestock	Product	Typical Performance Characteristics	Construction		Print Method*							
			Caliper (mils)	Facestock Adhesive Type Liner	Thermal Transfer	Flexographic	UV Inkjet	Laser/Toner-Based	Screen	Solvent Inkjet	Water Inkjet	
Polyester Bright Silver (cont.)	 OFM2802	Durable, moisture resistant film. Adhesion to a variety of surfaces, including LSE plastics. Designed for use on durable goods in an outdoor environment.	2.0 0.9 3.2	PET, Bright Silver TC P1400 50# SC	■	■	■					
	FM062	General purpose adhesive. Excellent die cutting properties.	2.0 0.9 3.2	PET, Bright Silver TC P1212 50# SC	■	■	■					
	9017FL	Bright silver with thick polyester liner suitable for domed decals. Thick, high-performance adhesive for durable graphic applications.	2.0 5.0 4.0	PET, Bright Silver PT 200MP Polyester Film	■	■	■		■			
Polyester Brushed Silver	 7909V	High abrasion and solvent resistance. 90# liner with layflat properties ideal for sheet and screen printing applications. Applications include heavy machinery, name plate, and safety labeling.	2.0 1.8 6.8	PET, Versatile Print TC 350 90# Polycoated Kraft	■	■	■	■	Ⓢ			
	 7214SA	Adhesive allows releases trapped air to prevent bubbling for easy application of large format graphics. Ideal for applications where outgassing is a concern. High performance adhesive provides great adhesion to HSE and LSE surfaces, powder coated paint, and slightly oily metals. 90# liner with layflat properties ideal for sheet and screen printing applications.	2.0 1.1 6.8	PET, Brushed Silver TC 350 90# Polycoated Kraft	■	■	■		Ⓢ			
	7028	Similar to 7909 with slightly lower coat weight for easier processing.	2.0 1.1 6.8	PET, Brushed Silver TC 350 90# Polycoated Kraft	■	■	■		Ⓢ			
	 OFM2902	Durable, moisture resistant film. Adhesion to a variety of surfaces, including LSE plastics. Designed for use on durable goods in an outdoor environment.	2.0 0.9 3.2	PET, Brushed Silver TC P1400 50# SC	■	■	■					
	9018FL	Brushed silver with thick polyester liner suitable for domed decals. Thick, high-performance adhesive for durable graphic applications.	2.0 5.0 4.0	PET, Brushed Silver PT 200MP Polyester		■			■			
	Polyester Platinum	 7872V	High abrasion and solvent resistance. Excellent high temperature resistance and adhesion to LSE plastics and smooth powder coats. Broad applications in automotive, electronics, healthcare, heavy machinery, general industrial. Differentiate your labels with a unique platinum metallic appearance.	2.0 1.8 3.2	PET, Versatile Print TC 350 55# Densified Kraft	■	■	■	■	■		
 7875V		High abrasion and solvent resistance. Durable label material with firm adhesive to resist oozing. Differentiate your labels with a unique platinum metallic appearance.	2.0 0.8 3.2	PET, Versatile Print TC 310 55# Densified Kraft	■	■	■	■	■			
Vinyl White	7904	Conformable to contoured surfaces. Excellent adhesion to LSE plastics and textured powder coats. 90# liner with layflat properties ideal for sheet and screen printing applications.	3.4 1.8 6.8	Soft White Vinyl NTC 350 90# Polycoated Kraft					Ⓢ	■		
	7605	Conformable to contoured surfaces. Excellent adhesion to LSE plastics and textured powder coats.	3.4 1.8 3.2	Soft White NTC 350 55# Densified Kraft	■	■						

*3M™ Durable Label Materials have been tested with various print systems with positive results. Print systems vary, so please request a sample and test in your specific application.

 **Go-To Product**  **Versatile Print Label Materials**  **90# polycoated kraft liner is specifically designed for screen printing.**

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Durable Label Materials (cont.)




Facestock	Product	Typical Performance Characteristics	Construction		Print Method*						
			Caliper (mils)	Facestock Adhesive Type Liner	Thermal Transfer	Flexographic	UV Inkjet	Laser/Toner-Based	Screen	Solvent Inkjet	Water Inkjet
Vinyl White (cont.)	7930T	Resists one-piece removal. Facestock fractures and tears easily. Excellent adhesion to powder coating, LSE plastics and oily metals. 90# liner with layflat properties ideal for sheet and screen printing applications.	2.0 0.8 6.8	White Destructible TC 350 90# Polycoated Kraft	■	■			Ⓢ		
	7053	Semi-flexible, non topcoated film. 90# liner with layflat properties ideal for sheet and screen printing applications.	4.0 1.1 6.8	Soft Clear Vinyl NTC 350 90# Polycoated Kraft					Ⓢ	■	
	7604FP	Topcoated, conformable to contoured surfaces. Consistent, high-speed dispensing. Excellent squeeze bottle performance.	3.5 1.2 3.2	Soft White TC3 300 55# Densified Kraft	■	■	■				
	7902	Non-topcoated. Conformable to contoured surfaces. 90# liner with layflat properties ideal for sheet and screen printing applications.	3.5 1.2 6.8	Soft White Vinyl NTC 300 90# Polycoated Kraft					Ⓢ	■	
	★ FV027805	Flexible film, ideal for printing with solvent, UV inkjet or UV flexo inks. High-tack and peel adhesive suitable for outdoor, textured LSE substrates. 90# liner with layflat properties ideal for sheet and screen printing applications.	3.2 1.1 6.8	Soft White Vinyl NTC P1480 90# Polycoated Kraft			■		Ⓢ	■	
	FV029405	Extended life, white vinyl offers durability and moisture resistance, and long-term dimensional stability for demanding applications. High performance tackified acrylic formulated for acid resistance and adhesion to polyolefins. 90# liner with layflat properties ideal for sheet and screen printing applications.	3.8 1.1 6.8	Soft White EL Vinyl P1480 90# Polycoated Kraft					Ⓢ	■	
	FV023202	High initial tack adhesive with good moisture resistance. Performs well in ladder label applications.	3.5 1.2 3.2	Soft White TC3 P1480 50# SC	■	■	■				
	7045	Non-topcoated film with good conformability. Excellent choice for curved surfaces. 90# liner with layflat properties ideal for sheet and screen printing applications.	3.2 0.9 6.8	Soft White Vinyl NTC P1400 90# Polycoated Kraft			■		Ⓢ	■	
	★ 7049	Non-topcoated film with good conformability. Excellent choice for curved surfaces. General purpose adhesive for a variety of surfaces. High performance adhesive. 90# liner with layflat properties ideal for sheet and screen printing applications.	3.8 0.9 6.8	Soft White EL Vinyl NTC P1400 90# Polycoated Kraft					Ⓢ	■	
	OFV0202	Designed for use in outdoor applications. Good adhesion to HSE and LSE plastics.	3.5 0.9 3.2	Soft White TC3 P1400 50# SC	■	■	■				
	FV032	Soft conformable vinyl that offers durability and moisture resistance. General purpose adhesive.	3.5 0.9 3.2	Soft White TC3 P1212 50# SC	■	■	■				
	FV172	Soft conformable translucent vinyl that has been topcoated for water-based flexo inks. High clarity general purpose adhesive.	3.5 0.9 3.2	Soft Translucent TC1 P1212 50# SC	■	■					
	FV018602	Topcoated black vinyl for press printing.	3.5 0.9 3.2	Soft Black Vinyl TC6 P1212 50# SC	■	■	■				
	FV292	Adheres to a variety of surfaces including polyolefins. Excellent choice for wire marking applications.	3.5 0.9 3.2	Soft White TC3 P1410 50# SC	■	■	■				

*3M™ Durable Label Materials have been tested with various print systems with positive results. Print systems vary, so please request a sample and test in your specific application.

★ Go-To Product Ⓢ 90# polycoated kraft liner is specifically designed for screen printing.

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Durable Label Materials (cont.)



Facestock	Product	Typical Performance Characteristics	Construction		Print Method*							
			Caliper (mils)	Facestock Adhesive Type Liner	Thermal Transfer	Flexographic	UV Inkjet	Laser/Toner-Based	Screen	Solvent Inkjet	Water Inkjet	
Vinyl White (cont.)	IJ39-20	Flexible film ideal for solvent or UV inkjet printable applications. High-tack and peel adhesive ideal for outdoor applications. Printed 3M™ Scotchcal™ 90# liner with layflat properties ideal for sheet and screen printing applications.	3.5 1.2 6.8	White Vinyl Permanent Acrylic 90# Polycoated Kraft						Ⓢ	■	
	7901	Non-topcoated. High bond, but offers clean removability on most surfaces for up to one year. Excellent for plasticizer resistance. 90# liner with layflat properties ideal for sheet and screen printing applications.	3.5 1.0 6.8	Soft White Vinyl NTC 500 90# Polycoated Kraft						Ⓢ	■	
Vinyl Cast	3690E+	Flexible and conformable white 3M™ Scotchcal™ Film with outstanding weathering properties. Non-transferable on some surfaces.	2.0 1.0 3.2	Bright White NTC 320 90g/sm glassine	■	■				■	■	
	3698E+	Flexible and conformable silver 3M™ Scotchcal™ Film with outstanding weathering properties. Non-transferable on some surfaces.	2.0 1.0 3.2	Matte Silver NTC 320 90g/sm glassine	■	■				■	■	
3M™ Water-based Inkjet Poly-propylene	 7790-IJ	Topcoat uniquely designed for waterbased inkjet print systems. Durable facestock and adhesive stand up to harsh environments. BS5609 certified durable label. Ideal for use in chemical drum labeling applications.	5.0 1.1 3.2	PP, Waterbased Inkjet TC 350 55# Densified Kraft					■			■
	 FP033-IJ	Topcoat uniquely designed for waterbased inkjet print systems. Durable facestock and adhesive stand up to harsh environments. Emulsion-based high performance LSE adhesive with high-tack for demanding applications. Broad applications in general industrial.	5.0 1.4 3.2	PP, Waterbased Inkjet TC P1480 50# SC					■			
Poly-propylene White	 7777	Bright white facestock offers high opacity. Film stiffness allows for easy die cutting and dispensing for automatic applications. Can be thermal transfer printed with resin ribbon.	2.6 0.9 3.2	Polypropylene Label Permanent Acrylic 50# Densified Kraft	■	■	■					
	7779	Same as 7777 except with 350 adhesive. Excellent adhesion to powder coats and LSE plastics.	2.6 1.1 3.2	Polypropylene Label 350 55# Densified Kraft	■	■						
	76716NA	Extreme durability when printed with 3M™ Durable Resin Ribbon 92904.	2.6 1.1 3.3	Polypropylene Film 350 55# Densified Kraft	■	■						

*3M™ Durable Label Materials have been tested with various print systems with positive results. Print systems vary, so please request a sample and test in your specific application.

 **Go-To Product**  **Water-based Inkjet Label Materials**  **90# polycoated kraft liner is specifically designed for screen printing.**

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Durable Label Materials (cont.)





Facestock	Product	Typical Performance Characteristics	Construction		Print Method*							
			Caliper (mils)	Facestock Adhesive Type Liner	Thermal Transfer	Flexographic	UV Inkjet	Laser/Toner-Based	Screen	Solvent Inkjet	Water Inkjet	
Poly-propylene White (cont.)	7776	Light-duty facestock with firm adhesive that resists oozing.	2.6 0.8 3.2	Polypropylene Label 310 55# Densified Kraft	■	■	■					
	FP022102	High performance adhesive designed for demanding LSE substrates. Matte film.	3.0 1.2 3.2	PP, EDP P1480 50# SC	■	■						
	 FP029102	High performance adhesive with high-tack and peel from difficult textured LSE plastics.	2.6 1.2 3.2	PP, TC2S P1480 50# SC	■	■	■					
	FP016102	Conformable moisture resistant film. Freezer-grade adhesive that can be applied at temperatures as low as 0°F.	2.3 0.8 3.2	PP, TC2S F2201 50# SC	■	■	■					
Poly-propylene Clear	FP102	General purpose adhesive offers excellent adhesion to a wide variety of substrates, including polyolefins.	2.0 0.9 3.2	PP, Clear TC P1410 50# SC	■	■	■					
Poly-propylene Metalized	FP032302	White opaque adhesive paired with metalized film offers exceptional opacity.	2.3 1.1 3.2	PP, Metalized TC P1655 50# SC	■	■	■					
Poly-ethylene	 FPE06602	Conformable film suitable alternative to vinyl label materials. Aggressive adhesive designed to adhere to both LSE and HSE surfaces.	2.5 1.1 3.2	White Polyethylene P1480 50# SC	■	■						
	FPE42	Conformable film suitable alternative to vinyl label materials. Aggressive adhesive designed to adhere to both LSE and HSE surfaces.	3.0 0.9 3.2	Clear Polyethylene P1410 50# SC	■	■						
Teslin®	7841	Excellent toner anchorage. Good conformability. Good print contrast when bar coding.	7.0 0.8 3.2	Matte White Teslin™ 310 55# Densified Kraft	■	■		■				

*3M™ Durable Label Materials have been tested with various print systems with positive results. Print systems vary, so please request a sample and test in your specific application.

Go-To Product

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Durable Label Materials (cont.)

Facestock	Product	Typical Performance Characteristics	Construction		Print Method*							
			Caliper (mils)	Facestock Adhesive Type Liner	Thermal Transfer	Flexographic	UV Inkjet	Laser/Toner-Based	Screen	Solvent Inkjet	Water Inkjet	
Paper	7004	Excellent quick stick and adhesion to low surface energy plastics.	4.0 0.9 2.5	60# Bright White High Gloss 300 43# Densified Kraft	■	■						
	 7000	High-gloss for fine printing. Adheres well to curved surfaces. Ideal for pharmaceutical applications.	4.0 0.9 2.5	60# White High Gloss 320 43# Densified Kraft	■	■						
	7000FL	Same as 7000 with film liner.	4.0 0.9 1.5	60# White High Gloss 320 Polyester Film	■	■						
	7011	Excellent flag resistance on small diameter vials. Used for unit dose pharmaceutical packages.	2.3 0.9 2.5	35# Coated Paper 320 43# Densified Kraft	■	■						
	7110	Readily fractures or delaminates. Ideal for tamper-resistant labeling. Provides write-on capability.	2.8 1.1 2.5	40# Uncoated Paper 320 43# Densified Kraft	■	■						
	 PS015402	Paper facestock with high performing adhesive for broad-based applications.	4.0 1.2 3.2	60# Semigloss P1480 50# SC	■	■						
	7142	Good thermal transfer printable facestock. Can be removed cleanly or repositioned on most substrates.	3.5 0.4 2.5	55# Coated Paper 1000 40# Kraft Glassine	■	■						
Acrylate	 7847	Two-layered film construction designed for laser etching provides excellent long-term durability for critical information.	2.4 1.2 3.2	Matte Black/White 350 55# Densified Kraft								
	 3921	Offers ultra-high temperature performance. Thermal transfer printable.	2.0 1.0 3.0	Matte White Acrylate 150 55# Densified Kraft	■	■						
	76999	Offers ultra-high temperature performance. Thermal transfer printable with un-branded liner.	2.0 0.8 3.2	Matte White Acrylate 150 C2S Glassine Liner	■	■						
Polyimide White	7812	Offers ultra-high temperature performance. Easy readability of bar codes. Thermal transfer printable.	2.0 2.0 3.2	Polyimide, Matte White 100 50# Densified Kraft	■							
Aluminum Foil Silver	7940	Vinyl topcoated for ink receptivity. Heavy adhesive coat weight suitable for textured surfaces. 90# liner with layflat properties ideal for sheet and screen printing applications.	2.0 1.7 6.8	Matte Silver TC 320 90# Polycoated Kraft		■				Ⓢ		
	7800	Vinyl topcoated for ink receptivity. Heavy adhesive coat weight suitable for textured surfaces. Excellent adhesion to LSE plastics.	2.0 1.7 3.0	Matte Silver TC 320 60# Densified Kraft		■				■		

*3M™ Durable Label Materials have been tested with various print systems with positive results. Print systems vary, so please request a sample and test in your specific application.

 Go-To Product  90# polycoated kraft liner is specifically designed for screen printing.

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Removable Label Materials

Facestock	Product	Typical Performance Characteristics	Construction		Print Method*							
			Caliper (mils)	Facestock Adhesive Type Liner	Thermal Transfer	Flexographic	UV Inkjet	Laser/Toner-Based	Screen	Solvent Inkjet	Water Inkjet	
Polyester White	FM01972	Matte film that offers thermal stability. Suitable for masking applications.	2.0 0.8 3.2	PET, White MC R3500 50# SC	■	■						
	FM1732R	Thermal transfer printable with resin ribbons. Removable from a variety of surfaces.	2.0 0.8 3.2	PET, White TC R3500 50# SC	■	■	■					
Vinyl White	★ 7600	Top-coated, high bond, but offers clean removability on most surfaces for up to one year. Excellent for plasticizer resistance. Key applications include automotive masking, outdoor removable.	3.5 1.0 2.5	Soft White Gloss TC 350 43# Densified Kraft	■	■	■					
	FV1222	Soft conformable vinyl that offers long-term adhesion with clean removability.	3.5 0.8 3.2	Soft White Vinyl TC3 R3500 50# SC	■	■	■					
Polypropylene White	★ FP016902	Good conformability and removability from a variety of surfaces. Excellent alternative to static cling.	2.3 0.8 3.2	PP, White TC2S R3500 50# SC	■	■	■					
Polypropylene Clear	FP56N	Clear conformable label offers long-term adhesion with clean removability. Excellent alternative to static cling with film liner for high speed dispensing.	2.0 0.8 1.5	PP, Clear TC2S R3500 Polyester Film	■	■	■					
	★ FP0862	Clear conformable label offers long-term adhesion with clean removability. Excellent alternative to static cling.	2.0 0.8 3.2	PP, Clear TC2S R3500 50# SC	■	■	■					
	FP024402	Specially formulated adhesive designed to be easily removable from a variety of surfaces. Offers lower peel and tack than R3500 adhesive.	2.0 0.8 3.2	PP, Clear TC2S R3800 50# SC	■	■	■					

*3M™ Durable Label Materials have been tested with various print systems with positive results. Print systems vary, so please request a sample and test in your specific application.

Stable, clean removal — even outdoors.




Select your range of strength, stability, adhesion and removability. These label materials feature our specially formulated acrylic adhesives, which include 3M™ Removable Adhesive 500 for stable, clean removal even during long-term outdoor applications. 3M™ Removable Adhesive R3500 is for use on smooth surfaces such as glass and plastics. Liners provide added versatility during processing such as die cutting, laminating and kiss cutting.




★ Go-To Product

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Tamper Evident Label Materials

Facestock	Product	Typical Performance Characteristics	Construction		Print Method*							
			Caliper (mils)	Facestock Adhesive Type Liner	Thermal Transfer	Flexographic	UV Inkjet	Laser/Toner-Based	Screen	Solvent Inkjet	Water Inkjet	
Destructible Facestocks	 7613T	Resists one-piece removal. Facestock fractures and tears easily. Excellent adhesion to powder coating, LSE plastics and oily metals.	2.0 0.8 3.2	White Vinyl TC 350 55# Densified Kraft	■	■	■					
	7930T	Same as 7613T, except with 90# polycoated kraft liner.	2.0 0.8 6.8	White Vinyl TC 350 90# Polycoated Kraft	■	■	■		Ⓢ	■		
	 3812	This destructible, non-shrink white film is designed as a non-removable security label. Once applied in a correct manner, one-piece removal is not possible on most surfaces.	1.6 1.2 3.2	Urethane, Matte White 350 Glassine	■	■	■					
	7110	Readily fractures or delaminates. Ideal for tamper-resistant labeling. Handwritable.	2.8 1.1 2.5	40# Uncoated White Paper 320 43# Densified Kraft	■	■						
	FA112	High-quality film resists one piece removal, fractures easily. Good initial tack adhesive.	2.0 0.9 3.2	Clear Acetate P1212 50# SC		■						
Polyester Tamper Indicating Films	7380	Tamper evident VOID. Ideal for security rating plates and certification plates.	2.3 0.8 3.2	Matte White VOID DMI TC 300 55# Densified Kraft	■	■						
	 7381/7866	Used for closures in packaging of OTC drugs. Facestock resists harsh environments.	2.0 0.8 3.2	Gloss White VOID TC 300 55# Densified Kraft	■	■	■					
	7384	Tamper evident VOID. Mirror finish hides security feature. Ideal for security closure seal.	2.0 0.8 3.2	PET, Bright Silver TC 300 55# Densified Kraft	■	■	■					
	7935	Facestock resists harsh environments. 90# liner with layflat properties ideal for sheet and screen printing applications.	2.0 0.8 6.8	Gloss White VOID TC 300 90# Polycoated Kraft	■	■	■	■	Ⓢ			
	7937	Ideal for security rating plates and certification plates. 90# liner with layflat properties ideal for sheet and screen printing applications.	2.3 0.8 6.8	Matte White VOID DMI TC 300 90# Polycoated Kraft	■	■	■	■	Ⓢ			
	FMV22	Thermal transfer printable VOID label. General purpose adhesive offers excellent adhesion to a wide variety of substrates, including polyolefins.	2.0 0.9 3.2	White VOID TC P1410 50# SC	■	■	■					

*Can be used to display the UL listing mark, but each case must be reviewed and approved by UL follow-up services before use.



Peace of mind you can readily see.

3M™ Tamper Evident Labels fracture from many surfaces when label removal is attempted, providing security and peace of mind. Tamper evident options include “void” messages, triangle shapes, or destructible facestocks. These tamper evident security labels feature adhesives that provide permanent or non-permanent markings on numerous substrates.

 **Go-To Product**  **90# polycoated kraft liner is specifically designed for screen printing.**

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Overlamine Label Materials

Facestock	Product	Typical Performance Characteristics	Construction		Print Method*						
			Caliper (mils)	Facestock Adhesive Type Liner	Thermal Transfer	Flexographic	UV Inkjet	Laser/Toner-Based	Screen	Solvent Inkjet	Water Inkjet
Polyester Gloss Clear	★ 7730FL	Non-topcoated. Film liner offers excellent graphic appearance. Excellent durability and UV resistance.	1.0 0.8 1.5	PET, Clear NTC 400 Polyester Film							
	7731FL	Non-topcoated. Same as 7730FL, except with 2.0 mil facestock.	2.0 0.8 1.5	PET, Clear NTC 400 Polyester Film							
	★ 7733FL	Ideal for long-term outdoor applications. Special UV resistant film provides 3 years outdoor durability.	1.0 0.8 1.5	PET, Clear UV 400 Polyester							
	7741	Non-topcoated. Excellent abrasion, chemical, and UV resistance.	1.0 0.8 2.5	PET, Clear NTC 400 43# Densified Kraft							
	8417	Non-topcoated. Solvent resistant and high heat tolerance. Ideal for fuel line identification. Intended for use with 8418.	1.0 1.2	PET, Clear NTC 100							
	OFM010N	Excellent UV resistance. Designed for indoor and outdoor overlaminating applications.	1.0 0.8 1.5	PET, Clear NTC P1400 Polyester Film							
	★ FM011	Basic polyester overlaminating film with high clarity adhesive.	1.0 0.8 2.5	PET, Clear NTC P1212 40# SC							
	FM452	Heavy gauge durable non-topcoated film designed for overlaminating applications. Abrasion resistant. Designed for indoor applications.	5.0 0.9 3.2	PET, Clear NTC P1212 50# SC							
	FM45N	Same as FM452 with a film liner for ultimate adhesive clarity.	5.0 0.9 1.5	PET, Clear NTC P1212 Polyester Film							
Polyester Matte Clear	7732FL	Non-topcoated. Film liner offers excellent graphic appearance. Excellent durability and UV resistance.	1.0 0.8 1.5	PET, Matte NTC 400 Polyester Film							
	7742	Non-topcoated. Excellent abrasion, chemical, and UV resistance.	1.0 0.8 2.5	PET, Matte NTC 400 43# Densified Kraft							
	★ 7744FL	Thermal transfer printable matte topcoat. Ideal where variable information is needed. Film liner provides smoother adhesive appearance.	1.3 0.8 1.5	PET, Matte TT TC 400 Polyester Film	■	■	■				
	7745FL	Higher matte finish than 7744FL. Can be used in laser and handwritable applications.	1.3 0.8 1.5	PET, Matte DMI TC 400 Polyester Film	■	■				■	
	FM071	Matte clear film for general purpose overlaminating applications.	1.0 0.8 2.5	PET, Matte NTC P1212 40# SC							

*Can be used to display the UL listing mark, but each case must be reviewed and approved by UL follow-up services before use.

Designed for superior label protection.

These 3M materials offer UV and high temp resistance which help to prevent color fading. The adhesive is formulated for bonding to challenging substrates. Densified and supercalendered kraft and polyester film liners make for efficient die cutting and auto dispensing. The durable facestocks resist abrasion, scuffs and weathering.



★ Go-To Product

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Overlamine Label Materials (cont.)

Facestock	Product	Typical Performance Characteristics	Construction	
			Caliper (mils)	Facestock Adhesive Type Liner
Acrylate Clear	★ 7735FL	Ideal for long-term outdoor applications. Special UV resistant film and adhesive provides 10 years outdoor durability.	3.0	Matte Acetate 400 Polyester Film
			0.8	
			1.5	
Acrylic Clear	8524	Clear satin overlamine for outdoor applications. Ideal for use with 3M™ Scotchcal™ IJ8624. Resists acids, mild alkalis, and salts.	2.0	UV Resistant Film P1212 50# SC
			0.9	
			3.2	
Vinyl Clear	FV02490N	Textured vinyl film is an alternative to polycarbonate for less demanding applications. High clarity adhesive with good initial tack and excellent die cutting properties.	5.0	Textured Vinyl NTC P1212 Polyester Film
			0.9	
			1.5	
Polycarbonate Clear	7737FL	Used to achieve the appearance of a subsurface screen printed polycarbonate.	3.0	Velvet Clear Lexan™ 400 Polyester Film
			0.8	
	7738FL	Same as 7737FL, except with 5.0 mil facestock.	5.0	Velvet Clear Lexan™ 400 Polyester Film
			0.8	
	FL01N	Liner offers high strength and caliper control. Recommended where the clarity of the adhesive is critical.	5.0	Velvet Clear Lexan™ P1212 Polyester Film
1.1				
1.5				
FL02N	Similar to 7737FL. Designed for indoor use.	3.0	Velvet Clear Lexan™ P1212 Polyester Film	
		1.1		
OFL010N	Specialty durable polycarbonate overlamine. High performance adhesive formulated for demanding applications. Adheres to a variety of surfaces. Excellent UV resistance.	3.0	Velvet Clear Lexan™ P1400 Polyester Film	
		1.0		
			1.5	

3M™ Specialty Label Materials

Facestock	Product	Typical Performance Characteristics	Construction		Print Method*						
			Caliper (mils)	Facestock Adhesive Type Liner	Thermal Transfer	Flexographic	UV Inkjet	Laser/Toner-Based	Screen	Solvent Inkjet	Water Inkjet
Automotive Applications: EV Battery Label Materials											
Polyester	V 7871V	High abrasion and solvent resistance. Excellent high temperature resistance and adhesion to LSE plastics and smooth powder coats. Specialty applications in automotive EV battery, GHS drum labeling. BS5609 certified durable label.	2.0	PET, Versatile Print TC 350 55# Densified Kraft	■	■	■	■	■		
			1.8								
			3.2								
Polyethylene	FPE06602	Conformable film suitable alternative to vinyl label materials. Aggressive adhesive designed to adhere to both LSE and HSE surfaces.	2.5	White Polyethylene P1480 50# SC	■	■					
			1.1								
			3.2								

*3M™ Durable Label Materials have been tested with various print systems with positive results. Print systems vary, so please request a sample and test in your specific application.

★ Go-To Product V Versatile Print Label Materials

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Specialty Label Materials (cont.)

Facestock	Product	Typical Performance Characteristics	Construction		Print Method*						
			Caliper (mils)	Facestock Adhesive Type Liner	Thermal Transfer	Flexographic	UV Inkjet	Laser/Toner-Based	Screen	Solvent Inkjet	Water Inkjet
Automotive Applications: VIN Label Material											
Acrylate	7847	Two-layered film construction designed for laser etching provides excellent long-term durability for critical information.	2.4	Matte Black/White 350 55# Densified Kraft							
			1.2								
			3.2								
Automotive Applications: Tire Label Materials											
Polypropylene	FP019802	Non-patterned tire tread label material with rubber based adhesive. Ideal for automated applications.	2.6	PP, T2S P1110 50# SC							
			1.5								
			3.2								
Teslin	FTS0700	Bead label for	7.0	Teslin P1110 50# SC							
			1.5								
			3.2								

*3M™ Durable Label Materials have been tested with various print systems with positive results. Print systems vary, so please request a sample and test in your specific application.

Extreme bonding to treated rubber.

3M™ Tire Label Materials are designed specifically for tire labeling. Our 3M™ Adhesive P1100 are permanent, rubber-based, pressure-sensitive adhesives designed for performance on vented and non-vented tire treads.



Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Specialty Label Materials (cont.)

Facestock	Product	Typical Performance Characteristics	Construction		Print Method*						
			Caliper (mils)	Facestock Adhesive Type Liner	Thermal Transfer	Flexographic	UV Inkjet	Laser/Toner-Based	Screen	Solvent Inkjet	Water Inkjet
3M™ Specialty Health Care Applications											
3M™ Versatile Print Polyester, Gloss White	V 7331V	High abrasion and solvent resistance. Good for indoor and outdoor use. Excellent bond to LSE plastics. Ideal for medical device applications.	2.0	PET, Versatile Print TC 300 55# Densified Kraft	■	■	■	■	■		
			0.8								
			3.2								
3M™ Water-based Inkjet Polyester	B 7882-IJ	Excellent cold temperature performance for a wide range of applications. Ideal for freezer or pharmaceutical applications.	3.0	PET, Waterbased Inkjet TC 400 55# Densified Kraft				■			■
			0.8								
			3.2								
Paper	★ 7000	High-gloss for fine printing. Adheres well to curved surfaces. Ideal for pharmaceutical applications.	4.0	60# White High Gloss 320 43# Densified Kraft	■	■	■				
			0.9								
			2.5								
	7000FL	Same as 7000 with film liner.	4.0	60# White High Gloss 320 Polyester Film	■	■	■				
			0.9								
			1.5								
Litho Tamper-Indicating White	7110	Readily fractures or delaminates. Ideal for tamper-resistant labeling. Handwritable.	2.8	40# Uncoated Paper 320 43# Densified Kraft	■	■					
			1.1								
			2.5								
	7011	Excellent flag resistance on small diameter vials. Ideal for unit dose pharmaceutical packages.	2.3	35# Coated Paper 320 43# Densified Kraft	■	■					
			0.9								
			2.5								
Polyolefin	FP035402	Offers excellent durability, conformability and moisture resistance. Ideal for blood bag applications.	3.3	Matte White Polyolefin P1650 50# SC	■	■					
			1.3								
			3.1								

*3M™ Durable Label Materials have been tested with various print systems with positive results. Print systems vary, so please request a sample and test in your specific application.



Meeting the demands of Health Care applications.

A range of adhesives makes for reliable performance without flagging on small diameter plastic vials, in autoclaves and where tamper evidence is a main concern.

★ Go-To Product V Versatile Print Label Materials B Water-based Inkjet Label Materials

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

Single Coated Tapes

Everyday task masters.

High temperatures or low. Indoor or outdoor.
There's a 3M tape for masking, splicing, holding,
sealing, bundling and marking.

Learn more at:
3M.com/Specialty

3M™ Anodizing Masking Tape 8985L

Survives chromic acid
with excellent masking
lines and clean
one-piece removal.



Selecting the right product for the job.

To help you make sure you find the optimum 3M tape or other adhesive-backed product for your particular application, you'll want to consider several factors:

- Backing material
- Adhesive type
- Application time and temperature
- Surface characteristics (e.g., roughness, surface energy, contours, etc.)
- End use conditions (e.g., temperature, UV exposure, abrasion, etc.)

The information on these two pages integrates those factors to help you narrow your selection to fewer products for a more in-depth evaluation.

3M Backing Materials

In many applications, 3M backings add a second surface that affects how the underlying surface relates to the environment.

To optimize that relationship, 3M backings offer a wide choice of performance and handling characteristics.

3M Pressure Sensitive Adhesives

Most of the products in this section feature a 3M pressure sensitive adhesive that bonds the backing to another surface on contact. Each adhesive has different characteristics that affect production and end use performance.

Backings	Characteristics
Paper	
Crepe	Conformable, easy tear.
Flatback	Strong, smooth, good for straight line masking.
Kraft	Strong, some versions are repulpable.
Tissue	Thin, porous to allow adhesive penetration of sheet.
Plastic	
Polyester	Strong even when thin, chemical resistant, high temperature resistance.
Polypropylene	Resistant to most solvents, conformable, tear resistant.
Polyethylene	Conformable, easy to stretch, chemical/acid/moisture resistant, economical.
Polyethylene/Polypropylene Co-polymer	Conformable, chemical/acid/moisture resistant.
UHMW-PE	High abrasion resistance, low coefficient of friction, anti-stick surface easy to clean.
Polyvinyl Chloride (Vinyl)	Conformable, abrasion resistant, resistant to most chemicals.
Polyimide	High temperature resistance, excellent dimensional stability, good insulation properties.
Polyamide (Nylon)	High temperature resistance, high strength and toughness, good chemical resistance but can absorb moisture.
Polytetrafluoroethylene (PTFE)	Low coefficient of friction, excellent high temperature and chemical resistance, anti-stick/release properties.
Polyvinyl Alcohol (PVA)	Water-soluble, organic solvent resistant, high temperature resistance.
Polyurethane	Abrasion/scratch resistant, impact/puncture resistant, UV and corrosion resistant.
Polyvinyl Fluoride	Excellent weather resistance, excellent long-term UV resistance, thin yet stiff feel.
Cloth	
Cotton	Strong, easy tear by hand, soft and drapable.
Glass Cloth	Strong, high temperature resistance, flame-resistant.
Vinyl Coated	Strong yet hand tearable, abrasion resistant, water-resistant, conformable.
Non-woven	
Fiber	Air permeable, strong enough to hold expanding foams.
Metals	
Aluminum	Heat and light reflective, moisture and chemical resistant, flame-resistant, outdoor weather resistant, conformable.
Copper	EMI/RFI shielding.
Lead	Electrically conductive, acid resistant, high conformability, x-ray opacity.
Stainless Steel	Corrosion resistant.
Rubber	
Neoprene	Abrasion resistant, die-cuttable
Combination (Laminates)	
Paper/Polyethylene	Weather and chemical resistant, hand tearable, stretch resistant.
Metalized/Polyester	Reflective, decorative.
Glass Cloth/PTFE	High temperature resistance, high strength.
Glass Cloth/Aluminum	Very high temperature resistance, high strength.
Non-woven/Aluminum	High heat and cold resistance.

Adhesives			
Rubber	Standard Acrylic	Modified Acrylic	Silicone
High initial bond	Moderate initial bond	Bonds to wider variety than standard acrylic	Fair initial bond
Softer	Firmer	Softer	Very firm
Widest variety of surfaces including low surface energy materials*	High surface energy*	Many surfaces	Fewer surfaces
Up to 350°F	Up to 450°F	Up to 300°F	Up to 600°F, excellent low temperature performance
Fair chemical resistance	Excellent chemical resistance	Good chemical resistance	Excellent chemical resistance
Fair UV resistance	Excellent UV resistance	Moderate UV resistance	Excellent UV resistance
Poor aging	Excellent aging	Durable	Excellent aging
Removable	Permanent	Various	Removable
Good solvent resistance	Excellent solvent resistance	Good solvent resistance	Excellent solvent resistance

*Surface energy ranges from high to low. The substrate must be unified, dry, and clean to maximize adhesive contact.

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

Selecting the best backing and adhesive.

Backings: Each Backing is Rated in Eight Critical Categories

Key to Charts 1–8

- PVC=Polyvinylchloride
- PE=Polyethylene
- PET=Polyester
- MF=Metal Foil
- PTFE=Polytetrafluoroethylene
- GC=Glass Cloth

Chart 1. Backings Thickness (Caliper)




Chart 2. Temperature Range Tape Backings




Chart 3. Conformability of Backings




Chart 4. Backing Cost




Chart 5. Backings as Moisture Barriers




Chart 6. Chemical Resistance of Backings




Chart 7. Solvent Resistance of Backings





Chart 8. Resistance to Recovery (Dead Stretch)



Adhesives: Each Adhesive is Rated in Five Critical Categories

Key to Charts 9–13

- R=Rubber Adhesive
- A=Acrylic Adhesive
- S=Silicone Adhesive

Chart 9. Initial Tack




Chart 10. Ultimate Adhesion to Steel




Chart 11. Temperature Ranges of Adhesives




Chart 12. Long-Aging Capabilities







Chart 13. Cost of Adhesives



Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.


3M™ Single Coated Tapes

Material (alphabetical order)	Product	Typical Performance Characteristics/ Application Ideas	Color	Total Caliper mils (mm)	Backing		Adhesive Type	Specs	Temperature Range °F (°C)
					Material	Caliper mils (mm)			
Premium Performance Aluminum Foil Tape	363/ 363L	An aluminum foil/glass cloth tape that can be used as a high temperature, heat reflective, protective wrap for certain cables and other components in aerospace and industrial applications. 363L is lined version.	Silver	7.3 (0.19)	Aluminum Foil Laminated to Glass Cloth	3.4 (0.09)	Silicone	F.A.R. 25.853(a)	-65 to 600 (-54 to 316)
	 425	Dead-soft aluminum foil tape. Masking of sensitive components to protect from damage during aircraft paint stripping. In white goods appliances, tape provides an excellent moisture barrier, helps reflect and dissipate heat.	Silver	4.6 (0.12)	Aluminum Foil	2.8 (0.07)	Acrylic	F.A.R. 25.853(a); SAE AMS T-23397; UL 723; UL 746C; LT-80 C	-65 to 300 (-54 to 149)
	427	Dead-soft aluminum foil tape. Lined version of 425 that can be easily die-cut into special sizes or shapes. Mask sensitive components to protect from damage during paint stripping or reflect and dissipate heat.	Silver	4.6 (0.12)	Aluminum Foil	2.8 (0.07)	Acrylic	F.A.R. 25.853(a); UL 723; UL 746C; LT-80 C	-65 to 300 (-54 to 149)
	431	Dead-soft aluminum foil with transparent acrylic adhesive for many permanent sealing, holding, splicing or masking applications requiring the protection offered by a foil backing.	Silver	3.1 (0.08)	Aluminum Foil	1.9 (0.05)	Acrylic	F.A.R. 25.853(a)	-65 to 300 (-54 to 149)
	433	Dead-soft aluminum foil backing with silicone adhesive that can be used in many high temperature applications.	Silver	3.6 (0.09)	Aluminum Foil	2.0 (0.05)	Silicone	F.A.R. 25.853(a); US Gov A-A-59258; MIL-T-47014	-65 to 600 (-54 to 316)
	433L	Lined version of 433.	Silver	3.5 (0.09)	Aluminum Foil	2.0 (0.05)	Silicone	F.A.R. 25.853(a)	-65 to 600 (-54 to 316)
	437	Dead-soft aluminum foil tape. Aggressive acrylic adhesive.	Silver	8.0 (0.20)	Aluminum Foil	2.8 (0.07)	Acrylic	—	-40 to 212 (-40 to 100)
	438	Thickest aluminum tape.	Silver	7.2 (0.18)	Aluminum Foil	5.0 (0.13)	Acrylic	F.A.R. 25.853(a)	-65 to 300 (-54 to 149)
	439	Lined version of 431.	Silver	3.1 (0.08)	Aluminum Foil	1.9 (0.05)	Acrylic	F.A.R. 25.853(a)	-65 to 300 (-54 to 149)
General Purpose Aluminum Foil Tape	3302	Aluminum foil tape. EMI/RFI shielding. Perforated.	Silver	3.5 (0.09)	Aluminum Foil	2.0 (0.05)	Conductive Acrylic	UL 510	-40 to 250 (-40 to 12)
Aluminum Sound Damping Foil	434	Aluminum foil constraining layer coated with a 2.0 mil (0.05mm) pressure sensitive viscoelastic polymer on a blue polyethylene easy-release liner. Controls resonant vibrations from -76°F to 68°F (-60°C to 20°C).	Silver	7.5 (0.19)	Aluminum	5.5 (0.14)	Viscoelastic Polymer	F.A.R. 25.853(a)	—
	435	Thicker version of 434. Controls resonant vibrations from -76°F to 68°F (-60°C to 20°C).	Silver	13.5 (0.34)	Aluminum	8.0 (0.2)	Viscoelastic Polymer	F.A.R. 25.853(a)	—
	436	Aluminum foil constraining layer coated with a 5.5 mil (0.14mm) pressure sensitive viscoelastic polymer on a blue polyethylene easy-release liner. Controls resonant vibrations from -76°F to 68°F (-60°C to 20°C).	Silver	17.5 (0.45)	Aluminum	12.0 (0.31)	Viscoelastic Polymer	F.A.R. 25.853(a)	—
	 2552	Aluminum foil constraining layer coated with a 5.0 mil (0.13mm) pressure sensitive viscoelastic polymer on a polycoated paper easy-release liner. Controls resonant vibrations from -25°F to 175°F (-32°C to 80°C).	Silver	15.0 (0.38)	Aluminum	10.0 (0.25)	Viscoelastic Polymer	F.A.R. 25.853(a)	—
	4014	Foil/foam sheet laminate.	Silver	250.0 (6.35)	Aluminum- Urethane	3.0 (0.08)	Viscoelastic Polymer	F.A.R. 25.853(a)	—

 **Go-To Product**

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Single Coated Tapes (cont.)

Material (alphabetical order)	Product	Typical Performance Characteristics/ Application Ideas	Color	Total Caliper mils (mm)	Backing		Adhesive Type	Specs
					Material	Caliper mils (mm)		
Fiberglass Cloth	 361	Glass cloth tape coated with a silicone adhesive for many applications requiring high temperature resistance, high adhesion and a very strong abrasion-resistant backing.	White	6.4 (0.16)	Glass Cloth	5.0 (0.13)	Silicone	F.A.R. 25.853
	3615	An easy unwind glass tape for many applications requiring high temperature resistance, high adhesion, and a very strong abrasion-resistant backing.	White	7.0 (0.18)	Glass Cloth	5.0 (0.13)	Silicone	—
	365	Splicing textured surfaces/thermosetting adhesive.	White	8.3 (0.20)	Glass Cloth	4.8 (0.12)	Thermoset Rubber	—
	3650	Splicing textured surfaces/thermosetting adhesive. Film lined version of 365.	White	8.3 (0.20)	Glass Cloth	4.8 (0.12)	Thermoset Rubber	—
	398FR	Glass cloth film tape with acrylic adhesive. Used for sealing seams on aircraft ducting and cargo area panels. Flame retardant. Skip-slit liner for ease of application.	White	7.0 (0.18)	Glass Cloth	5.0 (0.13)	Acrylic	BMS 5-146; F.A.R. 25.853(a); F.A.R. 25.855(d)
	398FRP	Printed backing version of 398FR.	White	7.0 (0.18)	Glass Cloth	5.0 (0.13)	Acrylic	BMS 5-146; F.A.R. 25.853(a); F.A.R. 25.855(d)
Lead Foil	420	Lead foil backing with rubber adhesive and a white, easy-release film liner.	Dark Silver	7.6 (0.19)	Lead Foil	5.0 (0.13)	Rubber	—
	421	Self-wound plating tape.	Dark Silver	6.6 (0.17)	Lead Foil	4.0 (0.10)	Rubber	—
Non-Woven	394	Air-permeable backing.	White	5.0 (0.13)	Non-Woven	4.5 (0.11)	Acrylic	—
	3294	Most permeable venting tape.	Pink	5.0 (0.13)	Non-Woven	4.5 (0.11)	Acrylic	—
Paper	101+	Indoor use. Light-duty applications.	Tan	5.1 (0.13)	Crepe Paper	—	Rubber	—
	200	Good instant adhesion.	Tan	4.4 (0.11)	Crepe Paper	—	Rubber	—
	201+	General indoor use. Light-to-medium duty. Clean removal.	Tan	4.4 (0.11)	Crepe Paper	—	Solvent-Free Rubber	—
	202	Good holding power.	Tan	6.3 (0.16)	Crepe Paper	—	Rubber	ASTM D 6123; D 6123M-97
	203	Low temperature tape. General purpose masking tape for holding, bundling, sealing and more.	Beige	4.7 (0.12)	Crepe Paper	—	Rubber	—
	213	Good on anodized aluminum.	Tan	6.0 (0.15)	Crepe Paper	—	Rubber	ASTM D 6123; D 6123M-97
	214	Stain resistant.	Tan	5.8 (0.15)	Crepe Paper	—	Rubber	ASTM D 6123; D 6123M-97
	225	Outdoor use.	Silver	5.8 (0.15)	Crepe Paper	—	Rubber	—
	226	Outdoor use.	Black	10.6 (0.27)	Polyethylene/ Crepe Paper	—	Rubber	—
	231	Best all-purpose paint masking tape.	Tan	7.6 (0.19)	Crepe Paper	—	Rubber	ASTM D 6123; D 6123M-97
	231A	Best all-purpose paint masking tape.	Tan	7.6 (0.19)	Crepe Paper	—	Rubber	—
	232	Good paint lines.	Tan	6.3 (0.16)	Crepe Paper	—	Rubber	—
	234	Excellent controlled unwind.	Tan	5.9 (0.15)	Crepe Paper	—	Rubber	ASTM D 6123; D 6123M-97
	250*	Flatback tape. Used in paint adhesion testing.	Tan	6.0 (0.15)	Flatback Paper	—	—	ASTM D 6123; D 6123M-97
	253	Silicone butt splicing tape.	Tan	4.6 (0.12)	Treated Flatstock Paper	3.5 (0.09)	Silicone	—
256*	Printable, accepts marking inks.	White, Red, Green	6.7 (0.17)	Flatback Paper	—	Rubber	ASTM D 6123; D 6123M-97	

*Scotch® brand.

Go-To Product

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.



3M™ Single Coated Tapes (cont.)

Material (alphabetical order)	Product	Typical Performance Characteristics/ Application Ideas	Color	Total Caliper mils (mm)	Backing		Adhesive Type	Specs
					Material	Caliper mils (mm)		
Paper (cont.)	301+	Good conformability to irregular surfaces. Great paint lines.	Yellow	6.3 (0.16)	Crepe Paper	—	Solvent-Free Rubber	—
	401+	Highly conformable to many surfaces. Superior adhesion to metal, rubber, glass and plastic. Great paint lines.	Green	6.7 (0.17)	Crepe Paper	—	Solvent-Free Rubber	—
	501+	Exceptionally conformable to irregular surfaces. Superior adhesion to metal, rubber, glass and plastic. Removes cleanly in one piece with no residue. Great paint lines.	Tan	7.3 (0.19)	Crepe Paper Treated with a Heat Resistant Saturant	—	High Temp Rubber	ASTM D 6123
	2214	Good for holding and bundling.	Tan	5.4 (0.14)	Crepe Paper	—	Rubber	—
	2307	Solvent-free construction; non-critical paint masking.	Tan	5.2 (0.13)	Crepe Paper	—	Rubber	—
	2308	Good transfer resistance.	Tan	5.3 (0.13)	Crepe Paper	—	Rubber	—
	2364	High temperature, crepe paper masking tape for general masking application. Good holding power.	Tan	6.5 (0.17)	Crepe Paper	—	Synthetic Rubber	ASTM D 6123; D 6123M-97
	2380	High temperature. Best holding to widest variety of surfaces.	Tan	7.2 (0.18)	Crepe Paper	—	Synthetic Rubber	ASTM D 6123; D 6123M-97
	2393	Smooth, heavy duty, high temperature masking tape.	Tan	7.6 (0.19)	Crepe Paper	—	Rubber	ASTM D 6123; D 6123M-97
	2460	For paint bake operations at temperatures up to 300°F (149°C). 14 days outdoor.	Gold	3.3 (0.08)	Flatback Paper	—	Acrylic	—
	2480S	A thin, strong, smooth flat back paper that gives sharp paint lines with low paint ridge. 60 days outdoor.	Green	4.0 (0.10)	Flatback Paper	—	Acrylic	—
	2510	General purpose masking tape for holding, bundling, sealing and general paint masking where a dark colored tape is required.	Black	5.6 (0.14)	Crepe Paper	—	Rubber	ASTM D 6123; D 6123M-97
	2515**	General purpose splicing, holding and bundling applications.	Tan	6.7 (0.17)	Kraft Paper	—	Rubber	—
	2517*	Excellent splicing, holding and bundling applications.	Medium Brown	6.5 (0.15)	Kraft Paper	—	Rubber	ASTM D 6123; D 6123M-97
	2525*	Premium splicing, bright color.	Orange	9.5 (0.24)	Flatback Paper	—	Rubber	—
	2526*	Excellent adhesion and strength for textile applications.	White	9.8 (0.24)	Flatback Paper	—	Rubber	—
2693	Very aggressive holding; excellent for multi-bake paint cycles.	Tan	7.9 (0.20)	Crepe Paper	—	Synthetic Rubber	ASTM D 6123; D 6123M-97	
Polyimide	8997/ 8997L	Transparent film. High temperature applications. 8997L is lined version.	Amber	2.2 (0.06)	Polyimide	1.0 (0.02)	Silicone	—
	8998/ 8998L	Transparent film. High temperature applications. 8998L is lined version.	Amber	3.3 (0.08)	Polyimide	2.0 (0.05)	Silicone	—

*Scotch® brand. **Tartan™ brand.

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Single Coated Tapes (cont.)

Material (alphabetical order)	Product	Typical Performance Characteristics/ Application Ideas	Color	Total Caliper mils (mm)	Backing		Adhesive Type	Specs
					Material	Caliper mils (mm)		
Polyester	396	Adhesion to low energy surfaces.	Transparent	4.1 (0.10)	Polyester	1.4 (0.04)	Rubber	—
	 850	Polyester film tape with acrylic adhesive. Used for splicing, holding, decorating, color-coding and sealing.	Transparent, Red, Black, White, Silver	1.9 (0.05)	Polyester	1.0 (0.03)	Acrylic	—
	853	Transparent polyester film tape with solvent-resistant adhesive. Used for butt splicing and tabbing applications.	Transparent	1.9 (0.05)	Polyester	1.0 (0.03)	Acrylic	L-T-100 F.A.R. 25.853(a)
	875	High-temperature, non-silicone, composite bonding.	Seafoam Green	2.0 (0.05)	Polyester	1.0 (0.03)	Rubber	—
	876	High-temperature, non-silicone, composite bonding.	Seafoam Green	3.1 (0.08)	Polyester	2.0 (0.05)	Rubber	—
	8402	Splicing tape. Adheres well to silicone.	Translucent Green	1.9 (0.05)	Polyester	1.0 (0.03)	Silicone	—
	8403/ 8403L	Splicing tape. Adheres well to silicone. 8403L is a lined version of 8403.	Translucent Green	2.4 (0.06)	Polyester	1.5 (0.04)	Silicone	—
	8412	Heavy-duty edge and hole reinforcing.	Transparent	6.3 (0.16)	Polyester	4.7 (0.12)	Acrylic	—
	8421	Photo film splicing.	White	2.3 (0.06)	Polyester	1.4 (0.04)	Rubber	—
	8422	Photo film splicing.	Black	2.3 (0.06)	Polyester	1.4 (0.04)	Rubber	—
	8437	Low emissivity, reflective tape. Metalized coating on both sides of the film.	Silver	1.9 (0.05)	Polyester	1.0 (0.03)	Acrylic	—
	8901	High temperature masking	Blue	2.6 (0.07)	Polyester	1.0 (0.03)	Silicone	—
	8902	High temperature masking	Blue	3.4 (0.09)	Polyester	2.0 (0.05)	Silicone	—
	8905	High temperature masking	Blue	6.5 (0.17)	Polyester	5.0 (0.12)	Silicone	—
	8911	High temperature label protection.	Transparent	2.7 (0.07)	Polyester	1.0 (0.03)	Silicone	—
	8985L	Survives chromic acid with excellent masking lines and clean one-piece removal.	Purple	3.9 (0.10)	Polyester	3.0 (0.08)	Rubber	—
	8991/ 8991L	Thin tapes, powder coat masking, high temperature applications. 8991L is lined version.	Blue	2.4 (0.06)	Polyester	1.0 (0.03)	Silicone	—
	 8992/ 8992L	Powder coat and anodized masking, high temperature applications. 8992L is lined version.	Green	3.2 (0.08)	Polyester	2.0 (0.05)	Silicone	—
8993LC	Protects finished surfaces from light abrasion, nicks and scratches during production, packaging and installation, process agent, rolls up products tape with deliver and assembly. Temporary holding tape.	Transparent	3.2 (0.08)	Polyester	3.0 (0.08)	Silicone	—	
Polypropylene	218/ 218L	Polypropylene plastic film tape with rubber adhesive. A high performance film backed tape with low profile and high adhesion to achieve excellent paint line and for other masking and holding applications. 218L is lined version.	Green	5.0 (0.13)	Polypropylene	—	Rubber	—
	265	Composite masking where sharp, clean, gel-coat color separation lines are desired.	Green	5.1 (0.13)	Polypropylene	—	Rubber/ Silicone	—
	8087	Construction seaming tape.	Red	3.0 (0.08)	Biaxially Oriented Polypropylene Film	1.5 (0.04)	Acrylic	—

*Scotch® brand.

Go-To Product

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.


3M™ Single Coated Tapes (cont.)

Material (alphabetical order)	Product	Typical Performance Characteristics/ Application Ideas	Color	Total Caliper mils (mm)	Backing		Adhesive Type	Specs
					Material	Caliper mils (mm)		
PTFE — Slick Surface	5151/ 5151L/ 5151PL	A woven glass cloth impregnated with PTFE tape which provides a high temperature release surface for protection and insulation. 5151L is a lined version. 5151PL is a thicker, premium liner.	Light Brown	5.3 (0.13)	Glass Cloth Impregnated w/PTFE	3.0 (0.08)	Silicone	—
	5153/ 5153L	Thicker version of 5151. 5153L is a lined version.	Light Brown	8.0 (0.20)	Glass Cloth Impregnated w/PTFE	5.8 (0.15)	Silicone	—
	5451	A woven glass cloth impregnated with PTFE tape which provides a high temperature release surface for protection and insulation.	Brown	5.6 (0.14)	Glass Cloth Impregnated w/PTFE	3.2 (0.08)	Silicone	—
	5453	Thicker version of 5451.	Brown	8.2 (0.21)	Glass Cloth Impregnated w/PTFE	6.0 (0.15)	Silicone	—
	5480	Skived PTFE film tape used for roller wrapping and other slick surface applications.	Gray	3.7 (0.09)	PTFE	2.0 (0.05)	Silicone	—
	5481	Heavy-duty skived PTFE film tape used for roller wrapping and other slick surface applications.	Gray	6.8 (0.17)	PTFE	5.0 (0.13)	Silicone	—
	★ 5490	PTFE Film tape with silicone adhesive used in many slick surface applications. Lay-flat backing.	Gray	3.7 (0.09)	PTFE	2.0 (0.05)	Silicone	—
	5491	Thicker version of 5490.	Gray	6.7 (0.17)	PTFE	5.0 (0.13)	Silicone	—
	5498	Extruded PTFE film tape with rubber silicone-free adhesive.	Brown	4.0 (0.10)	PTFE	2.0 (0.05)	Rubber	—
Polyethylene	480	Good chemical and solvent resistance, conformable, abrasion resistant.	Transparent	5.1 (0.13)	Polyethylene	4.0 (0.10)	Acrylic	—
	481	Preservation sealing tape. Clean removal up to 2 years.	Black	9.5 (0.24)	Polyethylene	7.5 (0.19)	Rubber	SAE-AMS-T-22085, Type II
	4811	Preservation sealing tape. Clean removal up to 1 year.	White	9.5 (0.24)	Polyethylene	7.5 (0.19)	Rubber	—
	★ 483	Conformability, UV resistance, and clean removal for sealing end cap on metal pipes stored outdoors.	Black, Blue, Green, Red, White, Yellow, Transparent	5.0 (0.13)	Polyethylene	3.9 (0.10)	Rubber	MIL-STD 2041D (SH)
Ultra High Molecular Weight (UHMW-PE) — Slick Surface	5421	General purpose tape to protect plastic and metal chutes, guide rails and containers from wear.	Transparent	6.7 (0.17)	UHMW-PE	5.0 (0.13)	Rubber	—
	★ 5423	Excellent abrasion resistance and low coefficient of friction makes this an effective solution for noise and vibration problems.	Transparent	11.7 (0.30)	UHMW-PE	10.0 (0.25)	Rubber	—
	5425	Solvent resistant adhesive with low coefficient of friction and abrasion resistance.	Transparent	5.0 (0.13)	UHMW-PE	3.0 (0.08)	Acrylic	—
	5430	Transparent UHMW-PE film tape with high-tack acrylic adhesive.	Transparent	7.0 (0.18)	UHMW-PE	5.0 (0.13)	Rubber	—
	9325	Thin version of 5430.	Transparent	5.0 (0.13)	UHMW-PE	3.0 (0.08)	Rubber	—

★ Go-To Product

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Single Coated Tapes (cont.)

Material (alphabetical order)	Product	Typical Performance Characteristics/ Application Ideas	Color	Total Caliper mils (mm)	Backing		Adhesive Type	Specs
					Material	Caliper mils (mm)		
Vinyl	470	Conformable and abrasion resistant for masking various surfaces during electroplating and anodizing.	Tan	7.1 (0.18)	Vinyl	6.3 (0.16)	Rubber	—
	 471/ 4712	Vinyl plastic tape ideal for color-coding, abrasion protection, decoration, sealing, patching, splicing, wrapping, and general purpose. Available in 7 colors and transparent. 4712 is a lined version of 471 for die-cutting applications.	Yellow, White, Red, Black, Green, Orange, Blue, Transparent	5.2 (0.13)	Vinyl	4.1 (0.10)	Rubber	MIL-STD 2041D (SH)
	471+	Superior conformability, sharp paint lines, clean removal.	Indigo	5.3 (0.13)	Vinyl	4.1 (0.10)	Rubber	—
	472	Abrasion resistant, high temperature resistant.	Black	10 (0.25)	Vinyl	9.0 (0.23)	Rubber	—
	477	Abrasion resistant.	Transparent	7.2 (0.18)	Vinyl	6.0 (0.15)	Rubber	—
	764	A general purpose vinyl tape for use in non-critical applications such as color-coding, bundling and safety marking.	Yellow, Red, White, Black, Blue, Green, Orange, Gray, Purple, Brown, Transparent	5.0 (0.13)	Vinyl	4.0 (0.10)	Rubber	—
	766	A general purpose hazard marking vinyl tape for use in non-critical applications.	Black & Yellow Stripes	5.0 (0.13)	Vinyl	4.0 (0.10)	Rubber	—
	767	A general purpose hazard marking vinyl tape for use in non-critical applications.	Red & White Stripes	5.0 (0.13)	Vinyl	4.0 (0.10)	Rubber	—
	971	Designed to withstand scuffing from pallets and heavy equipment found in high traffic areas. Its unique adhesive provides a strong bond to the floor yet promotes one piece clean removal. Ideal for 5S lean manufacturing initiatives.	Yellow, White, Red, Blue, Orange, Green	17 (0.43)	Vinyl	15 (0.38)	Rubber	—
	4735	Highly conformable, high temperature vinyl fine line tape for fascia panels, two-tone and other multiple color applications where critical paint break lines are required.	Orange	5.4 (0.14)	Vinyl	—	Rubber	—
	4737S	Highly visible backing version of 4737T.	Solid Blue	5.4 (0.14)	Vinyl	—	Rubber	—
	4737T	Conformable, high temperature vinyl fine line tape for fascia panels, two-tone and other multiple color applications where critical paint break lines are required.	Translucent Blue	5.4 (0.14)	Vinyl	—	Rubber	—
	4737TL	Lined version of 4737T.	Blue	5.4 (0.14)	Vinyl	—	Rubber	—
	5700	Critical applications. Adhesive side printing. For lane and safety marking.	Black & White Stripes	5.5 (0.14)	Vinyl	4.2 (0.11)	Rubber	—
	5702	Critical applications. Adhesive side printing. For lane and safety marking.	Black & Yellow Stripes	5.5 (0.14)	Vinyl	4.2 (0.11)	Rubber	—

 **Go-To Product**

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Single Coated Tapes (cont.)

Material (alphabetical order)	Product	Typical Performance Characteristics/ Application Ideas	Color	Total Caliper mils (mm)	Backing		Adhesive Type	Specs
					Material	Caliper mils (mm)		
Miscellaneous Tapes	215	Medium temperature. Fine line masking tape. Excellent conformability.	Blue	4.8 (0.12)	Copolymer Plastic Film	—	Rubber	—
	616	Lithographers tape.	Ruby Red	2.4 (0.06)	UPVC	1.6 (0.04)	Rubber	—
	695	Polyethylene film with a rubber-strip coated along edges of tape only and tack-free center. Riveters tape.	Yellow	3.0 (0.08)	Polyethylene	2.0 (0.05)	Acrylic*	—
	838	Weather-resistant film.	White	3.4 (0.09)	PVF	2.1 (0.05)	Acrylic	SAE-AMS-T-22085, Type IV
	855	Composite bonding tape.	White	3.6 (0.09)	Nylon	2.0 (0.05)	Rubber	—
	8555	Thicker version of 855, composite bonding tape.	White	7.0 (0.18)	Nylon	5.0 (0.13)	Rubber	—
	5401	High coefficient of friction for traction.	Tan	9.3 (0.24)	Fiberglass Reinforced Silicone	8.0 (0.20)	Silicone	—
	5461	High friction roller tape.	White	9.1 (0.23)	Silicone Rubber	7.8 (0.19)	Rubber	—
	7070UV	Durable, abrasion resistant, UV resistance surface protection. Excellent aerospace tape.	Clear	8.0 (0.2)	Polyurethane	6.5 (0.17)	Acrylic	—
	7071UV	Durable, abrasion resistant, UV resistance surface protection. Excellent aerospace tape.	Clear	14 (0.36)	Polyurethane	12.0 (0.31)	Acrylic	—
	8067	Window and door flashing tape.	Tan	10.0 (0.25)	Multilayer Elastomeric Film	5.0 (0.13)	Acrylic	ICC AC 148, AAMA 711
	8777	Air and water tight sealing tape.	Tan	10.0 (0.25)	Multilayer Elastomeric Film	5.0 (0.13)	Acrylic	—

*Strip coated along edges of tape only.

3M™ Single Coated Foam Tapes

Product Number	Color	Description	Adhesive	Approximate Thickness in. (mm)	Density lbs./cu. ft. (kg/cu m)	Tensile Strength psi (kPa)	Compression Deflection 25% psi (kPa)	Compression Set % Loss	Temperature Tolerance	
									Short-Term	Long-Term
Urethane										
4104*	Natural White	Firm, rigid, open cell urethane foam for cushioning. Allows air or gas vapors to pass through. Not recommended for outdoor use.	350 Acrylic	0.250 (6)	12 (192)	115 (795)	4 (27.6)	8	350°F (176°C)	200°F (93°C)
4108	Natural White		350 Acrylic	0.125 (3)	16 (256)	130 (895)	6 (82.8)	8	350°F (176°C)	200°F (93°C)
4116	Natural White		350 Acrylic	0.062 (1.5)	18 (288)	115 (795)	12 (82.8)	12	350°F (176°C)	200°F (93°C)
4314	Charcoal Gray	Soft conformable, low density open-cell urethane foam can help seal out air, dust and light when compressed 50%. Used to help damp sound and absorb vibration in electronics.	430 Acrylic	0.250 (6)	2 (32)	25 (170)	0.3 (2.1)	5	250°F (121°C)	150°F (66°C)
4317*	Charcoal Gray		430 Acrylic	0.375 (9.5)	2 (32)	25 (170)	0.3 (2.1)	5	250°F (121°C)	150°F (66°C)
4318	Charcoal Gray		430 Acrylic	0.125 (3)	2 (32)	25 (170)	0.3 (2.1)	5	250°F (121°C)	150°F (66°C)
Vinyl Foam Tapes										
4504*	Black	Durable, flexible, closed cell vinyl foams with excellent aging characteristics. Weather resistant. Can help to seal out dust, light and moisture when placed under 30% compression. Liner over PSA.	430 Acrylic	0.250 (6)	20 (320)	90 (620)	4 (27.6)	15	250°F (121°C)	150°F (66°C)
4508*	Black		430 Acrylic	0.125 (3)	20 (320)	100 (690)	4 (27.6)	15	250°F (121°C)	150°F (66°C)
4516*	Black		430 Acrylic	0.062 (1.5)	25 (400)	130 (895)	4 (27.6)	15	250°F (121°C)	150°F (66°C)
4714*	Black		430 Acrylic	0.250 (6)	14 (225)	75 (515)	2 (13.8)	15	250°F (121°C)	150°F (66°C)
4718*	Black		430 Acrylic	0.125 (3)	20 (320)	100 (690)	4 (27.6)	15	250°F (121°C)	150°F (66°C)
4726*	Black		430 Acrylic	0.062 (1.5)	20 (320)	130 (895)	3 (20.7)	15	250°F (121°C)	150°F (66°C)

*Meets requirements of UL 94HBF.

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Single Coated Foil/Foam Sheets

Product Master	Description	Material	Sheets Per Case	Sheet Size (in.)
4014	Absorbs and dissipates vibration and reduces noise in metal and plastic panels. Sheets make for excellent per-pound installed cost ratios on larger jobs.	250 mil open cell polyurethane foam with durable aluminum backing to resist aging and moisture.	50	6 × 48
			25	12 × 48
			15	18 × 48

3M™ Extreme Sealing Tapes

Product	Color	Backing/Adhesive	Tape Thickness mils (mm)	Tensile Strength lbs./in. (N/cm)	90° Peel Adhesion Strength [†] lbs./in. (N/cm)						Application Ideas
					Aluminum	Stainless Steel	Glass	Truck Paint	PVC	ABS	
4411G	Grey	Ionomer Film/Pressure Sensitive Acrylic	40 (1)	13 (23)	15 (26)	16 (28)	15 (26)	15 (26)	15 (26)	16 (28)	Seals RV trailers and roofs. Seals metal enclosures and awnings.
4411N	Neutral/Translucent	Ionomer Film/Pressure Sensitive Acrylic	40 (1)	13 (23)	15 (26)	15 (26)	15 (26)	14 (25)	16 (28)	16 (28)	Seals trailer home roofs and metal storage buildings. Seals vent stacks and windows. Seals gutters and downspouts. Seals skylights.
4411B	Black	Ionomer Film/Pressure Sensitive Acrylic	40 (1)	13 (23)	19 (33)	17 (30)	19 (33)	17 (30)	19 (33)	18 (32)	Seals outdoor signs/displays. Leak patching and repairs.
4412N	Neutral/Translucent	Ionomer Film/Pressure Sensitive Acrylic	80 (2)	13 (23)	18 (32)	18 (32)	19 (33)	19 (33)	19 (33)	19 (33)	

[†]Adhesion promoters were used on peel Adhesion test substrates.

3M™ Splicing Tapes

Adhesive Family ¹	Product	Description/Application Ideas	Tape Cal. (mils)	Carrier Type	Liner ²		Master Size	Specs	Adhesion				Chem. Resist.	Temp. Range	
					Type	Caliper (mils)			Metal	HSE Plastic	LSE Plastic	Foam		Low (°F)	High (°F)
900 Miscellaneous	9737	Clear, thin PET carrier. Aggressive and versatile splicing tape.	3.5	PET	55# DK White	3.5	54" x 180 yd	—	5	5	2	5	7	-10	300
	9737R	Red, thin PET carrier. Aggressive and versatile splicing tape.	3.5	PET	55# DK White	3.5	54" x 180 yd	—	5	5	2	5	7	-10	300
	9738	Clear, non-woven tissue carrier. Aggressive and versatile splicing tape.	4.3	Non-Woven Tissue	55# DK White	4.3	54" x 180 yd	—	5	5	2	5	7	-10	300
	9738R	Red, non-woven tissue carrier. Aggressive and versatile splicing tape.	4.3	Non-Woven Tissue	55# DK White	4.3	54" x 180 yd	—	5	5	2	5	7	-10	300
	9740	Clear, high peel, tack and shear strength. Performance grade splicing tape for corrugators.	3.5	PET	55# DK	3.5	54" x 180 yd	—	6	6	2	3	6	10	425
	9741	Clear, thick, super aggressive tape. Adheres to a wide variety of substrates for splicing applications.	6.5	PET	55# Glassine	6.5	54" x 180 yd	—	7	7	3	7	5	-40	200

3M™ Polyurethane Protective Tapes (PPT) — Long-Term Protection

Nominal Results

Product	Tape Structure (Backing/Adhesive)	Color	Total Thickness mils (mm)	Adhesion to Steel oz./in. Width	Tensile Strength lbs./in. (N/100 mm)	Elongation at Break (%)	Maximum Service Temp °F (°C)	Comments
Based on ASTM Test Method:			D-3652	D-3330	D-3759			
Indoor Type								
8547	Polyurethane/Acrylic	Transparent	13 (0.33)	14 (15)	75 (1313)	500	275 (135)	Flame resistant/low tack (passes NFPA 701).
8547-1	Polyurethane/Acrylic	Transparent	13 (0.33)	14 (15)	75 (1313)	500	275 (135)	Flame resistant/low tack (passes NFPA 701). Tape is easily removed from surface without leaving residue.

1. More information on pg. 11.

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Repulpable Tapes

To achieve true quality, a tape must meet all your needs. Outstanding strength is not enough. The tape must be easy to use, easy to choose, readily available and fully repulpable. We've built our reputation as an industry leader by being responsive to the increasingly complex needs of paper producers. Today, our customer base consists of clients who demand no less of their product than we demand of ours.

Product	Color	Comments	Tape Thickness mils (mm)	Tape Structure		Liner		Heat Resistance *°F (°C)	FDA Compliant [†]
				Backing/ Carrier	Adhesive	Type	Thickness mils (mm)		
Permanent Double Coated									
405	Lt. Green	Excellent for raw and starch-treated papers.	3.0 (0.08)	Tissue	Repulpable	UPVC	1.7 (0.04)	400 (200)	—
900	Blue	Recommended for light weight coated papers.	2.5 (0.06)	Tissue	Repulpable	Paper	3.2 (0.08)	400 (200)	Yes
900B	Blue	Recommended for super calendared papers.	2.5 (0.06)	Tissue	Repulpable	Paper	3.2 (0.08)	400 (200)	Yes
Permanent Single Coated									
901	Lt. Green	Excellent for raw and starch-treated papers.	4.0 (0.10)	Paper	Repulpable	UPVC	1.7 (0.04)	400 (200)	—
910	Blue	Recommended for coated and uncoated papers and paperboard.	4.0 (0.10)	Paper	Repulpable	—	None	400 (200)	Yes
914	Blue	Recommended for high speeds, digital business forms, perforated splicing tape.	4.0 (0.10)	Paper	Repulpable	—	None	400 (200)	Yes
9103	Blue	Printable, coatable backing.	4.5 (0.11)	Paper	Repulpable	Paper	2.9 (0.07)	400 (200)	Yes
9114	Blue	The easiest way to make a butt splice. Printable.	4.5 (0.11)	Paper	Repulpable	Paper	2.9 (0.07)	400 (200)	Yes
9960	Blue	Thinnest butt splicing tape for light weight uncoated and coated and supercalendered papers.	2.2 (0.06)	Paper	Repulpable	Paper	2.9 (0.07)	350 (180)	Yes
9969	Blue/White	Very thin butt splicing/cover tape for uncoated, newsprint and most coated papers.	2.2 (0.06)	Paper	Repulpable	Paper	2.9 (0.07)	350 (180)	Yes
Adhesive Transfer Tape									
R3037	Blue	Thinnest, fiber reinforced adhesive transfer tape.	2.0 (0.05)	None	Repulpable	Paper	3.3 (0.08)	250 (120)	Yes
Temporary Double Coated									
906	Blue/White	Flying splice at the Off-Machine Coater (OMC).	3.0 (0.08)	Tissue	Repulpable	Paper	3.2 (0.08)	400 (200)	Yes
9038	Blue/White	General purpose plus flying splice for the commercial printers, and corrugators.	3.5 (0.09)	Tissue	Repulpable	Paper	3.2 (0.08)	350 (180)	—
9069	Blue	Excellent for newsprint or directory stock.	3.5 (0.09)	Tissue	Repulpable	Paper	3.2 (0.08)	400 (200)	—
9977	Blue	High strength tissue for flying splices where extra strength is needed.	4.0 (0.10)	Tissue	Repulpable	Paper	3.2 (0.08)	400 (200)	—
R3227	Blue/White	General purpose temporary splicing.	3.5 (0.09)	Tissue	Repulpable	Paper	3.2 (0.08)	400 (200)	Yes
R3257	White	Thin tissue, very high-tack.	4.1 (0.11)	Tissue	Repulpable	Paper	3.2 (0.08)	400 (200)	Yes
R3287	White	Heavy tissue, very high-tack.	5.5 (0.14)	Tissue	Repulpable	Paper	3.2 (0.08)	400 (200)	Yes
Temporary Single Coated									
R3127	Blue/White/	General purpose, excellent holding power.	4.5 (0.11)	Paper	Repulpable	—	None	400 (200)	Yes
R3187	Kraft	General purpose, strong repulpable backing.	7.5 (0.19)	Paper	Repulpable	—	None	400 (200)	Yes
R3177	Blue/White/ Red	Heavy duty, extensible repulpable backing.	7.0 (0.16)	Paper	Repulpable	—	None	400 (200)	Yes
Splittable Flying Splice (SFS)									
R3345	Blue	Thin SFS tape for flying splices through supercalendering operations, and permanent butt splices for light weight coated papers.	4.8 (0.12)	Paper	Repulpable	Paper	2.9 (0.07)	400 (200)	—
R3375	Blue	Strong SFS tape for flying splices on heavy papers and high tension web processing through supercalendering operations.	6.5 (0.16)	Paper	Repulpable	Paper	2.9 (0.07)	400 (200)	—
R3379	Blue	Repulpable SFS tape used for high speed splicing conditions when high-tack is required and to compensate for roll profile issues.	7.5 (0.19)	Paper	Repulpable	Paper	2.9 (0.07)	400 (200)	—
R5348	Blue	Use with light- to medium-weight papers running through medium-temperature ovens.	5.0 (0.11)	Paper	Repulpable	Paper	2.9 (0.07)	350 (180)	—
R7359	Blue	Use with light- to heavy-weight papers running at high speeds and high temperatures.	6.6 (0.17)	Paper	Repulpable	Paper	2.9 (0.07)	400 (200)	—
R7369	Blue	Use with light- to heavy-weight paper on wide web rolls to help compensate for roll profile variations running at high speeds and high temperatures.	7.4 (0.19)	Paper	Repulpable	Paper	2.9 (0.07)	400 (200)	—
9990N	Blue	Splittable flying splice (SFS) system with metalized layer for auto-sensing splice detection applications.	5.5 (0.14)	Aluminized Paper**	Repulpable	Paper	2.2 (.05)	350 (180)	—
R9993	Blue	All in one tabbing and splicing tape for heatset printing applications.	5.0 (0.11)	Paper	Repulpable	Paper	2.9 (0.07)	400 (200)	—
R9996	Blue	Thinnest SFS tape for splicing applications in papermills and paper converting coating operations.	4.8 (0.12)	Paper	Repulpable	Paper	2.9 (0.07)	400 (200)	—
R9999	Blue	Repulpable SFS tape for heavyweight papers in manual and automatic splicing equipment, with moderate speed.	6.7 (0.17)	Paper	Repulpable	Paper	2.9 (0.07)	400 (200)	—

[†]All components of the adhesive and backing meet the requirements of indirect food additive regulations as described under 21 CFR 176.170 (Components of paper and paperboard in contact with aqueous and fatty food) and 21 CFR 176.180 (Components of paper and paperboard in contact with dry foods).

*As tested in laboratory. Results may vary depending on machine and web tensions, nature of paper surface, application pressure, etc. which are outside of 3M's control.

**Non-repulpable, screenable aluminized sensor strip.

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

Reclosable Fasteners

Hold tight. Remove easily.

The lightweight alternative to metal fasteners offering easy opening and closing. Reclosable Fasteners join dissimilar materials without corrosion or contamination. Plus, they offer vibration absorption, durability and security.

Learn more at:
3M.com/Fasteners




**3M™ Dual Lock™
Reclosable
Fasteners**
Fastening
power and
flexibility.



Fastening power and flexibility.

You have options. Check out the large 3M portfolio of solutions that offer these solutions:


- Clean, smooth “behind the scenes” hold for aesthetic improvements
- Lightweight alternatives to metal fasteners
- Simple to apply, use and maintain
- Variety of strengths to fit your project needs
- Flexibility to fit your designs, even the most constricted areas
- Ability to join dissimilar materials without corrosion and contamination
- Vibration absorption and security — no loosening or failing attachments
- Durable for repeated opening and closings — hundreds of reattachments



3M™ Dual Lock™
Reclosable Fastener
Type 400




3M™ Dual Lock™
Reclosable Fastener
Type 250



3M™ Dual Lock™
Reclosable Fastener
Type 170



3M™ Dual Lock™
Reclosable Fastener
Low Profile



3M™ Hook and Loop
Reclosable Fastener
Standard Thickness



3M™ Hook and Loop
Reclosable Fastener
Low Profile

Holding strength increases as you move up from 3M™ Hook and Loop through 3M™ Dual Lock™ Reclosable Fasteners.

3M™ Dual Lock™ Reclosable Fasteners

Stem Density
(per sq/in)
Combinations

Strongest
250:400

Stronger
250:250 or 170:400

Strong
170:250

Not Recommended
170:170 or 400:400



3M™ Hook and Loop Reclosable Fasteners



Interchangeable Strength Combinations



Type 400

Type 250

Type 170

Low Profile

Hooks on one side, loops on the other for secure, repeated closures.

- Up to 5,000 closures for our standard Hook and Loop
- Low profile options available, as much as 75% thinner than standard product

3M™ Dual Lock™ Reclosable Fasteners

Holding power to replace screws, bolts and rivets.

Durable enough to last through repeated opening and closing. Unique, interlocking mushroom-shaped heads snap shut and stay locked.

- Durable — up to 1,000 openings and closings before losing 50% of original tensile strength
- Helps reduce vibration
- Temperature, moisture and UV resistant
- Strong, pressure-sensitive adhesive bonds on contact
- Mushroom-shaped heads have 5X the tensile strength of hook-and-loop products

■ Best Suggested Product
● Performance Dependent on Selected Attachment Method
▲ Primer Recommended

Product	Stem Density (per sq./in.)	Adhesive	Color	3M Liner	Engaged Thickness	Temperature Resistance °F (°C)	Substrates					Use	Markets									
							Metals (Al & SS)	Glass	Plastics (Acrylic, PC, ABS)	Powder Coated Paints	Low Surface Energy (PP, PE)		Indoor/Outdoor	Aerospace & Rail	Appliance & Electronics	Design & Construction	Furniture & Upholstery	General Industrial	Marine & Specialty Vehicle	POP, Display & Signage		
SJ3540	250	Rubber	Black	White, 5 mil (0.13mm) Polyolefin	0.23" (5.7mm)	120 (49)	■		■	■	■	Indoor										
SJ3541	400	Rubber	Black																			
SJ3542	170	Rubber	Black																			
SJ3560	250	Clear Acrylic	Clear	Clear, 3 mil (0.08mm) Polyolefin	0.23" (5.7mm)	200 (93)	■	■	■	▲	▲	Indoor/Outdoor		■	■	■	■	■	■	■		
SJ3561	400	Clear Acrylic	Clear																			
SJ3562	170	Clear Acrylic	Clear																			
SJ3550CF ★	250	Clear Acrylic	Black	Clear, 3 mil (0.08mm) Polyolefin	0.23" (5.7mm)	200 (93)	■	■	■	▲	▲	Indoor/Outdoor		■	■	■	■	■	■	■		
SJ3551CF ★	400	Clear Acrylic	Black																			
SJ3552CF ★	170	Clear Acrylic	Black																			
SJ3870	250	Modified Acrylic	Black	Clear, 4.5 mil (0.11mm) Polyolefin	0.24" (6.1mm)	140 (60)	■		■	■	▲	Indoor/Outdoor										
SJ3871	400	Modified Acrylic	Black																			
SJ3872	170	Modified Acrylic	Black																			
SJ3782	250	Low Surface Energy Acrylic	Black	Brown, 83# Polykraft	0.16" (4.1mm)	120 (49)	■		■	■	■	Indoor/Outdoor		■								
SJ3440	250	None	Black	No Liner	0.15" (3.86mm)	220 (104)	●	●	●	●	●	Indoor/Outdoor		●	●	●	●	●	●	●		
SJ3441	400	None	Black																			
SJ3442	170	None	Black																			
SJ3443	400	Non-woven backing with no adhesive	Black	No Liner	0.28" (7.1mm)	220 (104)	●	●	●	●	●	Indoor/Outdoor		●	●	●	●	●	●	●		
SJ3444	170	Non-woven backing with no adhesive	Black	No Liner	0.28" (7.1mm)	220 (104)	●	●	●	●	●	Indoor/Outdoor		●	●	●	●	●	●	●		
SJ3445	250	Non-woven backing with no adhesive	Black	No Liner	0.28" (7.1mm)	220 (104)	●	●	●	●	●	Indoor/Outdoor		●	●	●	●	●	●	●		
SJ3460	250	None	Clear	No Liner	0.15" (3.86mm)	220 (104)	●	●	●	●	●	Indoor/Outdoor		●	●	●	●	●	●	●		
SJ3463	400	Piece Part Circle*	Black	No Liner	0.20 in.* (5.1mm)	220 (104)	■		■	■	■	Indoor/Outdoor		■	■	■	■	■	■	■		
SJ3481	400	Rigid Strip*	Black	No Liner	0.20 in.* (5.1mm)	220 (104)	●	●	●	●	●	Indoor/Outdoor		●	●	●	●	●	●	●		
SJ4570 ★	Low Profile/Thin	Low Surface Energy Acrylic	Clear	Brown, 83# Polykraft	0.098" (2.489mm)	158 (70)	■		■	■	■	Indoor/Outdoor		■	■	■	■	■	■	■		
SJ4575	Low Profile/Thin	Low Surface Energy Acrylic	Black	Brown, 83# Polykraft	0.098" (2.489mm)	158 (70)	■		■	■	■	Indoor/Outdoor		■	■	■	■	■	■	■		
SJ4580	Low Profile/Thin	Clear Acrylic	Clear	Red, 4.5 mil (0.11mm) Polyolefin	0.12" (3.0mm)	200 (93)	■	■	■	▲	▲	Indoor/Outdoor		■	■	■	■	■	■	■		

*Single thickness; not engaged †No adhesive

★ Go-To Product

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Hook and Loop Reclosable Fasteners

Hooks on one side, loops on the other for secure, repeated closures.

- Reliable PSA hold on contact with a variety of materials
- Available in black, white and beige
- Low profile options, as much as 75% thinner than standard product
- Up to 5,000 closures for standard Hook and Loop



Product	Type	Adhesive	Closure Life	Product Material	Liner Description	Engaged Thickness	Temperature Resistance °F (°C)	Substrates					Use	Markets			
								Metals (Al & SS)	Glass	Plastics (Acrylic, PC, ABS)	Powder Coated Paints	Low Surface Energy (PP, PE)		Indoor/Outdoor	Aerospace & Rail	Furniture & Upholstery	General Industrial
High Performance																	
SJ3526N	Hook	High Performance Rubber	5,000	Nylon	White, 3 mil (0.08mm) Polyethylene film 3M Red Print	0.14 in. (3.6mm)	120 (49)	■	■	■	■	■	Indoor	■	■	■	
SJ3527N	Loop	High Performance Rubber	5,000	Nylon		0.14 in. (3.6mm)	120 (49)	■	■	■	■	■	Indoor	■	■	■	
SJ3572	Hook	High Performance Acrylic	5,000	Nylon	Clear, 4 mil (0.10mm) Polypropylene film Embossed 3M logo	0.14 in. (3.6mm)	200 (93)	■	■	■	▲	▲	Indoor/Outdoor	■	■	■	
SJ3571	Loop	High Performance Acrylic	5,000	Nylon		0.14 in. (3.6mm)	200 (93)	■	■	■	▲	▲	Indoor/Outdoor	■	■	■	
General Purpose																	
SJ3522	Hook	Plasticizer Resistant Acrylic	5,000	Nylon	Clear, 3.5 mil (0.08mm) Polyolefin film No print	0.14 in. (3.6mm)	158 (70)	■	■	■	■	■	Indoor/Outdoor	■	■	■	
SJ3523	Loop	Plasticizer Resistant Acrylic	5,000	Nylon		0.14 in. (3.6mm)	158 (70)	■	■	■	■	■	Indoor/Outdoor	■	■	■	
SJ3530	Hook	High-tack Rubber	5,000	Nylon	Yellow, 3 mil (mm) Polyethylene film No Print	0.14 in. (3.6mm)	90 (32)	■	■	■	■	■	Indoor	■	■	■	
SJ3531	Loop	High-tack Rubber	5,000	Nylon		0.14 in. (3.6mm)	90 (32)	■	■	■	■	■	Indoor	■	■	■	
Without Adhesive																	
SJ3401	Loop	None	5,000	Nylon	None	0.12 in. (3.0mm)	200 (93)	●	●	●	●	●	Indoor/Outdoor	●	●	●	
SJ3402	Hook	None	5,000	Nylon	None	0.12 in. (3.0mm)	200 (93)	●	●	●	●	●	Indoor/Outdoor	●	●	●	
Low Profile/Thin																	
SJ3506	Hook	Acrylic	25	Polypropylene	Brown #83 Polykraft Green Print	0.034 in. (0.84mm)	158 (70)	■	■	■	▲	▲	Indoor/Outdoor	■	■	■	
SJ3507	Loop	Acrylic	25	Polyester		0.034 in. (0.84mm)	158 (70)	■	■	■	▲	▲	Indoor/Outdoor	■	■	■	
SJ3001	Back-to-back hook and loop	None	100	Polyester/Polypropylene	None	0.101 in (2.6mm)	200 (93)	■	■	■	□	□	Indoor/Outdoor	□	□	□	
Flame Resistant																	
SJ3519FR	Hook	Flame Resistant	5,000	FR Nylon	White, 3 mil (0.08mm) Polyethylene film 3M Red Print	0.14 in. (3.6mm)	158 (70)	■	■	■	■	■	Indoor	■	■	■	
SJ3518FR	Loop	Flame Resistant	5,000	FR Nylon		0.14 in. (3.6mm)	158 (70)	■	■	■	■	■	Indoor	■	■	■	
SJ3419FR	Hook	None	5,000	FR Nylon	None	0.12 in. (3.0mm)	200 (93)	●	●	●	●	●	Indoor/Outdoor	●	●	●	
SJ3418FR	Loop	None	5,000	FR Nylon	None	0.12 in. (3.0mm)	200 (93)	●	●	●	●	●	Indoor/Outdoor	●	●	●	

■ Best Suggested Product

▲ Primer Recommended

● Performance Dependent on Selected Attachment Method

□ Back-to-Back Fastener Which Can Wrap Around Any Type of Surface or Substrate

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

Specialty Products

Protective products for life's mishaps.

Life is full of risks, but you can offer your customers protection against some of them. 3M specialty products feature pressure-sensitive adhesives for long-lasting and fast-bonding protection where and when you need it.

3M™ Premium Polyurethane Foam Tapes

Product	Color	Adhesive	Approximate Thickness in. (mm)	Roll Size	Density lbs./cu. ft. (kg/cu m)	Tensile Strength (psi (kPa))	Tensile Elongation % Min.	Tear Strength Min. pli (kN/m)	Compression Deflection @23°C, psi (kPa)	Temperature Tolerance	
										Short-Term	Long-Term
Medium Density Series											
12026	Black	With* or without**	1/16 (1.6)	54" x 300 ft.	15 (239)	50 (345)	90	4.0 (0.7)	305–6.5 (24–45)	250°F (121°C)	150°F (66°C)
12032	Black	With* or without**	3/32 (2.4)	54" x 225 ft.	15 (239)	50 (345)	90	4.0 (0.7)	305–6.5 (24–45)	250°F (121°C)	150°F (66°C)
12028	Black	With* or without**	1/8 (3.2)	54" x 160 ft.	15 (239)	50 (345)	90	4.0 (0.7)	305–6.5 (24–45)	250°F (121°C)	150°F (66°C)
12036	Black	With* or without**	3/16 (4.8)	54" x 100 ft.	15 (239)	50 (345)	90	4.0 (0.7)	305–6.5 (24–45)	250°F (121°C)	150°F (66°C)
12034	Black	With* or without**	1/4 (6.4)	54" x 80 ft.	15 (239)	50 (345)	90	4.0 (0.7)	305–6.5 (24–45)	250°F (121°C)	150°F (66°C)
12038	Black	With* or without**	3/8 (9.5)	54" x 60 ft.	15 (239)	50 (345)	90	4.0 (0.7)	305–6.5 (24–45)	250°F (121°C)	150°F (66°C)
12030	Black	With* or without**	1/2 (12.7)	54" x 40 ft.	15 (239)	50 (345)	90	4.0 (0.7)	305–6.5 (24–45)	250°F (121°C)	150°F (66°C)
High Density Series											
12046	Black	With* or without**	1/16 (1.6)	54" x 300 ft.	20 (320)	75 (517)	100	7.0 (1.2)	8–12 (55–83)	250°F (121°C)	150°F (66°C)
12062	Black	With* or without**	3/32 (2.4)	54" x 225 ft.	20 (320)	75 (517)	100	7.0 (1.2)	8–12 (55–83)	250°F (121°C)	150°F (66°C)
12048	Black	With* or without**	1/8 (3.2)	54" x 160 ft.	20 (320)	75 (517)	100	7.0 (1.2)	8–12 (55–83)	250°F (121°C)	150°F (66°C)
12056	Black	With* or without**	3/16 (4.8)	54" x 100 ft.	20 (320)	75 (517)	100	7.0 (1.2)	8–12 (55–83)	250°F (121°C)	150°F (66°C)
12054	Black	With* or without**	1/4 (6.4)	54" x 80 ft.	20 (320)	75 (517)	100	7.0 (1.2)	8–12 (55–83)	250°F (121°C)	150°F (66°C)
12049	Black	With* or without**	3/8 (9.5)	54" x 60 ft.	20 (320)	75 (517)	100	7.0 (1.2)	8–12 (55–83)	250°F (121°C)	150°F (66°C)
12050	Black	With* or without**	1/2 (12.7)	54" x 40 ft.	20 (320)	75 (517)	100	7.0 (1.2)	8–12 (55–83)	250°F (121°C)	150°F (66°C)

*Adhesive Selection.

**Non Adhesive foams are UL 94HBF, File E61941 Recognized Components.

Construction Availability

Polymer	Thickness	Liner	Typical Performance Characteristics
Standard Viscoelastic Damping Polymer			
110	2 and 5 mil	Paper	Good damping performance at higher temperature: 40–105°C (104–221°F). Heat and pressure needed for bonding.
112	1, 2 and 5 mil	Paper	Good damping performance at 0–65°C (32–142°F). Pressure only for adequate bonding at room temperature (21°C/70°F) for many applications.
130	2 and 5 mil	Polyester	Good damping performance at moderate temperature range of 20–90°C (68–194°F). Pressure only for adequate bonding at room temperature (21°C/70°F) for some applications.
Ultra-Pure Viscoelastic Damping Polymer			
242	1 and 2 mil	Polyester	Good damping performance at 0–65°C (32–142°F). Low outgassing by GC/MS (Modified ASTM 4526). Low ionics.

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

Flexographic Mounting Systems

Where science meets craft.

The 3M flexographic portfolio melds the best worlds of 3M: science and craft. Innovative 3M flexo solutions deliver optimal, consistent, and productive quality. These flexo products ensure that a craftsman's print room is a space where science and craft work as one.

Learn more at:
[3M.com/Flexo](https://www.3m.com/Flexo)

Outstanding quality from every angle.

Dependable, consistent, plus faster mounting and demounting.





Performance you can trust.

Our tapes give operators outstanding quality from every angle with the 3M™ Print Quality Advantage.



Optimal

With the industry's largest range of tape densities.


- Expanded gamut printing
- Faster presses
- Maximize your investment in new plate and screening technologies
- Flexible today and into the future
- Optimizing every run
- Consistent, predictable



Consistent

With one of the industry's tightest caliper tolerances, delivering predictable print results.

- Dependable performance day after day
- Consistent, tight tape caliper
- Bubble-free mounting
- Dependable adhesive performance



Productive

With industry-leading productivity-enhancing adhesives.

- Protect your resources and assets
- Simplify plate mounting
- Keep your press running faster
- Ease of use
- Faster mounting and demounting

3M™ Flexographic Mounting Systems

3M™ Combination Printing Tapes							3M™ Process Printing Tapes
18 Series: Firm	17 Series: Medium Firm	15 Series: Medium	10 Series: Standard	13 Series: Medium Soft	19 Series: Light Medium	12 Series: Light	11 Series: Process
10% Highlight							
40% Midtone							
Reverse							
100% Solid							
Quality results when plate contains mostly solids in a combination of solid and halftone images.	Quality results when plate contains slightly more solids in a combination of solid and halftone images.	Quality results for high speed printing with fine type reverses and expanded color gamut.	Quality results when solid and halftone areas are equally important.	Quality results for high speed printing of combination work when halftone areas exceed solid.	Soft support improves tone reproduction when process and halftone images predominate.	Low density maximizes dot reproduction for high quality process work and screen printing.	Low density maximizes dot reproduction for high quality process work and screen printing.
E1815, E1815H, 1815M E1820, E1820H, 1820M E1840H, E1860H	E1715, E1715H E1720, E1720H, 1720M	E1515, E1515H E1520, E1520H	E1015, E1015H, 1015, 1015M E1020, E1020H, 1020, 1020M, 1020R E1040, E1040H, 1040 E1060, E1060H, 1060	E1315, E1315H E1320, E1320H	E1915, E1915H, 1915M, E1915S, E1915HS E1920, E1920H, 1920M, E1920S, E1920HS, 1920S,	E1215, E1215H E1220, E1220H	E1115, E1115H, 1115 E1120, E1120H, 1120

E: Air Release Medium Plate Side Adhesion; **EH:** Air Release High Plate Side Adhesion; **S:** High Sleeve Side Adhesion for Urethane Sleeves; **M:** Modified Plate Side Adhesion; **DL:** Double Liner; **R:** Rubber Plates; **K:** High sleeve side adhesion for composite sleeves.

Additional calipers available for specialized applications.

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Flexographic Mounting Systems (cont.)

Product	Application Thickness in. (mm)	Manufactured Target Thickness in. (mm)	Description	Plates	Cylinders	Color	Features	
3M™ Flexomount™ Solid Plate Mounting Tapes								
Solid Printing Tapes	411DL	0.015 (0.38)	0.015 (0.38)	Gray double coated tape with a soft rubber adhesive on each side of a vinyl carrier. Available in single and double liner.	P/R	SS/S/K	Gray	Gray vinyl tapes with high adhesion. Helps reduce edge lifting. Helps minimize pin holing on solid work.
	412DL	0.020 (0.51)	0.020 (0.51)		P/R	SS/S/K	Gray	
	447DL	0.010 (0.25)	0.010 (0.25)		P/R	SS/S/K	Gray	
18 Series 3M™ Cushion-Mount™ Plus Firm Combination Plate Mounting Tapes								
Solid Printing Tapes	E1815H, E1815	0.015 (0.38)	0.017 (0.43)	Differential acrylate adhesive system on each side of a foam carrier, protected by a release liner on one side.	P	SS/S/K	Blue	Better solid ink density than the standard combination printing tapes. Clean removal from plate and print cylinder.
	E1820H, E1820	0.020 (0.51)	0.022 (0.56)		P	SS/S/K	Blue	
	E1840H, E1860H	0.040 (1.02) 0.060 (1.52)	0.042 (1.07) 0.062 (1.57)		P	SS/S/K	Blue	
17 Series 3M™ Cushion-Mount™ Plus Medium Firm Combination Plate Mounting Tapes								
Solid Printing Tapes	E1715H, E1715	0.015 (0.38)	0.017 (0.43)	Differential acrylate adhesive system on each side of a foam carrier, protected by a release liner on one side.	P	SS/S/K	Teal	Quality results when plate contains slightly more solids in a combination of solid and halftone images.
	E1720H, E1720, 1720M	0.020 (0.51)	0.022 (0.56)		P	SS/S/K	Teal	
15 Series 3M™ Cushion-Mount™ Plus Medium Combination Plate Mounting Tapes								
Solid Printing Tapes	E1515H, E1515	0.015 (0.38)	0.017 (0.43)	Differential acrylate adhesive system on each side of a foam carrier, protected by a release liner on one side.	P	SS/S/K	Purple	High quality, medium combination print.
	E1520H, E1520	0.020 (0.51)	0.022 (0.56)		P	SS/S/K	Purple	
10 Series 3M™ Cushion-Mount™ Plus Standard Combination Plate Mounting Tapes								
Combination Printing Tapes	E1015H, E1015, 1015, 1015M	0.015 (0.38)	0.017 (0.43)	Differential acrylate adhesive system on each side of a foam carrier, protected by a release liner on one side.	P	SS/S/K	White	Most versatile 3M™ Cushion-Mount™ Plus Tapes. Effectively prints most types of flexographic printing.
	E1020H, E1020, 1020, 1020R	0.020 (0.51)	0.022 (0.56)		P/R	SS/S/K	White	
	E1040, 1040, E1040H	0.040 (1.02)	0.042 (1.07)		P	SS/S/K	White	
	E1060, 1060, E1060H	0.060 (1.52)	0.062 (1.57)		P	SS/S/K	White	
13 Series 3M™ Cushion-Mount™ Plus Medium Soft Combination Plate Mounting Tapes								
Solid Printing Tapes	E1315H, E1315	0.015 (0.38)	0.017 (0.43)	Differential acrylate adhesive system.	P	SS/S/K	Yellow	High quality, medium-soft combination print.
	E1320H, E1320	0.020 (0.51)	0.020 (0.51)		P	SS/S/K	Yellow	
19 Series 3M™ Cushion-Mount™ Plus Light Medium Combination Plate Mounting Tapes								
Solid Printing Tapes	E1915H, E1915, E1915HS, E1915S	0.015 (0.38)	0.017 (0.43)	Differential acrylate adhesive system on each side of a foam carrier, protected by a release liner on one side.	P	SS/S	Pink	Soft support improves tone reduction when process and halftone images predominate.
	E1920H, E1920	0.020 (0.51)	0.022 (0.56)		P	SS/S	Pink	
	E1920S, 1920S, E1920HS	0.020 (0.51)	0.022 (0.56)		P	S/K	Pink	
12 Series 3M™ Cushion-Mount™ Plus Light Combination Plate Mounting Tapes								
Solid Printing Tapes	E1215H, E1215	0.015 (0.38)	0.017 (0.43)	Differential acrylate adhesive system on each side of a foam carrier, protected by a release liner on one side.	P	SS/S	Orange	—
	E1220H, E1220	0.020 (0.51)	0.022 (0.56)		P	SS/S	Orange	
11 Series 3M™ Cushion-Mount™ Plus Process Plate Mounting Tapes								
Process Printing	E1115H, E1115, 1115	0.015 (0.38)	0.017 (0.43)	Differential acrylate adhesive system on each side of a foam carrier, protected by a release liner on one side.	P	SS/S	Tan	Better tone reproduction than the standard combination printing tapes. Clean removal from plate and print cylinder.
	E1120H, E1120, 1120	0.020 (0.51)	0.022 (0.56)		P	SS/S	Tan	

E: Air Release Liner; **M:** Modified Plate Side Adhesion; **DL:** Double Liner; **S:** Urethane Sleeve; **K:** High sleeve side adhesion for composite sleeves; **SS:** Stainless Steel Cylinder; **R:** Rubber Plates; **P:** Photopolymeric Plates; **EH:** High Plate Side Adhesion.

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

E-Series Tapes with 3M™ Comply™ Adhesive System

The bubble-free answer.




E-Series Tapes were the first plate mounting tapes in the market with patented 3M™ Comply™ Adhesive System which virtually eliminates air bubbles with the micro-channels in the adhesive. That means saving the mounter time and eliminating press down time caused by air bubbles.

EH-Series Tapes


Tight hold for small cylinders.

3M™ EH-Series Tapes combine the air-release of 3M™ E-Series Tapes with higher plate side adhesion to resist edge lifting on cylinder diameters as small as 2 inches.

Microscopic View of Adhesive Surface Measured with Interferometer



Pebbled Liner



Flat Liner

3M™ Comply™ Adhesive System Benefits

Stays on with reduced edge-lifting.

Exclusive 3M plate-side adhesive maintains tight contact between tape and plate to dramatically reduce edge lifting. Saves the prep time, downtime, and labor of sealing plate edges.

Peels off easily to reduce plate damage.

E-series tapes grip tightly but peel off so easily you can virtually eliminate plate back treatment. You're less likely to damage plates, so you can save time, labor and money.

Bubble-free print quality.

Prevent blemishes in screen and process printing, and help assure proper registration.

3M™ Thin Tapes

When cushioning is unnecessary, these tapes can mount both rubber and photopolymer plates. Some are also repositionable.

Product	Tape Thickness in. (mm)	Description	Compressible Sleeves	Corrugated	Rotary Letterpress	Make Ready	Features
415	0.004 (0.10)	Double coated tape with a medium-firm acrylic adhesive on each side of a polyester carrier.		■	■		Good adhesion to a wide range of surfaces. Can be used for Cameron Press applications.
442KW	0.004 (0.10)	Double coated tape with a firm rubber adhesive on each side of a polyester carrier.		■	■		Plate mounting applications requiring a thin tape to bond rubber or photopolymer plates to metal cylinders.
443	0.005 (0.13)	Double coated tape with a soft rubber adhesive on each side of a polyester carrier.		■	■		Mounting applications requiring a thin tape to bond polyester, fiberglass and other surfaces.
465	0.002 (0.05)	Acrylic adhesive transfer tape.		■		■	Small area plate build-up or make-ready. Also used to mount primed rubber plates.
927	0.002 (0.05)	Acrylic adhesive transfer tape.		■		■	Corrugated plate mounting applications where repositionability and removability are not required.
950	0.005 (0.13)	Acrylic adhesive transfer tape.		■			

All tapes listed on this chart have been used successfully on non-compressible sleeves.

Continued on next page.

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Thin Tapes (cont.)

Product	Tape Thickness Inch (mm)	Description	Compressible Sleeves	Corrugated	Rotary Letterpress	Make Ready	Features
2205	0.005 (0.13)	Double coated film tape with differential acrylic adhesive with a polyester film carrier on a kraft paper liner.	■	■			For the corrugated printing industry to hold flexographic print plates to PVC saddles/carriers. Removes cleanly.
2205FL	0.005 (0.13)	Double coated film tape with differential acrylic adhesive with a polyester film carrier on a film liner.	■	■			Adhesives designed specifically for corrugated flexo mounting. Removes cleanly and easy to reposition.
9500PC	0.005 (0.13)	High performance acrylic adhesive on each side of a polyester carrier.	■		■		Thin tape plate mounting applications requiring higher performance than 442KW Tape.

All tapes listed on this chart have been used successfully on non-compressible sleeves.

3M™ Flexographic Mounting Aids

Product	Description
3M™ AP86A	Helps hold the leading and trailing edges of the plate to prevent edge lifting.
3M™ Aluminum Foil Tape 425	Seals plate edges against ink and solvent penetration that can cause edge lifting.
3M™ Vinyl Tape 471	Seals plate edges against ink and solvent penetration that can cause edge lifting.
3M™ Polyester Film Tape 850	Seals plate edges against ink and solvent penetration that can cause edge lifting.
Scotch® Magic Tape 810	Secures proofing paper to a proofer/mounter with good adhesion but simple removal from the proofing cylinder.

3M™ Non-Repulpable Splicing Tapes

Go To Products	Description	Tape Thickness mil (mm)	Carrier Thickness mil (mm)	Carrier Type	Color	Adhesion oz./in. (N/25 mm)	High Temp (Short-Term) °F (°C)	Go-To Application*	
								Zero Speed	Flying Speed
Based on ASTM Test Method:		D-3652	D-3652			D-3330			
Adhesive Transfer Tapes									
465	High-tack. Excellent adhesion to most paper stocks. Flexible to -60°F (-51°C).	2.0 (0.05)	—	No Carrier	Clear	25 (6.8)	250 (121)		
9498	Low temperature splicing.	2.0 (0.05)	—	No Carrier	Clear	20 (6.0)	250 (121)	■	
9499	High temperature splicing.	2.0 (0.05)	—	No Carrier	Clear	45 (12.5)	350 (177)	■	
Double Coated Tapes									
415/ 9420	High-tack adhesion to paper and many other surfaces.	4.0 (0.10)	0.5 (0.01)	Polyester	Clear/Red	25 (6.8)	180 (82)		
469	High temperature, high-tack.	5.5 (0.14)	1.0 (0.02)	Tissue	Red	60 (16.7)	350 (177)		■
9576	Medium tack for general splicing and roll closing.	4.0 (0.10)	1.0 (0.02)	Polypropylene	Red/Black/ Yellow	30 (13.5)	165 (75)		
9737/ 9737R	Thin PET carrier. Aggressive and versatile tape for many surfaces.	3.5 (0.09)	0.5 (0.01)	Polyester	Clear/Red	60 (16.7)	300 (150)	■	■
9738/ 9738R	Non-woven tissue carrier. Aggressive and versatile tape for many surfaces.	4.3 (0.11)	1.3 (0.03)	Non Woven Tissue	Clear/Red	60 (16.7)	300 (150)	■	■
9740	High temperature with extremely wide range. High peel, tack, and shear properties. Performance grade splicing for corrugators.	3.5 (0.09)	0.5 (0.01)	Polyester	Clear	70 (21.2)	425 (218)		■
9741/ 9741R	Thick tape adheres to a wide variety of substrates. Super aggressive for low surface energy substrates.	6.5 (0.17)	0.5 (0.01)	Polyester	Clear/Red	120 (34.0)	200 (93)		
Splittable Flying Splice Tape									
8387	Splice even the most challenging substrates: cast and biaxially oriented polypropylene, polyester, and aluminum foil.	7.0 (0.19) without liner	3.0 (0.09)	Film	Pink/Black	60 (16.7)	175 (79)		■

*All tapes in this chart can be considered for zero speed or flying speed splices.

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.

Numerical Product Index

Product	Page	Product	Page	Product	Page	Product	Page	Product	Page
101+	69	442KW	87	910	76	4004	32	4979F	33
110	82	443	87	914	76	4008	32	4988	15
112	82	444	22	920XL	29	4014	68, 75	4991	33
130	82	444PC	22	924	30	4016	32	4991B	33
200	69	447DL	86	926	30	4026	32	4994	15
201+	69	450EK	29	927	17, 87	4052	32	4996	15
202	69	450X	29	928	30	4056	32	4997	15
203	69	463	19	941	16	4085	32	4998	15
213	69	465	19, 87, 88	950	17, 87	4104	74	4999	15
214	69	465XL	29	950EK	17	4108	74	5002	15
215	74	467MC	16	965	16	4116	74	5002D	15
218	71	467MP	16	966	16	4314	74	5051	15
218L	71	467MPF	16	966FL	16	4317	74	5151	72
225	69	468MC	16	969	30	4318	74	5151L	72
226	69	468MP	16	971	73	4411B	75	5151PL	72
231	69	468MPF	16	976	30	4411G	75	5153	72
231A	69	469	88	987	30	4411N	75	5153L	72
232	69	470	73	1015	86	4412N	75	5401	74
234	69	471	73, 88	1015M	86	4462	32	5421	72
242	82	471+	73	1020	86	4466	32	5423	72
250	69	472	73	1020R	86	4492	32	5425	72
253	69	476	24	1040	86	4496	32	5430	72
256	69	476XL	29	1060	86	4504	74	5451	72
265	71	477	73	1115	86	4508	74	5453	72
301+	70	480	72	1120	86	4516	74	5461	74
361	69	481	72	1720M	86	4658F	26, 32	5480	72
363	68	483	72	1920S	86	4712	73	5481	72
363L	68	501+	70	2205	88	4714	74	5490	72
365	69	501FL	17	2205FL	88	4718	74	5491	72
394	69	502FL	17	2214	70	4726	74	5498	72
396	71	583	32	2307	70	4735	73	5700	73
398FR	69	588	32	2308	70	4737S	73	5702	73
398FRP	69	615	32	2364	70	4737T	73	5906	33
401+	70	615S	32	2380	70	4737TL	73	5907	33
401M	24	616	74	2393	70	4811	72	5908	33
405	76	665	26	2460	70	4905	34	5909	33
406	32	666	26	2480S	70	4910	34	5913	33
410M	24	668	32	2510	70	4914	34	5915	33
411DL	86	690	32	2515	70	4914-015	34	5915P	33
412DL	86	695	74	2517	70	4914-020	34	5925	33
415	23, 87, 88	764	73	2525	70	4919F	33	5925P	33
420	69	766	73	2526	70	4920	34	5930	33
421	69	767	73	2552	68	4926	33	5930P	34
425	68, 88	810	88	2693	70	4930	34	5952	34
427	68	838	74	3028EK	23	4936	33	5952P	34
431	68	850	71, 88	3294	69	4936F	33	5958FR	34
433	68	853	71	3302	68	4941	33	5962	34
433L	68	855	74	3615	69	4941F	33	5962P	34
434	68	875	71	3650	69	4947F	33	7000	58, 64
435	68	876	71	3690E+	56	4950	34	7000FL	58, 64
436	68	900	75, 76	3693FLE	29	4955	34	7004	58
437	68	900B	76	3698E+	56	4956	33	7011	58, 64
438	68	901	76	3812	60	4956F	33	7028	54
439	68	906	76	3921	58	4959	34	7029	52

Numerical Product Index

Product	Page	Product	Page	Product	Page	Product	Page	Product	Page
7033	52	7831	51	7962MP	20	9045MP	28	9576	88
7034	49	7840HL	51	7965MP	20	9057MP	28	9579	24
7037	48	7841	57	7966MWS	28	9059MP	28	9599	24
7045	55	7847	58, 63	7966WDL	28	9061MP	28	9626	19
7049	55	7850-IJ	40, 50	7980	50	9069	76	9627	19
7053	55	7850HL	50	7992MP	28	9082	16	9628B	23
7070UV	74	7861	51	7993MP	28	9085	16	9628FL	23
7071UV	74	7863V	53	7995MP	28	9085UV	16	9629B	23
7110	58, 60, 64	7864	49	7997MP	28	9086	23	9629FL	23
7142	58	7865	52	8067	74	9087	23	9629PC	23
7214SA	54	7866	60	8087	71	9103	76	9653LE	18
7220SA	48	7868V	39, 48	8132LE	20	9114	76	9667MP	16
7222	52	7871V	39, 48, 62	8142KCL	21	9325	72	9668MP	16
7246	50	7871VFL	48	8153LE	20	9372DKW	17	9671	17
7247	52	7872V	39, 54	8171PCL	21	9372W	17	9671LE	18
7323V	39, 53	7873V	53	8211	21	9375W	17	9672	17
7331FL	49	7874	50	8212	21	9415PC	26	9672LE	18
7331V	39, 49, 64	7875V	39, 54	8213	21	9416	26	9675	18
7340FL	53	7876V	39, 51	8214	21	9420	88	9690+	22
7350	51	7879FL	52	8215	21	9425	26	9731	25
7350FL	51	7880	50	8387	88	9425HT	26	9731-100	25
7350V	39	7880HL	51	8402	71	9442	18	9731-50	25
7380	60	7881	52	8403	71	9443NP	24	9737	75
7381	60	7882-IJ	40, 50, 64	8403L	71	9445	18	9737R	75, 88
7384	60	7883	52	8412	71	9449S	26	9738	75
7600	59	7883HL	52	8417	61	9453FL	18	9738R	75, 88
7604FP	55	7901	56	8418	49	9453LE	18	9740	75, 88
7605	54	7902	55	8421	71	9456	23	9741	75, 88
7613T	60	7903FL	53	8422	71	9457	19	9741R	88
7730FL	61	7903V	39, 53	8437	71	9458	17	9772WL+	18
7731FL	61	7904	54	8524	62	9459W	17	9773WL+	18
7732FL	61	7905	51	8547	75	9461P	16	9774WL+	18
7733FL	61	7905V	39	8547-1	75	9462P	16	9775WL+	18
7735FL	62	7907	48	8555	74	9471	17	9816L	24
7737FL	62	7908FL	48	8777	74	9471FL	18	9816M	24
7738FL	62	7908V	39, 48	8901	71	9471LE	18	9817M	25
7741	61	7909V	39, 54	8902	71	9472	17	9824	23
7742	61	7924	53	8905	71	9472FL	18	9828	23
7744FL	61	7930T	55, 60	8911	71	9472LE	18	9828PC	23
7745FL	61	7931	49	8985L	71	9482PC	18	9832+	23
7776	57	7935	60	8991	71	9483	21	9832HL+	23
7777	56	7937	60	8991L	71	9485EK	18	9925XL	29
7779	56	7940	58	8992	71	9485PC	18	9934XL	29
7790-IJ	40, 56	7945MP	27	8992L	71	9495B	22	9960	76
7800	58	7950	51	8993LC	71	9495LE	22	9969	76
7810	50	7952MP	20	8997	70	9495MP	22	9977	76
7812	58	7953MP	27	8997L	70	9496LE	25	9990N	76
7813	52	7955MP	20	8998	70	9498	88	12026	82
7815	51	7956MP	27	8998L	70	9499	88	12028	82
7815FL	51	7956MWS	27	9009	22	9500PC	23, 88	12030	82
7816FL	49	7956WDL	27	9017FL	54	9502	17	12032	82
7816V	39, 49	7957MP	27	9018FL	54	9505	17	12034	82
7818	52	7959MP	27	9019	22	9552	20	12036	82
7830	49	7961MP	28	9038	76	9555	20	12038	82

Numerical Product Index

Product	Page	Product	Page	Product	Page	Product	Page	Product	Page
12046.....	82	E1515H.....	86	FM232.....	52	OFM010N.....	61	SJ3441.....	79
12048.....	82	E1520.....	86	FM452.....	61	OFM2402.....	53	SJ3442.....	79
12049.....	82	E1520H.....	86	FM45N.....	61	OFM2802.....	54	SJ3443.....	79
12050.....	82	E1715.....	86	FMV22.....	60	OFM2902.....	54	SJ3444.....	79
12054.....	82	E1715H.....	86	FP56N.....	59	OFM3102.....	52	SJ3445.....	79
12056.....	82	E1720.....	86	FP102.....	57	OFM03402.....	49	SJ3460.....	79
12062.....	82	E1720H.....	86	FP033-IJ.....	40, 56	OFV0202.....	55	SJ3463.....	79
76716NA.....	56	E1815.....	86	FP016102.....	57	PS015402.....	58	SJ3481.....	79
76999.....	58	E1815H.....	86	FP016902.....	59	R3037.....	76	SJ3506.....	80
92015.....	22	E1820.....	86	FP019802.....	63	R3127.....	76	SJ3507.....	80
93005LE.....	22	E1820H.....	86	FP022102.....	57	R3177.....	76	SJ3518FR.....	80
93010LE.....	22	E1840H.....	86	FP024402.....	59	R3187.....	76	SJ3519FR.....	80
93015LE.....	22	E1860H.....	86	FP029102.....	57	R3227.....	76	SJ3522.....	80
93020LE.....	22	E1915.....	86	FP032302.....	57	R3257.....	76	SJ3523.....	80
97053.....	19	E1915H.....	86	FP035402.....	64	R3287.....	76	SJ3526N.....	80
99786+.....	23	E1915HS.....	86	FP0862.....	59	R3345.....	76	SJ3527N.....	80
99786NP+.....	23	E1915S.....	86	FPE42.....	57	R3375.....	76	SJ3530.....	80
		E1920.....	86	FPE06602.....	57, 62	R3379.....	76	SJ3531.....	80
		E1920H.....	86	FTS0700.....	63	R5348.....	76	SJ3540.....	79
Alphanumeric		E1920HS.....	86	FV032.....	55	R7359.....	76	SJ3541.....	79
AP86A.....	88	E1920S.....	86	FV172.....	55	R7369.....	76	SJ3542.....	79
DCX 1018.....	24	F9460PC.....	16	FV292.....	55	R9993.....	76	SJ3550CF.....	79
E1015.....	86	F9465PC.....	19	FV1222.....	59	R9996.....	76	SJ3551CF.....	79
E1015H.....	86	F9467U.....	19	FV018602.....	55	R9999.....	76	SJ3552CF.....	79
E1020.....	86	F9469PC.....	16	FV023202.....	55	RP+040GF.....	34	SJ3560.....	79
E1020H.....	86	F9473PC.....	16	FV02490N.....	62	RP+040GP.....	34	SJ3561.....	79
E1040.....	86	FA112.....	60	FV027805.....	55	RP+060GF.....	34	SJ3562.....	79
E1060.....	86	FL01N.....	62	FV029405.....	55	RP+060GP.....	34	SJ3571.....	80
E1060H.....	86	FL02N.....	62	GPH-060GF.....	34	RP+080GF.....	34	SJ3572.....	80
E1115.....	86	FM011.....	61	GPH-110GF.....	34	RP+080GP.....	34	SJ3782.....	79
E1115H.....	86	FM01961K.....	51	GPH-160GF.....	34	RP+110GF.....	34	SJ3870.....	79
E1120.....	86	FM01972.....	59	GPT-020.....	21	RP+110GP.....	34	SJ3871.....	79
E1120H.....	86	FM034602.....	51	GPT-020F.....	21	RP+160GF.....	34	SJ3872.....	79
E1215.....	86	FM041902.....	49	IJ39-20.....	56	RP+160GP.....	34	SJ4570.....	79
E1215H.....	86	FM042.....	52	L1+DCP.....	31	RP+230GP.....	34	SJ4575.....	79
E1220.....	86	FM043702.....	53	L1+RT.....	31	RP+230GP.....	34	SJ4580.....	79
E1220H.....	86	FM047202.....	53	L3+T3.....	31	SJ3001.....	80	SP7202.....	30
E1315.....	86	FM062.....	54	L3+T5.....	31	SJ3401.....	80	SP7533.....	30
E1315H.....	86	FM071.....	61	LSE-060WF.....	34	SJ3402.....	80	SP7555.....	30
E1320.....	86	FM092.....	53	LSE-110WF.....	34	SJ3418FR.....	80	XT2105.....	17
E1320H.....	86	FM162.....	51	LSE-160WF.....	34	SJ3419FR.....	80	XT2112.....	17
E1515.....	86	FM1732R.....	59	OFL010N.....	62	SJ3440.....	79		

**Regulatory information for 3M IATD products is available at
3M.com/regs**

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.



**Industrial Adhesives and Tapes Division
3M Center, Building 225-3S-06
St. Paul, MN 55144-100
800-362-3550 877-369-2923 (Fax)
3M.com/converter**

3M, Bumpon, Comply, Controltac, Cushion-Mount, Dual Lock, ElectroCut, Flexomount, Safety-Walk, Scotch, Scotchcal, Scotchgard, Scotchlite, Scotch-Weld, Tartan and VHB are trademarks of 3M Company. All other trademarks of property of their respective owner. Please recycle. Printed in USA.
© 3M 2023. All rights reserved. 70-0707-7624-3 Rev July 2023